



BNL-213548-2020-JAAM

Accuracy of Thermodynamic Databases for Hydroxyapatite Dissolution Constant

N. Sahai, M. A. Schoonen

To be published in "ASTROBIOLOGY"

December 2019

Environment, Biology, Nuclear Science & Nonproliferation
Brookhaven National Laboratory

U.S. Department of Energy

~OTHER

Notice: This manuscript has been authored by employees of Brookhaven Science Associates, LLC under Contract No. DE-SC0012704 with the U.S. Department of Energy. The publisher by accepting the manuscript for publication acknowledges that the United States Government retains a non-exclusive, paid-up, irrevocable, world-wide license to publish or reproduce the published form of this manuscript, or allow others to do so, for United States Government purposes.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or any third party's use or the results of such use of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof or its contractors or subcontractors. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

BNL-213548-2020-JAAM

***Accuracy of Thermodynamic Databases for Hydroxyapatite
Dissolution Constant***

Nita Sahai^{1,2,3}*

and

Martin A. Schoonen^{4,5}

**¹Department of Polymer Science, ²Department of Geoscience,
and ³Integrated Bioscience Program, University of Akron, Akron, OH 44325, USA**

**⁴Environmental and Climate Sciences, Brookhaven National Laboratory Building 460,
P. O. Box 5000, Upton, NY 11973, USA;**

⁵Department of Geosciences, Stony Brook University, Stony Brook, NY 11794, USA

***corresponding author: sahai@uakron.edu**

Submitted to the journal ASTROBIOLOGY

December 2019

Environment, Biology, Nuclear Science & Nonproliferation Directorate

Brookhaven National Laboratory

**U.S. Department of Energy
Office of Science (SC)**

Biological and Environmental Research (BER) (SC-023)

Notice: This manuscript has been authored by employees of Brookhaven Science Associates, LLC under Contract No. DE- SC0012704 with the U.S. Department of Energy. The publisher by accepting the manuscript for publication acknowledges that the United States Government retains a non-exclusive, paid-up, irrevocable, world-wide license to publish or reproduce the published form of this manuscript, or allow others to do so, for United States Government purposes.

Accuracy of Thermodynamic Databases for Hydroxyapatite Dissolution Constant

Nita Sahai^{1,2,3} *

and

Martin A. Schoonen^{4,5}

¹Department of Polymer Science, ²Department of Geoscience, and ³Integrated Bioscience Program, University of Akron, Akron, OH 44325, USA

⁴Environmental and Climate Sciences, Brookhaven National Laboratory Building 460, P. O. Box 5000, Upton, NY 11973, USA; ⁵Department of Geosciences, Stony Brook University, Stony Brook, NY 11794, USA

*corresponding author: sahai@uakron.edu

Abstract

Discrepancies have been noted in the solubility constant values of calcium phosphate minerals between various databases employed in widely-used aqueous speciation calculation software programs. This can cause serious errors in the calculated speciation of waters using these software programs. The aim of the present communication was to bring to light these discrepancies. Experimental determinations of the hydroxyapatite solubility product vary by as much as ten orders of magnitude as a result of experimental challenges related to the presence of impurities in the hydroxyapatite used, incongruent dissolution and the contamination of solutions with dissolved carbon dioxide. It is suggested that the value used in the database Thermo.dat is consistent with experimental data devoid of common experimental problems, while other common databases use values that lead to a vastly overestimated solubility of hydroxyapatite.

1. Introduction

The accuracy of thermodynamic databases employed in aqueous speciation codes is critical to obtaining reliable results from the codes. Some widely used software and thermodynamic databases in the fields of aqueous geochemistry and environmental chemistry are the EQ3/EQ6 (Wolery, 1992), Geochemists' Workbench[®] (Bethke et al., 2019) and PHREEQC (Parkhurst and Apello, 1999). The original database, Thermo.dat, was developed at Lawrence Livermore National Laboratory and used in the pioneering code, EQ3/EQ6 (Wolery, 1992). This database was subsequently updated by Lawrence Livermore National Laboratory and referred to with the name THERMO.COM.V8.R6+. PHREEQC uses its own database. All three databases are available as options in Geochemist's Workbench[®]. We recently became interested in calculating the speciation of calcium and phosphate, among other ions, in a specific research context. Therefore, we undertook a comparison of the solubility constants (K_{sp}) for calcium phosphate minerals in these three thermodynamic databases. We were surprised to discover that wide discrepancies exist in the values reported for calcium phosphate minerals, such as hydroxyapatite ($\text{Ca}_5(\text{PO}_4)_3\text{OH}$, HAP), fluorapatite ($\text{Ca}_5(\text{PO}_4)_3\text{F}$) and whitlockite ($\text{Ca}_3(\text{PO}_4)_2$) between the three databases. We, therefore, became concerned with determining which database had the accurate K_{sp} values. The goal of this short communication is to share the results of our investigation.

2.0 Methods

2.1 Determining the accurate solubility constant of HAP

We chose to use HAP (note that the mineral is referred to as hydroxylapatite in THERMO.dat and THERMO.COM.V8.R6+.) as the case mineral to determine which thermodynamic database

reports the accurate values of solubility products. We subsequently compared this value to those reported in the various thermodynamic databases.

2.2 Speciation calculations

We also ran a speciation calculation on Geochemist's Workbench[®] for a system in which 5 gram of HAP is equilibrated with 1 kg pure water at 298°K using the three databases and compared the output in terms of calcium and phosphate speciation.


3. Results and Discussion

3.1 Determining the accurate solubility constant of HAP

We first calculated the standard Gibb's free energy of reaction (ΔG_r^0) for dissolution of HAP.

Since all three databases in Geochemist's Workbench[®] use a stoichiometry for HAP which is

$\text{Ca}_5(\text{PO}_4)_3\text{OH}$, we write the dissolution equation using this stoichiometry:



using the standard Gibb's free energy of formation of the *i-th* reactants and products ($\Delta G_{f,i}^0$),

according to:

$$\Delta G_r^0 = 10\Delta G_{f,\text{Ca}^{2+}}^0 + 6\Delta G_{f,\text{PO}_4^{3-}}^0 + 2\Delta G_{f,\text{OH}^{-}}^0 - \Delta G_{f,\text{HAP}}^0 \quad (2)$$

Using standard Gibb's free energy of formation from Faure (1998) (Table 1), we obtain $\Delta G_r^0 =$

$$84.4 \text{ kcal.mol}^{-1} \quad (3)$$


Relating ΔG_r^0 to the equilibrium constant, K_{sp} , we obtain:

$$\log K_{\text{sp}} = \frac{-\Delta G_r^0}{2.303RT} = -61.9 \quad (4)$$

where R is the ideal gas constant = $1.987 \times 10^{-3} \text{ kcal.mol}^{-1}\text{K}^{-1}$ and T is the absolute temperature

(K).

The equation for solubility of HAP in THERMO.DAT with the corresponding log K value is:




To make the right-hand side of Eq (5) consistent with the presence of $\text{OH}^-_{(\text{aq})}$ as in Eq (1), we

add:




to yield:



To make the right-hand side of Eq 7 consistent with the presence of PO_4^{3-} in Eq (1), we add:




to obtain:



The log K value in Eq (9) value is similar (within 0.5 log units) to that obtained from the standard Gibbs' Free energies of formation (Eq 4). This suggests that the value in Thermo.dat is accurate.

The equation for solubility of HAP in THERMO.COM.V8.R6+ with the corresponding log K value is:




To make the right-hand side of Eq (10) consistent with the presence of $\text{OH}^-_{(\text{aq})}$ as in Eq (1), we

add:




to yield:



To make the right-hand side of Eq 12 consistent with the presence of PO_4^{3-} in Eq (1), we add:




to obtain:



The $\log K_{\text{sp}}$ value in Eq (14) is dissimilar to that obtained from standard Gibbs' Free energies of formation (Eq 4) or to the value in Thermo.dat (Eq. 9). The value in Thermo.com.V8.R6+ is off from the accurate value obtained from Gibb's free energies of formation by -8 log units.

The equation for solubility of HAP in PHREEQC with the corresponding log K value is:



To make the right-hand side of Eq (15) consistent with the presence of $\text{OH}^-_{(\text{aq})}$ as in Eq (1), we add:



to yield:



The $\log K_{\text{sp}}$ value in Eq. (17) is dissimilar to that obtained from standard Gibbs' Free energies of formation (Eq 4) or to the value in Thermo.dat (Eq. 9) but is identical to the value obtained from Thermo.COM.V8.R6+ dat (Eq. 14).

3.2 Speciation Calculations

Table 2 and Figure 1 show the results of the speciation calculation for the solubility of HAP in water. The results from using the Thermo.COM.V8.R6+ and the PHREEQC databases are similar to each other but different from those obtained by using the Thermo.dat database. The concentrations of Ca^{2+} and total PO_4 ($\sim = \text{H}_2\text{PO}_4^- + \text{HPO}_4^{2-}$) are overpredicted by a factor of 4.5 to 5 when using either the Thermo.COM.V8.R6+ or the PHREEQC database compared to that predicted by Thermo.dat. The pH of the solution is also overpredicted by 0.7 units.

3.3 Comparison with Experimental K_{sp} Values

The experimental measurement of K_{sp} values for a mineral such as HAP that is so highly insoluble is a challenging task. Various values have been reported in the literature for K_{sp} of HAP, including -58.5 (Avnimelech et al., 1973; McDowell et al., 1977), -57.5 (Bell et al., 1979), -56.2 (Jaynes et al., 1999) and -53.3 (Zhu et al., 2009) to state a few. With the exception of the value reported by Zhu et al. (2009), which is consistent with the values in the Thermo.COM.V8.R6+ or the PHREEQC database, all the remaining values are similar and suggest a more negative value of K_{sp} . The challenge of determining an accurate value of K_{sp} for calcium phosphate phases was discussed in detail by Pan and Darvell (2009). These authors noted that the conventional method of determining the K_{sp} of HAP is by the “large excess of solid” method, wherein a large amount of HAP is added to a solution and the analyzed solution concentration is combined with ionic speciation calculations to obtain K_{sp} . Pan and Darvell (2009) noted in detail that incongruent dissolution, phase transformation, inaccurate speciation calculations and contamination by ions, especially CO_2 , leads to the large variation in reported K_{sp} values. In particular, the presence of CO_2 in the initially synthesized solid, which is subsequently used for the dissolution experiment, increases the solubility of the HAP. A value of

-57.5 was obtained by Bell et al. (1979) by strict elimination of CO₂ contamination, whereas similar precautions were not stated in the study by Zhu et al. (2009). Pan and Darvell (2009) suggested an alternative method to determine the K_{sp} of calcium phosphate phases, which is the “solid titration” method. This method eliminates the errors introduced by the phenomena listed above. Using the solid titration method, Pan and Darvell (2009) determined a K_{sp} of HAP = -63, which is even more negative than the values determined by previous workers (Avnimelech et al., 1973; McDowell et al., 1977; Bell et al. 1979) and close to but also more negative than the theoretical value of -61.9 obtained in the present study from free energies of formation (Eq. 4). The value of -63 is very close to the value of -62.4 used in Thermo.dat. Therefore, based on the above discussion, it is concluded that the value reported in Thermo.dat is the most accurate of the three databases.

4. Conclusions

Combining our result for the K_{sp} value calculated from Gibbs free energies of formation and the experimental K_{sp} value of -63 obtained by the solid titration method, the THERMO.dat value is deemed to be consistent with the best available experimental data, whereas the values reported in THERMO.COM.V8.R6+ and PHREEQC are not correct. Although we have not conducted a similar analysis for other metal phosphate minerals, discrepancies exist in the K_{sp} values for the calcium phosphate minerals, fluorapatite and whitlockite, between the three databases. Based on the analysis for HAP, we believe that the K_{sp} values for the other calcium phosphate minerals in Thermo.dat will be accurate.

Acknowledgements: NS thanks Dr. Edward Weil for a generous gift fund.

REFERENCES

Avnimelech, Y., Moreno E. C., and Brown W. E. (1973) Solubility and surface properties of finely divided hydroxyapatite. *J. Res. Nat. Bur. Stand.* 73A: 149-155.

Bell, L. C., Mika, H., and Kruger, B. J. (1978) Synthetic hydroxyapatite-solubility product and stoichiometry of dissolution. *Arch. Oral. Biol.* 23: 329-336.

Bethke, C., Farrell B. and Yeakel, S. (2019) The Geochemist's Workbench[®] Release 12. GWB Essentials Guide, 186 pp.

Faure G. (1998) *Principles and Applications of Geochemistry*. 2nd ed. Prentice Hall, NJ, 600 pp, Appendix B.

Jaynes, W. F., Moore, P. A, Jr., and Miller, D. M. (1999) Solubility and ion activity products of calcium phosphate minerals. *J. Env. Qual.* 28: 530-536.

McDowell, H., Gregory T. M., and Brown W. E. (1977) Solubility of $\text{Ca}_5(\text{PO}_4)_3\text{OH}$ in the system $\text{Ca}(\text{OH})_2\text{-H}_2\text{PO}_4\text{-H}_2\text{O}$ at 5, 15, 25 and 37 °C. *J. Res. Nat. Bur. Stand.* 81A: 273-281.

Pan, H.-B. and Darvell, B. W. (2009) Calcium phosphate solubility: The need for re-evaluation. *Cryst. Growth. Design* 9: 639-645.

Parkhurst, D. L. and Apello, C.A.J. (1999) User's guide to PHREEQC (version 2), a computer program for speciation, batch-reaction, one-dimensional transport and inverse geochemical calculations. USGS Water-Resources Investigations Report 99-4259.

Wolery, T. J. (1992) EQ3/EQ6, A software package for geochemical modeling of aqueous systems: Package overview and installation guide (Version 7). Lawrence Livermore National Laboratory Report, UCRL-MA-110662, 66 pp.

Zhu, Y., Zhang, X., Chen, Y., Qinlin, X., Lan, J. Qian, M. and He, N. (2009) A comparative study on the dissolution and solubility of hydroxyapatite and fluorapatite at 25⁰C and 45⁰C. *Chem. Geol.* 268, 89-96.

Figure Captions

Figure 1. Concentrations of calcium ion and total dissolved phosphate in equilibrium with HAP in water using the three thermodynamic databases available in Geochemist's Workbench[®].

Table 1. Standard Gibbs free energy of formation of the *i-th* species (Faure, 1998)

Species	$\Delta G_{f,i}^0$ (kcal.mol ⁻¹)
Hydroxyapatite, Ca ₁₀ (PO ₄) ₆ (OH)	-3030
Ca ²⁺ _(aq)	-132.5
PO ₄ ²⁻ _(aq)	-243.5
OH ⁻ _(aq)	-37.6

Table 2. Results of speciation calculations for the solubility of HAP in water using the three thermodynamic databases in Geochemist's Workbench®.

Aqueous Species	Thermo.dat (molal)	THERMO.COM.V8.R6+ (molal)	PHREEQC (molal)
Ca ²⁺ _(aq)	2.968 e-06	1.512 e-05	1.408 e-05
OH ⁻ _(aq)	2.416 e-06	1.214 e-05	1.131 e-05
HPO ₄ ²⁻ _(aq)	1.703 e-06	8.879 e-06	8.27 e-06
H ₂ PO ₄ ⁻ _(aq)	1.157 e-07	1.167 e-07	1.161 e-07
P _{tot, (aq)}	1.819 e-06	8.996 e-06	8.386 e-06
pH	8.368	9.076	9.049