# Nature-inspired methylated polyhydroxybutyrates from C1 and C4 feedstocks

**Authors:** Zhiyao Zhou[1], Anne M. LaPointe[1], Timothy D. Shaffer[2] & Geoffrey W. Coates[1]*

**Affiliations:**

[1]Department of Chemistry and Chemical Biology, Baker Laboratory, Cornell University, Ithaca, NY 14853, USA.

[2]ExxonMobil Technology and Engineering Company, 1545 Route 22, Annandale, NJ 08801, USA

**Abstract:** Polyolefin plastics are widely used due to their low cost and outstanding properties, but their environmental persistence presents a major societal challenge. Polyhydroxyalkanoates (PHA) are biodegradable substitutes for polyolefins; however, their high cost and thermal instability are impediments to their widespread applications. Here we report a series of methylated polyhydroxybutyrates, poly(3-hydroxy-2-methylbutyrate)s, that are structurally inspired by natural PHAs. The *cis* homopolymers exhibit tacticity-independent crystallinity, which allows for the discovery of high-melting, thermally stable, and mechanically tough copolymers, and a full range of polyolefin-like properties can be further achieved by tailoring the *cis*/*trans* ratio of the repeating units. Moreover, these materials can be synthesized from inexpensive carbon monoxide and 2-butene feedstocks and they can be chemically recycled or upcycled at their end-of-life. The versatile properties, abundant feedstocks, and end-of-life utility of this family of polyesters will enable a powerful platform for the discovery of sustainable alternatives to polyolefin plastics.

In the year 2020, the cumulative global mass of synthetic plastics achieved the dubious distinction of exceeding the total combined mass of all terrestrial and marine animals[1]. As an inevitable consequence, the ever-growing amount of plastic waste has become a major threat to

the planet, despite governmental action to mitigate plastic pollution[2]. While mechanical recycling provides a means to collect and sort postconsumer plastics, alternative strategies, such as biodegradation, are needed to tackle plastic wastes that leak into the environment, especially the most common[3] yet environmentally persistent polyolefins, with an estimated 4.8-12.7 million metric tons of total plastics entering the ocean in 2010[4]. In this regard, the biodegradable polyhydroxyalkanoates[5,6] (PHA) produced by bacteria continue to attract industrial attention as potential substitutes for polyolefin plastics in packaging and other single-use applications. A major member of the PHA family is isotactic poly[(*R*)-3-hydroxybutyrate] (*R*-P3HB), which may also be produced via chemical synthesis[7,8,9,10]. It exhibits low toxicity and a high melting point (ca. 175 °C) that is similar to isotactic polypropylene (*i*PP), but the low production volumes, brittleness and thermal instability of *R*-P3HB homopolymers have limited their widespread use. Although the mechanical properties of *R*-P3HB may be improved by copolymerizing with other monomers [11,12,13], or in combination with more elaborate stereochemical and sequence control[14], other problems have not been fully addressed. While major efforts were focused on variations at C3 position of repeating units, we report herein a family of methylated polyhydroxybutyrates, poly(3-hydroxy-2-methylbutyrate) (PHMB, Fig. 1a), that contain an extra methyl substituent and stereocenter at the C2-position. This structural evolution enables us to establish a versatile platform of PHA polymers with enhanced thermal stability, and their melting points and mechanical strength are close or superior to various commodity plastics[15] (Fig. 1b). Such properties can be further tailored by altering the polymer tacticity and the *cis*/*trans* ratio of the monomers.

While the 3-hydroxy-2-methylbutyrate (HMB) repeating unit has been incorporated into P3HB copolymers via ring-opening copolymerization[16] as well as bacterial engineering[17,18,19,20,21], PHMB homopolymers have only been reported very recently[22,23]. While *cis*- or *trans*-PHMB homopolymers can be prepared by an efficient one-pot carbonylation/polymerization reaction, the

materials were amorphous[22]. The enantiopure (2R, 3R)-*trans*-PHMB homopolymer can be biosynthesized from gene-modified bacteria[23] and exhibits superior thermal and mechanical properties. However, a systematic evaluation of the full potential of PHMB, especially via chemical synthesis, has not been performed. Based on our previous success in streamlined syntheses of other PHA polymers, such as P3HB[24] and poly(3-hydroxypropionate) (P3HP)[25], we designed a similar strategy that can produce PHMB from 2-butene oxide and CO via carbonylation and polymerization reactions (Fig. 1c). 2-Butene oxide can be industrially produced by the epoxidation of 2-butene[26], an abundant C4 feedstock that can be derived from both fossil fuel and biorenewable sources[27,28]. Alternatively, 2-butene oxide can also be prepared via dehydration[29] of microbially produced 2,3-butanediol[30]. Catalytic carbonylation of the epoxides with CO in the presence of [Lewis acid]$^+$[Co(CO)$_4$]$^-$ complexes[31,32,33,34] yields 2,3-dimethyl-$\beta$-propiolactone (DMPL**)** with inversion of stereochemistry at the site of ring-opening. With this method, *cis*- and *trans*-DMPL can be easily produced on decagram scale in the laboratory (see SI for details). PHMB can thus be prepared with tunable microstructures from both DMPL isomers in the presence of suitable metal alkoxide catalysts. We decided to initially pursue the homopolymerization of *cis*-DMPL, as it is derived from the more accessible, thermodynamically more stable *trans*-2-butene and *trans*-2-butene oxide feedstocks[26,35].

**Results and discussion**

Inspired by the seminal discovery of syndiotactic $\beta$-butyrolactone (BBL) polymerization using single-site yttrium complexes[36,37,38], the polymerization of *cis*-DMPL using complex A[39] was investigated (Supplementary Table S1). The polymerization was complete within 2 h, resulting in high molecular weight ($M_n$ >100 kDa) PHMB with excellent syndiotacticity (95% *racemo* diad, $P_r$ = 0.95). The polymer obtained is semicrystalline and exhibits a high $T_m$ (> 200 °C). While the syndiotactic *cis*-PHMB's physical properties are promising, the limited availability

and high price of yttrium limit the industrial-scale production of such material. We therefore investigated zinc-based catalysts that are earth-abundant and highly active for BBL polymerization[24,40]. Mehrkhodavandi and coworkers recently reported a series of zinc phenoxide catalysts that initiated polymerization of BBL with extremely high turnover frequency[41] to give syndioenriched P3HB. Prompted by these studies, we found that *in situ* generated complexes B[42] and C both produce *cis*-PHMB with high molecular weight ($M_n$ >100 kDa), narrow dispersity ($Đ$ <1.1), and >99% conversion in 24 h (Supplementary Table S1). Complex B gives higher syndiotacticity ($P_r$ = 0.75), possibly due to the presence of a $C_s$ symmetrical bispyrazole-phenoxide ligand backbone (Supplementary Fig. S16). Complex C induces similar degrees of syndiotacticity ($P_r$ = 0.63) in *cis*-PHMB compared to previous P3HB synthesis[41] with similar catalysts. Both PHMB polymers, however, are semicrystalline with high $T_m$, and their melting temperatures decrease slightly with deceasing tacticity. *Surprisingly, completely atactic cis-PHMB is also semicrystalline with a high melting point (Supplementary Table S1)*. Similar powder X-ray diffraction (PXRD) patterns were observed for all *cis*-PHMB samples, regardless of stereoregularity (Supplementary Fig. S24). The tacticity-independent crystallinity[43,44,45,46,47] and extremely high melting points were unexpected and may permit the use of *cis*-PHMB as a versatile crystalline component in PHA thermoplastics. However, all these materials are brittle, with strain at break ($\varepsilon_B$) not exceeding 20% (Fig. 2). The brittleness across these materials severely limits their further applications and suggests that simply adjusting the tacticity is insufficient to improve their mechanical properties. Thus, we embarked on other structural modifications to solve this limitation.

The toughness of *R*-P3HB can be improved by copolymerization with different comonomers bearing similar chemical structures[10,11]. With this strategy, *trans*-DMPL may be an ideal comonomer due to its structural resemblance to the *cis* isomer. In addition, the comonomer

stream could come from a mixture of 2-butene without laborious separation of the two stereoisomers, which would greatly enhance its industrial practicality. Since the copolymer would likely have diminished crystallinity and thermal behaviors, we chose complex B for further studies, hoping that the higher syndiotacticity it provided in *cis*-PHMB could offset the decreased $T_m$ from stereodefects introduced by the comonomer. When the mixtures of DMPL isomers with varied *cis* content (90%, 80% and 70%) were polymerized by complex B, high molecular weight copolymers of PHMB were obtained (Fig. 3a and Supplementary Table S2). All three copolymers exhibit semicrystallinity albeit with moderate tacticity for the major *cis* composition. Although their $T_m$ and $T_c$ decrease with lower *cis* content (Fig. 3b), these copolymers still maintain high melting points ($T_m$ >130 °C). Unlike *R*-P3HB[48], minimal decrease in molecular weight or broadening of dispersity was observed when the selected PHMB copolymer was heated at 170 °C (Supplementary Fig. S44). Similar enhancement in thermal stability was also reported for biosynthesized *trans*-PMHB[23]. Further kinetic experiments showed that the *cis*-DMPL was consumed faster than the *trans* isomer ($k_{cis}/k_{trans}$ = 4.0, Supplementary Fig. S45-S46) in the copolymerization, indicating that the copolymers are tapered rather than completely random. Given the lower melting points and attenuated crystallinity of the copolymers, we expected that the copolymerization strategy might improve the ductility and toughness of the materials.

We then measured the tensile properties of the three copolymers (Fig. 3c). Encouragingly, all copolymers are tough materials with $\varepsilon_B$ greater than 300%. At higher *cis*-DMPL content (90%), the copolymer behaves very similar to *i*PP and high-density polyethylene (HDPE), with a high yield stress ($\sigma_Y$ = 26.1 ± 1.3 MPa) and ductility ($\varepsilon_B$ = 373 ± 50%). Although it is less stiff than the hard polyolefins, with Young's modulus ($E$) = 0.34 ± 0.01 GPa, it possesses a higher stress at break ($\sigma_B$ = 30.7 ± 1.3 MPa). Upon lowering the *cis* content to 80%, the copolymer becomes softer and resembles low-density polyethylene (LDPE) with similar yield stress ($\sigma_Y$ = 10.3 ± 0.2 MPa) and

Young's modulus ($E$ = 0.106±0.003 GPa). Moreover, it is more ductile ($\varepsilon_B$ = 783±7%) and tougher, exhibiting a much higher stress at break ($\sigma_B$ = 36.6±0.1 MPa) than LDPE. If the *cis*-DMPL percentage is further decreased to 70%, the copolymer is even softer and can be stretched to about 10 times of its original length ($\varepsilon_B$ = 1020±55%). The ductility of these copolymers is further illustrated by the photos taken before and after being stretched (Fig. 3c). All the copolymers obtained here exhibit high tensile toughness (96~177 MJ/m$^3$) that are close to or higher than the reference polyolefin samples. These results demonstrate that a full spectrum of different polyolefin-like materials, from hard to soft, can be easily obtained by simply adjusting the *cis*-DMPL content in the comonomer mixture, which can be precisely controlled by the *trans*/*cis* ratio of starting 2-butene and 2-butene oxide.

Finally, we carried out a preliminary depolymerization study of PHMB to tiglic acid[23,48,49] (Fig. 4). In the presence of MgO (1 wt%), PHMB can be depolymerized cleanly at 200 °C to give pure tiglic acid with 93% yield. Since tiglic acid was used as a feedstock for the biosynthesis of *trans*-PMHB[23], this process offers potential open-loop chemical recycling of PHMB. Through further pyrolysis of tiglic acid into *trans*-2-butene[50] and *cis*/*trans* isomerization of 2-butenes[35], this approach could also permit alternative closed-loop chemical recycling of PHMB. In addition, tiglic acid and its esters have been commonly used in fragrance and food additives, suggesting that PHMB may be also upcycled to value-added products in a green, atom-economic manner. The facile post-consumer transformations of PHMB will permit additional avenues for their waste management.

In conclusion, we have discovered a class of synthetic PHA materials, PHMBs, that can be easily synthesized from industrial C4 feedstocks 2-butene and carbon monoxide in a practical and scalable manner, and may biodegrade, be recycled, or upcycled. The *cis*-PHMB homopolymers exhibit tacticity-independent crystallinity and high melting points, and by copolymerizing both

*cis*- and *trans*-DMPL, we can obtain a full range of tough and high-melting copolymer materials that mimic commodity polyolefin plastics in a well-controlled and predictable manner. The study of the biodegradability and industrial composting ability of these polymers is ongoing, and we also plan to study their compatibility as blending materials to improve the properties of other biodegradable polymers. These materials could provide a promising platform for sustainable alternatives to polyolefin plastics, and their facile synthesis, renewable sourcing, and potential biodegradability may provide an additional way to mitigate plastic pollution.

## References


1. Elhacham, E. et al. Global human-made mass exceeds all living biomass. *Nature* **588**, 442–444 (2020).
2. Borrelle, S. B. et al. Predicted growth in plastic waste exceeds efforts to mitigate plastic pollution. *Science* **369**, 1515–1518 (2020).
3. Geyer, R., Jambeck, J. R. & Law, K. L. Production, use, and fate of all plastics ever made. *Sci. Adv.* **3**, e1700782 (2017).
4. Jambeck, J. R. et al. Plastic waste inputs from land into the ocean. *Science* **347**, 768–771 (2015).
5. Müller, H. M. & Seebach, D. Poly(hydroxyalkanoates): a fifth class of physiologically important organic biopolymers? *Angew. Chem. Int. Ed. Eng.* **32**, 477–502 (1993).
6. Sudesh, K., Abe, H. & Doi, Y. Synthesis, structure and properties of polyhydroxyalkanoates: biological polyesters. *Prog. Polym. Sci.* **25**, 1503–1555 (2000).
7. Ajellal, N. et al. Polymerization of racemic β-butyrolactone using supported catalysts: a simple access to isotactic polymers. *Chem. Commun.* **46**, 1032–1034 (2010).

8. Tang, X. & Chen, E. Y.-X. Chemical synthesis of perfectly isotactic and high melting bacterial poly (3-hydroxybutyrate) from bio-sourced racemic cyclic diolide. *Nat. Commun.* **9**, 2345 (2018).
9. Dong, X. & Robinson, J. R. The role of neutral donor ligands in the isoselective ring-opening polymerization of rac-β-butyrolactone. *Chem. Sci.* **11**, 8184–8195 (2020).
10. Westlie, A. H., Quinn, E. C., Parker, C. R., & Chen, E. Y. X. Synthetic Biodegradable Polyhydroxyalkanoates (PHAs): Recent Advances and Future Challenges. *Prog. Poly. Sci.* **134**, 101608 (2022).
11. Noda, I., Lindsey, S. B. & Caraway, D. "Nodax™ Class PHA Copolymers: Their Properties and Applications." In: *Plastics from Bacteria.* G.-Q. Chen Ed., vol. 14 of *Microbiology Monographs* (Springer, Berlin, 2010) 237–255.
12. Tang, X. et al. Biodegradable polyhydroxyalkanoates by stereoselective copolymerization of racemic diolides: stereocontrol and polyolefin-like properties. *Angew. Chem. Int. Ed.* **59**, 7881–7890 (2020).
13. Tang, X., Shi, C., Zhang, Z. & Chen, E. Y.-X. Toughening biodegradable isotactic poly(3-hydroxybutyrate) via stereoselective copolymerization of a diolide and lactones. *Macromolecules* ***54***, 9401–9409 (2021).
14. Tang, X., Westlie, A. H., Watson, E. M. & Chen, E. Y.-X. Stereosequenced crystalline polyhydroxyalkanoates from diastereomeric monomer mixtures. *Science* **366**, 754–758 (2019).
15. Jost, V. Packaging related properties of commercially available biopolymers–an overview of the status quo. *EXPRESS Polym. Lett.* **12**, 429–435 (2018).
16. Kobayashi, T., Yamaguchi, A., Hagiwara, T. & Hori, Y. Synthesis of poly(3-hydroxyalkanoate)s by ring-opening copolymerization of (R)-β-butyrolactone with other four-

membered lactones using a distannoxane complex as a catalyst. *Polymer* **36** 4707–4710 (1995).

17. Füchtenbusch, B., Fabritius, D. & Steinbüchel, A. Incorporation of 2-methyl-3-hydroxybutyric acid into polyhydroxyalkanoic acids by axenic cultures in defined media. *FEMS Microbiol. Lett.* **138**, 153–160 (1996).
18. Watanabe, Y., Ishizuka, K., Furutate, S., Abe, H. & Tsuge, T. Biosynthesis and characterization of novel poly(3-hydroxybutyrate-co-3-hydroxy-2-methylbutyrate): thermal behavior associated with α-carbon methylation. *RSC Adv.* **5**, 58679–58685 (2015).
19. Furutate, S. et al. Biosynthesis and characterization of novel polyhydroxyalkanoate copolymers consisting of 3-hydroxy-2-methylbutyrate and 3-hydroxyhexanoate. *J. Polym. Res.* **24**, 221 (2017).
20. Dong, H., Liffland, S., Hillmyer, M. A. & Chang, M. C. Engineering in vivo production of α-branched polyesters. *J. Am. Chem. Soc.* **141**, 16877–16883 (2019).
21. Furutate, S., Abe, H. & Tsuge, T. Thermal properties of poly(3-hydroxy-2-methylbutyrate-co-3-hydroxybutyrate) copolymers with narrow comonomer-unit compositional distributions. *Polym. J.* **53,** 1451–1457 (2021).
22. Yang, J.-C., Yang, J., Li, W.-B., Lu, X.-B. & Liu, Y. Carbonylative polymerization of epoxides mediated by tri-metallic complexes: a dual catalysis strategy for synthesis of biodegradable polyhydroxyalkanoates. *Angew. Chem. Int. Ed.* **61***,* e202116208 (2022).
23. Furutate, S. *et al.* Superior thermal stability and fast crystallization behavior of a novel, biodegradable α-methylated bacterial polyester. *NPG Asia Mater.* **13**, 31 (2021).
24. Dunn, E. W. & Coates, G. W. Carbonylative polymerization of propylene oxide: a multicatalytic approach to the synthesis of poly(3-hydroxybutyrate). *J. Am. Chem. Soc.* **132**, 11412–11413 (2010).

25. Dunn, E. W., Lamb, J. R., LaPointe, A. M. & Coates, G. W. Carbonylation of ethylene oxide to β-propiolactone: a facile route to poly(3-hydroxypropionate) and acrylic acid. *ACS Catal.* ***6***, 8219−8223 (2016).

26. Berndt, T., Kreipl, A. & Lenski, U. Epoxidation of 2-butene from raffinate 2 feedstock. *Ind. Eng. Chem. Res*. **49**, 3957–3960 (2010).

27. Bond, J. Q., Alonso, D. M., Wang, D., West, R. M. & Dumesic, J. A. Integrated catalytic conversion of γ-valerolactone to liquid alkenes for transportation fuels. *Science* **327**, 1110–1114 (2010).

28. Lin, L. et al. Quantitative production of butenes from biomass-derived γ-valerolactone catalysed by hetero-atomic MFI zeolite. *Nat. Mater.* **19**, 86–93 (2020).

29. Kim, T. Y. et al. Gas-phase dehydration of vicinal diols to epoxides: dehydrative epoxidation over a $Cs/SiO_2$ catalyst. *J. Catal.* **323**, 85–99 (2015).

30. Song, C. W., Park, J. M., Chung, S. C., Lee, S. Y. & Song, H. Microbial production of 2,3-butanediol for industrial applications. *J. Ind. Microbiol. Biotechnol.* **46**, 1583–1601 (2019).

31. Mahadevan, V., Getzler, Y. D. Y. L. & Coates, G. W. $[Lewis\ Acid]^+[Co(CO)_4]^-$ complexes: a versatile class of catalysts for carbonylative ring expansion of epoxides and aziridines. *Angew. Chem. Int. Ed.* **41**, 2781–2784 (2002).

32. Schmidt, J. A. R., Mahadevan, V., Getzler, Y. D. Y. L. & Coates, G. W. A readily synthesized and highly active epoxide carbonylation catalyst based on a chromium porphyrin framework: expanding the range of available β-lactones. *Org. Lett.* **6**, 373–376 (2004).

33. Schmidt, J. A. R., Lobkovsky, E. B. & Coates, G. W. Chromium (III) octaethylporphyrinato tetracarbonylcobaltate: a highly active, selective, and versatile catalyst for epoxide carbonylation. *J. Am. Chem. Soc.* **127**, 11426–11435 (2005).

34. Rowley, J. M., Lobkovsky, E. B. & Coates, G. W. Catalytic double carbonylation of epoxides to succinic anhydrides: catalyst discovery, reaction scope, and mechanism. *J. Am. Chem. Soc.* **129**, 4948–4960 (2007).

35. Pavlov, O. S., Karsakov, S. A. & Pavlov, S. Y. 1-Butene and 2-butenes production using the positional isomerization of butenes catalyzed by sulfonic acid cation exchangers. *Theor. Found. Chem. Eng.* **44,** 531–535 (2010).

36. Amgoune, A., Thomas, C. M., Ilinca, S., Roisnel, T. & Carpentier, J.-F. Highly active, productive, and syndiospecific yttrium initiators for the polymerization of racemic β-butyrolactone. *Angew. Chem. Int. Ed.* **45**, 2782–2784 (2006).

37. Ajellal, N. et al. Syndiotactic-enriched poly(3-hydroxybutyrate)s via stereoselective ring-opening polymerization of racemic β-butyrolactone with discrete yttrium catalysts. *Macromolecules*, **42**, 987–993 (2009).

38. Carpentier, J.-F. Rare-earth complexes supported by tripodal tetradentate bis(phenolate) ligands: a privileged class of catalysts for ring-opening polymerization of cyclic esters. *Organometallics* **34**, 4175–4189 (2015).

39. Kramer, J. W. et al. Polymerization of enantiopure monomers using syndiospecific catalysts: a new approach to sequence control in polymer synthesis. *J. Am. Chem. Soc.* **131**, 16042–16044 (2009).

40. Rieth, L. R., Moore, D. R., Lobkovsky, E. B. & Coates, G. W. Single-site β-diiminate zinc catalysts for the ring-opening polymerization of β-butyrolactone and β-valerolactone to poly (3-hydroxyalkanoates). *J. Am. Chem. Soc.* **124**, 15239–15248 (2002).

41. Ebrahimi, T., Aluthge, D. C., Hatzikiriakos, S. G. & Mehrkhodavandi, P. Highly active chiral zinc catalysts for immortal polymerization of β-butyrolactone form melt processable syndio-rich poly(hydroxybutyrate). *Macromolecules* **49**, 8812–8824 (2016).

42. Schofield, A. D., Barros, M. L., Cushion, M. G., Schwarz, A. D. & Mountford, P. Sodium, magnesium and zinc complexes of mono(phenolate) heteroscorpionate ligands. *Dalton Trans.* 85–96 (2009).

43. Ruiz de Ballesteros, O. et al. Thermal and structural characterization of poly(methylene-1, 3-cyclopentane) samples of different microstructures. *Macromolecules* **28**, 2383–2388 (1995).

44. Lee, L.-B. W. & Register, R. A. Hydrogenated ring-opened polynorbornene: a highly crystalline atactic polymer. *Macromolecules* **38***,* 1216–1222 (2005).

45. Corradini, P., Auriemma, F. & De Rosa, C. Crystals and crystallinity in polymeric materials. *Acc. Chem. Res.* **39**, 314–323 (2006).

46. Shi, C. et al. High-performance pan-tactic polythioesters with intrinsic crystallinity and chemical recyclability. *Science Adv.* **6**, eabc0495 (2020).

47. Kafle, N. et al. Roles of conformational flexibility in the crystallization of stereoirregular polymers. *Macromolecules*, **54**, 5705–5718 (2021).

48. Abe, H. Thermal degradation of environmentally degradable poly(hydroxyalkanoic acid)s. *Macromol. Biosci*. **6**, 469–486 (2006).

49. Nishida, H., Shirai, Y. & Hassan, M. A. Highly selective transformation of poly[(*R*)-3-hydroxybutyric acid] into *trans*-crotonic acid by catalytic thermal degradation. *Polym. Degrad. Stab.* **95**, 1375–1381 (2010).

50. Bigley, D. B. 742. Studies in decarboxylation. Part I. The mechanism of decarboxylation of unsaturated acids. *J. Chem. Soc.* 3897–3899 (1964).

**Acknowledgments** We thank S. N. MacMillan (Cornell University) for help with X-ray crystallography. This work was supported by Department of Energy (No. DE-FOA-0002414) and

ExxonMobil. This work made use of the Cornell Center for Materials Research and the NMR Facility at Cornell University, which are supported by the NSF under awards DMR-1719875 and CHE-1531632, respectively. The funders had no role in study design, data collection and analysis, decision to publish or preparation of the manuscript.

**Author contributions** Z. Z. and A. M. L. designed and performed all experiments. G. W. C. directed the research. All authors prepared the manuscript.

**Competing interests** Z. Z., A. M. L. and G. W. C. are inventors on US provisional patent application 63/ 220,301, submitted by Cornell University, which covers synthesis and characterization of PHMB. T. D. S. declares no competing interests.

**Figure Legends**

**Fig. 1 | General design of methylated polyhydroxyalkanoates, PHMB. a,** Structural evolution from *i*PP, *R*-P3HB to PHMB. **b,** PHMB exhibits thermal and mechanicial properties that are comparable or superior to various commercial polymers, such as (bio)degradable (green) polyhydroxylbutyrate (PHB), polylactic acid (PLA), polycaprolactone (PCL), poly(butylene adipate terephthalate) (PBAT), and nondegradable (red) *i*PP and high-density polyethylene (HDPE). **c,** Streamlined synthesis of PHMB from 2-butene via epoxidation, carbonylation and polymerization.

**Fig. 2 | Polymerization of *cis*-DMPL by different initiators to give *cis*-PHMB homopolymers with varied degree of syndiotacticity. All the syndioenriched *cis*-PHMB homopolymers are high-melting but brittle. $T_m$ refers to the major melting peak observed in DSC.**

**Fig. 3 | Synthesis and characterization of PHMB copolymers with different *cis* content. a,** Polymerization of *cis*/*trans* mixture of DMPL with varied *cis* content. In all case, PHMB copolymers are obtained with high molecular weight ($M_n$ > 100 kDa) and low polydispersity ($Đ$ =

1.03 - 1.05). **b,** Thermal properties of different PHMB copolymers. All PHMB copolymers obtained have high melting points. **c,** Representative tensile curves of different PHMB copolymers with 90%, 80% and 70% *cis* blends. All PHMB copolymers are tough, and their tensile properties are comparable to some commercial polyolefin plastics. Their thermal and mechanical properties can be further tuned by the *cis* content of the starting materials. The inset photos are specimens before and after being stretched. $T_m$ refers to the major melting peak observed in DSC and $T_c$ refers to the crystallization peak.

**Fig. 4 | In addition to potential biodegradation, PHMB can be depolymerized to tiglic acid under catalytic MgO with near-quantitative yield. Tiglic acid is a value-added C5 feedstock and can also be pyrolyzed to generate *trans*-2-butene, which would permit the potential chemical recycling and upcycling of PHMB.**

## Methods

General carbonylation procedure:

In a glovebox, the selected carbonylation catalyst was dissolved in THF and cooled to -35 °C. In a separate container, the corresponding *cis*- or *trans*-2-butene oxide and THF were combined and cooled to -35 °C. The solutions of catalyst and epoxide were combined in a pre-chilled (-35 °C) autoclave which was then sealed and brought out of the glovebox. The reactor was pressurized with CO (700~900 psi) and heated (50~65 °C) for 16~20 h. The reactor was cooled and then vented carefully and opened. After removal of THF from the reaction mixture, the residual mixture was distilled under vacuum to give pure *trans*- or *cis*-DMPL, respectively.

General polymerization procedure:

In a glovebox, to a solution of DMPL (in pure form or as *cis*/*trans* mixtures) in $CH_2Cl_2$ was added a solution of selected initiator (complex A, B or C) at 25 °C. The resulting mixture was set at 25 °C for 2~24 h. The reaction mixture was then removed from glovebox, precipitated from mixtures of hexane and diethyl ether, and dried under vacuum to give the corresponding polymer.

Detailed synthetic methods, depolymerization procedures, and characterization data are available in the Supplementary Information.

**Data availability**

The data supporting the findings of this study are available within the paper and its Supplementary Information. Source Data for Fig. 3 is provided with the paper. Crystallographic data for the structure reported in this article have been deposited at the Cambridge Crystallographic Data Centre, under deposition number CCDC-2135622. Copies of the data can be obtained free of charge via https://www.ccdc.cam.ac.uk/structures/.