


Exceptional service in the national interest



Modeling for understanding and preventing cascading thermal runaway in battery packs

John Hewson, Randy Shurtz, Summer Ferreira, Josh Lamb, Chris Orendorff, Babu Chalamala
Sandia National Laboratories

FAA Triennial Fire and Cabins Safety Research Conference 2016
October 26, 2016




Sandia National Laboratories is a multi-program laboratory managed and operated by Sandia Corporation, a wholly owned subsidiary of Lockheed Martin Corporation, for the U.S. Department of Energy's National Nuclear Security Administration under contract DE-AC04-94AL85000.

SAND2016-xxxx C


The drive to greater energy density and efficiency

- Increased energy densities and other material advances lead to more reactive systems – greater efficiency / less losses.
 - Charged batteries include a ‘fuel’ and ‘oxidizer’ all internally.
 - Li-Ion electrolyte, packaging, and other materials are often flammable.
 - External heating or internal short circuits can lead to thermal runaway.



Validated reliability and safety is one of four critical challenges identified in 2013 Grid Energy Storage Strategic Plan

- Failure rates as low as 1 in several million,
- But number of cells used in energy storage is potentially huge (billions).
- Moderate likelihood of 'something' going wrong,
- Need to design against many possibilities.




www.nissan.com
www.internationalbattery.com
www.samsung.com
www.saft.com




Battery Abuse Testing Laboratory (BATLab)

- Comprehensive abuse testing platforms for safety and reliability of cells, batteries and systems from mWh to kWh
- Mechanical abuse
 - Penetration
 - Crush
 - Impact
 - Immersion
- Thermal abuse
 - Over temperature
 - Flammability measurements
 - Thermal propagation
 - Calorimetry
- Electrical abuse
 - Overvoltage/overcharge
 - Short circuit
 - Overdischarge/voltage reversal
- Characterization/Analytical Tools
 - X-ray computed tomography
 - Gas analysis
 - Surface characterization
 - Optical/electron microscopy




Thermal Test Complex



FLAME and RADIANT HEAT
Required size for validation
Radiant heat w/convective control



**Additional
40-sq.-ft. Radiant
Heat Test Cell**




Crosswind Test Facility (XTF)
Controlled Crosswind Configuration



Abuse Testing

12 Ah (~50 Wh) Cell Overcharge Abuse



(Internal temperature limited due to ejection of cell contents)

50 Wh cell in 8' containment
50 kWh battery failure -- 50 MWh battery failure?



Key Challenges:

- *Potential heat release can exceed stored energy.*
- *Potential cascading failure to other cells*



Approaches to designing in safety

The current approach is to test our way into safety¹


- Large system (>1MWh) testing is difficult and costly.

Consider supplementing testing with predictions of challenging scenarios and optimization of mitigation.

- Develop multi-physics models to predict failure mechanisms and identify mitigation.
- Build capabilities with small/medium scale measurements.
- Still requires some testing and validation.




Time: 46.683046



¹ 'Power Grid Energy Storage Testing Part 1.' Blume, P.; Lindenmuth, K.; Murray, J. EE – Evaluation Engineering. Nov. 2012.

How do we evaluate thermal runaway in realistic scenarios?

- Leverage the large DOE-NNSA Investments in Sierra-Mechanics Integrated Code simulation tools developed at Sandia National Laboratories under the Advanced Scientific Computing (ASC) program for Science-based Stockpile Stewardship by applying these tools to battery safety analysis



Heat transfer mechanisms in a fire


Physics:

- Turbulent fluid mechanics (buoyant plumes)
- Participating Media Radiation (PMR)
- Reacting flow (hydrocarbon, particles, solids)
- Conjugate Heat Transfer (CHT)
- The simulation tool *predicts* the thermal environment and object response

Core Capabilities

Sierra/Fuego


Low-Mach fire simulations with particle transport and thermal radiation



Sierra/Aria



Thermal transport simulations with various energetic material models

- Fully resolved chemistry
- Lower order level set burn propagation
- Gas production and pressure calculation



Development of heat release models from calorimetry measurements


- Calorimetry measurements inform and calibrate models for heat release rates.
- Here cathode heat release models are evaluated based on literature measurements.
- These heat release models are in our codes and used in subsequent predictions.



- Measurement from: MacNeil, D. D. and J. R. Dahn (2001). *Journal of Physical Chemistry A* **105**(18): 4430-4439.
- Models based on Spotnitz, R. and J. Franklin (2003). *Journal of Power Sources* **113**(1): 81-100.

Development of heat release models from calorimetry measurements

- Calorimetry measurements inform and calibrate models for heat release rates.
- Here cathode heat release models are evaluated based on literature measurements.
- These heat release models are in our codes and used in subsequent prediction




- SEI decomposition $2 \text{ROCO}_2\text{Li} \rightarrow \text{Li}_2\text{CO}_3 + \text{prod}$
- Cathode-electrolyte $\text{CoO}_2 + \text{C}_3\text{H}_4\text{O}_3 \rightarrow \frac{1}{3}\text{Co}_3\text{O}_4 + \text{prod}$
- Electrolyte-salt $\text{C}_3\text{H}_4\text{O}_3 + \text{LiPF}_6 \rightarrow \text{prod}$
- Anode-electrolyte $\text{C}_6\text{Li} + \text{C}_3\text{H}_4\text{O}_3 \rightarrow \text{Li}_2\text{CO}_3 + \text{prod}$

- Measurement from: MacNeil, D. D. and J. R. Dahn (2001). Journal of Physical Chemistry A **105**(18): 4430-4439.
- Models based on Spotnitz, R. and J. Franklin (2003). Journal of Power Sources **113**(1): 81-100.


Modeling thermal runaway in lithium ion cells

- Evolution simulated using calorimetry-derived heating rates and lumped thermal mass.
 - Consider SEI decomposition, cathode-electrolyte reaction, electrolyte
- If you have good low-temperature calorimetry for your ***specific chemistry*** and can adequately model the heat transfer, predictions of initial runaway are achievable.


Temp. evolution two environ.
temps., two cathode materials



Max temp. predicted versus
environment (oven) temp.




Thermal runaway occurs if heat release exceeds heat losses



- Predicted heating rates based on ARC measurements.
- Higher environment temperature leads to thermal runaway.
- Low temperature degradation occurs in both cases.

Thermal runaway occurs if heat release exceeds heat losses





But, if the temperature dependence is strong, sensitivity to scale and heat losses is small.

Focus mitigation on shallow-sloped regions!

- Criterion for self heating:

$$\Delta H [C]^n A e^{-E/RT} + \dot{q}_{internal} > h_{eff} \left(S/V \right) (T - T_{\infty})$$



Impact of SOC on Runaway – Josh Lamb Expts.



- Results show a nearly linear relationship between total heat release (kJ) and cell SOC – similar to data for cell size this suggests that failure enthalpy is based largely on the stored energy available
- Heat release rates (e.g. runaway reaction kinetics) follow an almost exponential relationship with cell SOC – again this is traditionally thought to cause a greater risk of thermal runaway
- Could a runaway still occur with large numbers of low SOC cells or cells in well insulated conditions?

Increasing stored energy (SOC) leads to exponentially faster heat release rates




- Fully charged cells observed to undergo more violent exothermic reactions.
- Charged fraction of cathode and anode are reactive component.
 - CoO_2 vs LiCoO_2 ; LiC_6 vs C_6
- Greater heat release associated with greater fractions of active material (greater SOC).



- Higher temperatures give exponentially greater heat release due to Arrhenius rate constants.

Failure of a single cell can propagate to rest of pack



Experimental propagation in 5 stacked pouch cells



Lamb, J., et al. (2015). Journal of Power Sources **283**: 517-523.


Cascading propagation across multiple (5) cells

- Prediction and mitigation of cell-to-cell propagation is key to addressing risk.
- Here simulating propagation across series of pouch cells.
- Accurate measurements of highest temperature kinetics unavailable and need to be calibrated to get agreement.





Sensitivity of propagation rate to high-T kinetics

- Multiply low and high temperature rates by 10x.
 - Accelerated low-T rates has negligible effect.
 - Accelerated high-T rates has first-order effect (anode Li-electrolyte reaction).



Pulsating Propagation at large scales




- Extend modeling to large scales at small cost relative to measurements.
- Here predictions include multi-step mechanism involving anode, cathode, electrolyte reactants.
- Pulsating front speed observed.



- Propagation across a large pack (128 cells here) exhibits pulsating instabilities.
- Note heating rate varies by 100x (log scale).

Pulsating Propagation at large scales


- Extend modeling to large scales at small cost relative to measurements.
- Here predictions include multi-step mechanism involving anode, cathode, electrolyte reactants.
- Pulsating front speed observed.



- Note heating rate varies by 100x (log scale).

The mechanism of pulsating propagation





- Heat released is conducted upstream of reaction front, increasing the total enthalpy (sum of sensible and chemical enthalpy) $H_{TOT} = c_p T + Y_r \Delta H_r$
- Front propagates rapidly through preheated region with larger H_{TOT} .



- Slow propagation (low Temp), but preheating mixture ahead of reaction front.

- Rapid propagation (high Temp), into preheated mixture.

Parameter studies of propagation at large scales are possible with models



- Prediction and mitigation of cell-to-cell propagation is key to addressing risk.
- Single-step heat-release predictions with a range of heat release and boundary temps.
- Propagation across a large pack (80 cells here) exhibits pulsating instabilities.

- Thermal runaway is a risk and potential barrier to development and acceptance.
- Heat release rates are moderate relative to potential dissipation.
- Heat release rates scale exponentially with SOC – net heat release.
- Identification of thermal ignition criterion and sensitivity to low temperature rates.
- Cell-to-cell propagation along homogenized pack structures exhibits pulsating behavior, depending on total enthalpy transport.
- Quality measurements are key to parameter identification.

Acknowledgements



- Supported by Imre Gyuk and the Department of Energy OE Electrical Energy Storage Program.

<http://www.sandia.gov/ess/>

- Collaborative discussions with Dave Ingersoll, Harry Moffat and Stefan Domino from Sandia and Forman Williams from UCSD have provided insight and guidance.