


The Response of Metals to Extreme Environments

K. Hattar

Sandia National Laboratories

April 2nd, 2019



Collaborators:


- D.L. Buller, D.C. Bufford, S.H. Pratt, T.J. Boyle, B.A. Hernandez-Sanchez, S.J. Blair, B. Muntifering, C. Chisholm, P. Hosemann, A. Minor, J. A. Hinks, F. Hibberd, A. Ilinov, D. C. Bufford, F. Djurabekova, G. Greaves, A. Kuronen, S. E. Donnelly, K. Nordlund, F. Abdeljawad, S.M. Foiles, J. Qu, C. Taylor, J. Sugar, P. Price, C.M. Barr, D. Adams, M. Abere, L. Treadwell, A. Cook, A. Monterrosa, IDES Inc, J. Sharon, B. L. Boyce, C. Chisholm, H. Bei, E.P. George, W. Mook, Hysitron Inc., G.S. Jawaharam, S. Dillon, R.S. Averback, N. Heckman, J. Carroll, S. Briggs, E. Carnes, J. Brinker, D. Sasaki, T. Nenoff, B.G. Clark, P.J. Cappillino, B.W. Jacobs, M.A. Hekmaty, D.B. Robinson, L.R. Parent, I. Arslan, & Protochips, Inc.

This work was partially funded by Sandia National Laboratories is a multimission laboratory managed and operated by National Technology & Engineering Solutions of Sandia, LLC, a wholly owned subsidiary of Energy Sciences, U.S. Department of Energy. This work was a subsidiary of Honeywell International Inc., for the U.S. Department of Energy's National Nuclear Security Administration under contract DE-NA0003525. Office of Science. Sandia National Laboratories is a multi-mission laboratory managed and operated by National Technology and Engineering Solutions of Sandia, LLC., a wholly owned subsidiary of Honeywell International, Inc., for the U.S. DOE's National Nuclear Security Administration under contract DE-NA-0003525. The views expressed in the article do not necessarily represent the views of the U.S. DOE or the United States Government.



Outline

1. Introduction to Sandia National Laboratories and its *In situ* Ion Radiation Transmission Electron Microscope (I³TEM)
2. Understanding radiation stability in nanoparticles
3. Effect of radiation environments on nanocrystalline metals
4. Lasers in a TEM (why not?)
5. State-of-art in quantitative *in situ* mechanical testing
6. Other environments (*in situ* SEM, liquid, and gas)



Potential Evolution of System Design


Use the Nearest Stone



to




- Radar charts and Ashby plots of current material
- Accelerated and field testing
- **Scientist create a new materials. Engineers find an application.**



Materials by Design

- Physics-based approach
- Requires multiscale modeling
- **Engineers require given properties, Scientists tailor the chemistry and microstructure to achieve it.**


Great vision! We are making strides, but we are not there yet





Sandia National Laboratories

“Exceptional service in the national interest”



May 13, 1949

Dear Mr. Wilson:


I am informed that the Atomic Energy Commission intends to ask that the Bell Telephone Laboratories accept under contract the direction of the Sandia Laboratory at Albuquerque, New Mexico.

This operation, which is a vital segment of the atomic weapons program, is of extreme importance and urgency in the national defense, and should have the best possible technical direction.


I hope that after you have heard more in detail from the Atomic Energy Commission, your organization will find it possible to undertake this task. In my opinion you have here an opportunity to render an exceptional service in the national interest.

I am writing a similar note direct to Dr. O. E. Buckley.

Very sincerely yours,



Mr. Leroy A. Wilson,
President,
American Telephone and Telegraph Company,
150 Broadway,
New York 7, N. Y.



 **SANDIA NATIONAL LABORATORIES**
President Harry S. Truman Fellowship in
National Security Science and Engineering

**“Sandia develops advanced
technologies to ensure global peace.”**
– S. Younger



Sandia National Laboratories




Sandia's USER Capabilities

Core Facility - SNL






- Nanophotonics & Optical Nanomaterials
- Soft- Biological & Composite Nanomaterials
- Quantum Materials
- In-situ Characterization and Nanomechanics

Gateway Facility - LANL



D. Hanson, W. Martin, M. Wasiolek




Sandia National Laboratories is a multi-mission laboratory managed and operated by National Technology and Engineering Solutions of Sandia, LLC., a wholly owned subsidiary of Honeywell International, Inc., for the U.S. Department of Energy's National Nuclear Security Administration under contract DE-NA0003525.



Sandia National Laboratories

In situ Characterization and Nanomechanics

Developing and implementing world-leading capabilities to study the dynamic response of materials and nanosystems to mechanical, electrical, or other stimuli.




- How do defects and crystal distortions alter the mechanical and other extrinsic properties in nanostructured materials?
- How can we understand and control energy transfer across interfaces and over multiple length and time scales?
- How does the environment change the mechanical response and surface structure of nanoscale materials?

Sandia's Ion Beam Laboratory




Ion Beam Laboratory Capabilities



Ion Beam Analysis (IBA)

Shooting a charged particle at an unknown material to determine its identity, local chemistry, and structure.



Ion Beam Modification (IBM)

Changing the optical, mechanical, and chemical properties of materials via ion implantation to meet technological needs

In Situ Ion Irradiation Microscopy (I³M)

Bombarding nano samples with various particles and observing the changes in real time to understand how materials will behave in extreme environments.

Radiation Effects Microscopy (REM)

Using ion emissions to determine the Radiation hardness of microelectronics, identifying potential weaknesses.

The IBL has a unique and comprehensive ion beam capability set including and *In situ* Ion Irradiation Transmission Electron Microscopy.

Benefits & Limitations of *in situ* TEM

Benefits

1. Real-time nanoscale resolution observations of microstructural dynamics

Limitations

1. Predominantly limited to microstructural characterization
 - Some work in thermal, optical, and mechanical properties
2. Limited to electron transparent films
 - Can often prefer surface mechanisms to bulk mechanisms
 - Local stresses state in the sample is difficult to predict
3. Electron beam effects
 - Radiolysis and Knock-on Damage
4. Vacuum conditions
 - 10^{-7} Torr limits gas and liquid experiments feasibility
5. Local probing
 - Portions of the world study is small




Fig. 6: Wing surface of the house fly.
(First internal photography, $U = 60$ kV, $M_s = 2200$)
(Driest, E., and Müller, H.O.: Z. Wiss. Mikroskopie 52, 53-57 (1935))






Fig. 2: Sketch by the author (9 March 1931) of the cathode ray tube for testing one-stage and two-stage electron-optical imaging by means of two magnetic electron lenses (electron microscope) [8].





Sandia's Concurrent *In situ* Ion Irradiation TEM Facility

Collaborator: D.L. Buller

10 kV Colutron - 200 kV TEM - 6 MV Tandem






IBIL from a quartz stage inside the TEM



Outline




1. Introduction to Sandia National Laboratories and its *In situ* Ion Radiation Transmission Electron Microscope (I³TEM)
2. Understanding radiation stability in nanoparticles
3. Effect of radiation environments on nanocrystalline metals
4. Lasers in a TEM (why not?)
5. State-of-art in quantitative *in situ* mechanical testing
6. Other environments (*in situ* SEM, liquid, and gas)






Single Ion Strikes: 46 keV Au¹⁺ ions into 5 nm Au nanoparticles

Collaborator: D.C. Bufford









Single Ion Strikes: 46 keV Au¹⁺ ions into 20 nm NPs

Collaborator: D.C. Bufford



Formation of Dislocation Loops & Sputtered Particles due to He implantation


Collaborators: D.C. Bufford, S.H. Pratt & T.J. Boyle



Sandia National Laboratories

Exploring Radiation effects in Au Nanorods

Collaborators: J. A. Hinks, F. Hibberd, A. Ilinov, D. C. Bufford, F. Djurabekova, G. Greaves, A. Kuronen, S. E. Donnelly & K. Nordlund






Crystal Orientation Matters!



Sandia National Laboratories

Outline


1. Introduction to Sandia National Laboratories and its *In situ* Ion Radiation Transmission Electron Microscope (I³TEM)
2. Understanding radiation stability in nanoparticles
3. Effect of radiation environments on nanocrystalline metals
4. Lasers in a TEM (why not?)
5. State-of-art in quantitative *in situ* mechanical testing
6. Other environments (*in situ* SEM, liquid, and gas)




Dose Rate Effects in Nanocrystalline Metals

Collaborators: C. Chisholm, P. Hosemann, & A. Minor

7.9×10^9 ions/cm²/s



6.7×10^7 ions/cm²/s



VS









Improved vibrational and ion beam stability permits us to work at 120kx or higher permitting imaging of single cascade events



Sandia National Laboratories

Quantifying Grain Boundary Radiation Stability of Nanocrystalline Au

Collaborators: D.C. Bufford, F. Abdeljawad, & S.M. Foiles



Any texture or grain boundary evolution can be directly observed and quantified




10 MeV Si



Sandia National Laboratories

Direct Comparison to Mesoscale Modeling

Collaborators: D.C. Bufford, F. Abdeljawad, & S.M. Foiles



Because of the matching length scale, the initial microstructure can serve as direct input to either MD or mesoscale models & subsequent structural evolution can be directly compared.




Sandia National Laboratories



1D Brownian Motion in Real Time



Collaborator: D.C. Bufford



- Dislocation loop moves between two pinning sites
 - ~30 nm apart







Triple beam condition:
2.8 MeV Au^{4+} + 10 keV He^+ / D_2^+



Simultaneous *In situ* TEM Triple Beam: 2.8 MeV Au⁴⁺ + 10 keV He⁺/D₂⁺

Collaborator: D.C. Bufford



In situ triple beam He, D₂, and Au beam irradiation has been demonstrated on Sandia's I³TEM! Intensive work is still needed to understand the defect structure evolution that has been observed.

Speed
x1.5


- **Approximate fluence:**
 - Au 1.2×10^{13} ions/cm²
 - He 1.3×10^{15} ions/cm²
 - D 2.2×10^{15} ions/cm²
- **Cavity nucleation and disappearance**




Sandia National Laboratories

Heterogeneous Bubble Formation under Some Radiation Sequences

Collaborator: B. Muntifering & J. Qu



$10^{17} \text{ He}^+/\text{cm}^2$
Visible damage to the sample








0.7 dpa Ni³⁺ irradiation
High concentration of cavities along grain boundaries



Sandia National Laboratories

Cavity Growth during *In situ* Annealing of 10 keV He⁺ Implanted and then 3 MeV Irradiated Ni³⁺

Collaborator: B. Muntifering & J. Qu



Bubble to cavity transition and cavity evolution can be directly studied









Precession Electron Diffraction Reveals Hidden Grain Structure

Collaborator: B. Muntifering & J. Qu

Cavities in helium implanted, self-ion irradiated, nc nickel film annealed to 400 °C



Cavities span multiple grains at identified grain boundaries




100 nm


Bubble Migration and Growth in a Single Grain Boundary

Collaborator: C. Taylor, B. Muntifering, J. Sugar & D. Adams


573 K




623 K



673 K




723 K



- 573K: Growth at GB from diffusion of interstitial He or small He-V clusters
- 623 K: Growth at GB from diffusion of interstitial He or small He-V clusters
- 673 K: Bubble migration to GB & cavity growth, intragranular growth from diffusion of interstitial He or small He-V clusters
- 723 K: Blister formation at boundaries, intragranular faceted cavity growth.

Cavities Role on Grain Boundary Motion


Collaborator: C. Taylor, B. Muntifering, J. Sugar & D. Adams




Cavities effect grain boundary mobility, triple junction angle



grain boundary motion alters cavity coalescence




Cavities in helium implanted, Pd foil during annealing at 700 °C



Sandia National Laboratories

Outline


1. Introduction to Sandia National Laboratories and its *In situ* Ion Radiation Transmission Electron Microscope (I³TEM)
2. Understanding radiation stability in nanoparticles
3. Effect of radiation environments on nanocrystalline metals
4. Lasers in a TEM (why not?)
5. State-of-art in quantitative *in situ* mechanical testing
6. Other environments (*in situ* SEM, liquid, and gas)




Initial Laser Heating Observations

Collaborator: P. Price, C.M. Barr, D. Adams, M. Abere






Pt Grain Growth



Reactive Multilayer Films



Nanoparticle Sintering



We can now introduce rapid thermal heating with
any TEM stage or ion beam conditions




Sandia National Laboratories




Complex Interaction Au NPs Exposed to Laser Irradiation

Contributors: P. Price, L. Treadwell, A. Cook



Speed = 2.5x



A Complex Combination of Sintering, Reactions, and Ablation Occurs

μ s Resolution with a Standard Camera

Collaborator: P. Price, A. Monterrosa, D. Adams, M. Abere, & IDES Inc.

fs


ps

ns

μ s

ms

s





- Electrostatic deflection of electrons
- 4, 9, or 16 images per frame, spread over a large camera
- Any exposure time up to the limits of the camera
 - Ultimate limit is beam current/brightness



1-to-1 Frame Capture (<5 ms per frame) Sintering of 20 nm Au Nanoparticles




Collaborator: P. Price, A. Monterrosa, & IDES Inc.



16 frames captured with <5 ms
exposure per frame

Temporal Compressive Sensing to Improve Temporal Resolution


Collaborator: P. Price, A. Monterosa, & IDES Inc.



A pseudorandom exposure pattern can produce more than 16 frames within the same exposure time

Current Status of DTEM Conversion




Collaborator: P. Price, A. Monterrosa, C.M. Barr, D. Adams, M. Abere, & IDES Inc.



- 266 nm UV laser induced photoemission has been achieved!
- 6 ns single-shot DTEM image of P47

Outline

1. Introduction to Sandia National Laboratories and its *In situ* Ion Radiation Transmission Electron Microscope (I³TEM)
2. Understanding radiation stability in nanoparticles
3. Effect of radiation environments on nanocrystalline metals
4. Lasers in a TEM (why not?)
5. State-of-art in quantitative *in situ* mechanical testing
6. Other environments (*in situ* SEM, liquid, and gas)




In situ Qualitative Mechanical Testing

Collaborators: C. Barr



Gatan straining TEM Holder

- Minimal control over displacement and no “out-of-box” force information
- Successful in studies in observing dislocation-GB interactions/mechanisms
- Ideally both grains have kinematic BF 2-beam conditions: challenging in ST holder


Traditional Gatan Heating and Straining Holder




Thin film tension “jig”: Jet thinned disk:



Dislocation interactions as a function of GB character ($\Sigma 3$ twin GB below):



Observe deformation mechanisms in nanocrystalline metals during tensile straining:



In situ Quantitative Mechanical Testing

Contributors: J. Sharon, B. L. Boyce, C. Chisholm, H. Bei, E.P. George, P. Hosemann, A.M. Minor, & Hysitron Inc.



Hysitron PI95 *In Situ* Nanoindentation TEM Holder


- Sub nanometer displacement resolution
- Quantitative force information with μN resolution
- **Concurrent real-time imaging by TEM**





Hysitron Corp.



Notched Bar



Nanopillars




Notched Micro Tension Bars






Cyclic Loading Coupled with ACOM

Collaborators: C. Barr & W. Mook



Mean load (P_{mean}) = 135 μN

Amplitude load (P_{amp}) = 35 μN




Orientation maps pre-, intermediate, and post- in-situ mechanical test can assist in deconvoluting possible mechanisms during cyclic loading


Crack Initiation at Notch

Collaborators: C. Barr & W. Mook


120,000 total cycles



123,600 cycles



164,000 cycles



- Crack initiation and initial propagation at notch tip
- Second crack initiates at $\sim 90^\circ$ to first crack, both 45° to notch tip normal
- Intra-granular crack (crack #2) propagates until reaching initial grain boundary and is subsequently arrested









Sandia National Laboratories



Crack Propagation, Closure, and Re-Direction

Collaborators: C. Barr & W. Mook




Sandia National Laboratories

Cyclic Loading: Complex Crack Propagation


Collaborators: C. Barr & W. Mook

8x playback speed
N = 40,000 in 200s

100 nm



- Mean load: 135 μ N; Amplitude load: 35 μ N
- 200 Hz, 200s test (15 fps 1k x 1k camera)



- $da/dN = 1.7 \times 10^{12} \text{ m/cycle}$
- Non-linear crack extension rate
- Crack propagation path changes “direction”




Sandia National Laboratories

Irradiation Creep (4 MeV Cu³⁺ 10⁻² DPA/s)


Contributors: G.S. Jawaharam, S. Dillon & R.S. Averback

Controlled Loading Rate Experiments




In-situ TEM
radiation
creep is
feasible!


50 nm Cu-W multilayer
20 Min



No Irradiation
(Loading rate 0.6 Mpa s⁻¹)




Irradiation Creep
(Loading rate 0.6 Mpa s⁻¹)



Outline

1. Introduction to Sandia National Laboratories and its *In situ* Ion Radiation Transmission Electron Microscope (I³TEM)
2. Understanding radiation stability in nanoparticles
3. Effect of radiation environments on nanocrystalline metals
4. Lasers in a TEM (why not?)
5. State-of-art in quantitative *in situ* mechanical testing
6. Other environments (*in situ* SEM, liquid, and gas)







Scaling Back Up: *In situ* Ion Irradiation SEM (I³SEM)

Collaborators: N. Heckman, D. Buller, B. Boyce, J. Carroll, C. Taylor, B. Muntifering, & S. Briggs



First Beam into SEM
on April 6th, 2018






Can We Gain Insight into the Corrosion Process through *In situ* TEM?

Contributors: D. Gross, J. Kacher, I.M. Robertson & Protochips, Inc.

Microfluidic Stage

- Mixing of two or more channels
- Continuous observation of the reaction channel




Pitting mechanisms during dilute flow of acetic acid over 99.95% nc-PLD Fe involves many grains.
Large grains resulting from annealing appear more corrosion tolerant

Other Fun Uses of Microfluidic Cell

Protocell Drug Delivery

S. Hoppe,
E. Carnes,
J. Brinker


Liposome
encapsulated
Silica destroyed
by the electron
beam



Liposomes in Water

S. Hoppe,
D. Sasaki


Liposomes
imaged in
flowing aqueous
channel



BSA Crystallization

S. Hoppe


Crystallization of excess
Bovine Serum Albumen
during flow



La Structure Formation

S. Hoppe,
T. Nenoff

La
Nanostructure
form from LaCl_3
 H_2O in wet cell
due to beam
effects




Unconventional *In situ* Microscopy Creates a wealth of Possibilities

- Sandia's I³TEM is one of only two facilities in the US

- Only facility in the world with a triple beam *in situ* ion irradiation capabilities
- *In situ* high energy ion irradiation from H to Au
- *In situ* gas implantation
- Dynamic TEM and time compression imaging
- 11+ TEM stages with various capabilities

Currently applying the I³TEM capabilities to various material systems in combined environmental conditions



Collaborators:

D.L. Buller, D.C. Bufford, S.H. Pratt, T.J. Boyle, B.A. Hernandez-Sanchez, S.J. Blair, B. Muntifering, C. Chisholm, P. Hosemann, A. Minor, J. A. Hinks, F. Hibberd, A. Ilinov, D. C. Bufford, F. Djurabekova, G. Greaves, A. Kuronen, S. E. Donnelly, K. Nordlund, F. Abdeljawad, S.M. Foiles, J. Qu, C. Taylor, J. Sugar, P. Price, C.M. Barr, D. Adams, M. Abere, L. Treadwell, A. Cook, A. Monterrosa, IDES Inc, J. Sharon, B. L. Boyce, C. Chisholm, H. Bei, E.P. George, W. Mook, Hysitron Inc., G.S. Jawaharram, S. Dillon, R.S. Averback, N. Heckman, J. Carroll, S. Briggs, E. Carnes, J. Brinker, D. Sasaki, T. Nenoff, B.G. Clark, P.J. Cappillino, B.W. Jacobs, M.A. Hekmaty, D.B. Robinson, L.R. Parent, I. Arslan. & Protochips



This work was partially funded by the Division of Materials Science and Engineering, Office of Basic Energy Sciences, U.S. Department of Energy. Materials Science and Engineering, Office of Basic Energy Sciences, U.S. Department of Energy. This work was performed, in part, at the Center for Integrated Nanotechnologies, an Office of Science User Facility operated for the U.S. Department of Energy (DOE) Office of Science. Sandia National Laboratories is a multi-mission laboratory managed and operated by National Technology and Engineering Solutions of Sandia, LLC., a wholly owned subsidiary of Honeywell International, Inc., for the U.S. DOE's National Nuclear Security Administration under contract DE-NA-0003525. The views expressed in the article do not necessarily represent the views of the U.S. DOE or the United States Government.



Sandia's USER Capabilities



D. Hanson, W. Martin, M. Wasiolek


www.cint.lanl.gov

- Spring and Fall proposals for 18 months
- Rapid Access proposal anytime for 3 months

Core Facility - SNL






Gateway Facility - LANL



www.nsuf.inl.gov

- Three proposal a year for 9 months



This work was partially funded by the Division of Materials Science and Engineering, Office of Basic Energy Sciences, U.S. Department of Energy. Materials Science and Engineering, Office of Basic Energy Sciences, U.S. Department of Energy. This work was performed, in part, at the Center for Integrated Nanotechnologies, an Office of Science User Facility operated for the U.S. Department of Energy (DOE) Office of Science. Sandia National Laboratories is a multi-mission laboratory managed and operated by National Technology and Engineering Solutions of Sandia, LLC., a wholly owned subsidiary of Honeywell International, Inc., for the U.S. DOE's National Nuclear Security Administration under contract DE-NA-0003525. The views expressed in the article do not necessarily represent the views of the U.S. DOE or the United States Government.




Sandia National Laboratories



Back-up



Sandia National Laboratories




PED in Liquid Cell Environment

Contributors: C. Taylor, S. Pratt, & T. Nenoff

$\text{LaCl}_3 \cdot 7\text{H}_2\text{O} : 10\text{ H}_2\text{O} : \text{PED}$


TEM Image




Virtual BF




Virtual BF



Index + Phase (green = hydride)



Phase Reliability + Phase






Radiation Tolerance is Needed in Advanced Scintillators for Non-proliferation Applications


Contributors: S.M. Hoppe, B.A. Hernandez-Sanchez, T. Boyle



In situ Ion Irradiation TEM (I³TEM)




High-Z nanoparticles (CdWO_4) are promising, but are radiation sensitive




+

Hummingbird tomography stage








Tomography of Irradiated CdWO_4 :
3 MeV Cu^{3+} at ~ 30 nA



Radiation Stable Nanoparticles!

Collaborators: T.J. Boyle, S.J. Blair, B. Muntifering



Ion	Energy (keV)	Dose (ions/cm ²)	Damage (dpa)
		Dose rate (ions/cm ² /s)	Damage rate (dpa/s)
Cu	3000	1.2×10^{14}	4.45
		1.3×10^{10}	4.9×10^{-4}
He	10	2.3×10^{18}	113
		1.4×10^{14}	7.0×10^{-3}
& Cu	3000	2.2×10^{14}	8.01
		1.3×10^{10}	4.9×10^{-4}

In contrast some NPs appear to be very radiation stable



Sandia National Laboratories