

# Dynamic Compression of Synthetic Diamond Windows

SAND2007-5966P



LABORATORY DIRECTED RESEARCH & DEVELOPMENT


Sandia National Laboratories

Primary Investigator: D.H. Dolan, Project Manager: T. Mehlhorn

## DYNAMIC COMPRESSION RESEARCH

- Rapid material loading
  - 10-1000 ns time scales
  - Nearly adiabatic
  - Extreme conditions
    - 1-1000 GPa (1 GPa=10,000 atm)
    - RT to many eV
- Reveals a wide range of material phenomena
  - Elastic-plastic deformation
  - Phase transformations
  - Chemical reactions

Duvall and Graham, Rev. Mod. Phys. 49, 523 (1977).




**Loading methods:**  
 Impact  
 Explosives  
 Electromagnetic (Z)  
 Laser

## PROBLEM: WINDOWS NEEDED TO MAINTAIN STRESS

- Windows must be:
  - transparent (primarily visible, emerging infrared and x-ray applications)
  - robust to chemical, thermal, and mechanical stresses
    - example: NaCl is not a particularly good choice
  - easily understood and modeled
  - No time dependent phenomena
- Other considerations:
  - Mechanical impedance
  - Thermal conductivity
  - Cost (relative to experiment)
    - Typically need to be <\$1000 per piece
- Strong need for high impedance windows in the 10-100+ GPa domain

## DIAMOND IS A GREAT WINDOW MATERIAL


- Many useful properties:
  - Transparent (visible, infrared, x-ray)
  - Large elastic range
    - 50-100 GPa, possibly higher
  - Very robust
  - High mechanical impedance
  - Large thermal conductivity
- Natural diamond is too expensive
  - Typical impact window (1" O.D. x 1/4" thick):
    - 3.2 cc weighs in at 57 carats (11.3 g)
    - Waves travel at roughly 18 km/s
    - 50 ns experiment requires 4 X 1 mm (0.2 carat) window
    - Mass scales as  $t^3$  (100 ns requires 1.6 carat)
- Diamond Prices are artificially high
  - <http://www.edwardjayepstein.com/diamond/prologue.htm>



The diamond anvil cell revolutionized static high pressure research. Schematic from A. Jayaraman, Rev. Mod. Phys. 55, 65, (1983).

## APPROACH: INVESTIGATE SYNTHETIC DIAMOND


- CVD diamond:
  - Single crystals
  - Colorless
  - Large windows possible
  - Can be more perfect than natural diamond
    - Harder
    - Higher thermal conductivity
- Limited number of sources
  - Carnegie DOE Alliance Center (CDAC)
  - Apollo Diamond





Left: 7x7x2 mm CDAC diamond  
(>\$4000 market, ~\$200 to produce)

Right: ~2 mm square, < 1 mm thick  
commercial diamond plate  
(~\$200 market)

## RESULTS: SHOCK COMPRESSION




- Symmetric impact experiments probe the elastic/transparent range
  - Elastic response observed to 48 GPa
  - Very large window correction (2.7-2.9)
  - Consistency study and HEL under investigation
- Technical challenges
  - Sample variability
  - Multiple optical reflections
  - Sub-nanosecond rise times



## WORK PLANNED (FY 2008)

- Shock/isentropic compression studies of diamond beyond 100 GPa (1 Mbar) using ZR



## SIGNIFICANCE: DYNAMIC COMPRESSION AND BEYOND

- Dynamic materials campaign applications
  - Immediate impact: high impedance window for shock and isentropic compression
    - High pressure liquid isentropes (deuterium, water)
    - Dynamic strength measurements
    - Diamond melt studies (NIF capsule material)
  - Future impacts
    - Dynamic pyrometry and x-ray diffraction measurements
    - Combined static-dynamic compression experiments
- Broader applications
  - Novel diagnostics (disposable neutron detectors)
  - Micro-electronic/mechanical systems
  - Other possibilities??

