

RECEIVED

OCT 04 1996

OSTI

**Chemical and Radiation Stability of a
Proprietary Cesium Ion Exchange
Material Manufactured from WWL
Membrane and SuperLig® 644**

G. N. Brown
K. J. Carson
J. R. DesChane

R. J. Elovich
P. K. Berry

September 1996

Prepared for the U.S. Department of Energy
under Contract DE-AC06-76RLO 1830

Pacific Northwest National Laboratory
Operated for the U.S. Department of Energy
by Battelle



MASTER

ds
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor Battelle Memorial Institute, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or Battelle Memorial Institute. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

PACIFIC NORTHWEST NATIONAL LABORATORY

operated by

BATTELLE

for the

UNITED STATES DEPARTMENT OF ENERGY

under Contract DE-AC06-76RLO 1830

Printed in the United States of America

Available to DOE and DOE contractors from the
Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831;
prices available from (615) 576-8401.

Available to the public from the National Technical Information Service,
U.S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA, 22161



This document was printed on recycled paper.

DISCLAIMER

**Portions of this document may be illegible
in electronic image products. Images are
produced from the best available original
document.**

**Chemical and Radiation Stability
of a Proprietary Cesium Ion Exchange
Material Manufactured from WWL
Membrane and SuperLig® 644**

G. N. Brown
K. J. Carson
J. R. DesChane
R. J. Elovich
P. K. Berry

September 1996

Prepared for
the U.S. Department of Energy
under Contract DE-AC06-76RLO 1830

Pacific Northwest National Laboratory
Richland, Washington 99352

Summary

Pretreatment of nuclear process wastes for the ion exchange removal of cesium and other radionuclides has been proposed as one method to minimize the amount of high-level radioactive waste (HLW) at Hanford. This study evaluated cesium-selective SuperLig® 644 (IBC Advanced Technologies, American Fork, UT) entrapped in a proprietary WWL web membrane (3M, St. Paul, MN) for chemical and radiation stability in simulated caustic neutralized current acid waste (NCAW), 0.5 M HNO₃, distilled water, and air. Following exposure from 0 to 2.0E+09 rad, the material was evaluated for cesium uptake in a series of 5 M sodium NCAW simulants with variable cesium concentrations. The following specific conclusions and recommendations resulted from the study:

- The radiolytic stability of the SuperLig® 644/WWL membrane appears to be sufficient for typical activities involving ion exchange pretreatment of radioactive cesium. Essentially no decrease in cesium selectivity or loading (K_d) was observed during cobalt-60 gamma irradiation of the material in either distilled water or 0.5 M HNO₃ up to 1.0E+09 rad. The cesium K_d decreased by a factor of two after exposure to 2.0E+09 rad in water or acid.
- Essentially no decrease in cesium K_d was observed during the irradiation of the SuperLig® 644/WWL membrane in 5 M NCAW or ambient air up to 1.0E+08 rad. However, under these same conditions, the observed Cs K_d values decreased more than an order of magnitude between 1.0E+08 and 2.0E+09 rad. These high irradiation dose results portray an extreme situation and should not be considered representative of typical process conditions.
- Chemical stability of the SuperLig® 644/WWL membrane under caustic conditions is significantly lower than in ambient air or under neutral or acidic conditions. Even at low irradiation doses (e.g., 0 to 1.0E+07 rad), cesium K_d s of approximately 80 milliliter per gram (mL g⁻¹) were observed for the NCAW irradiated membrane. At these lower irradiation doses, cesium K_d s of approximately 300 mL g⁻¹ were measured in other matrices. These results suggest that the material is less stable in caustic solution irrespective of the radiation exposure.

In terms of mechanical stability, samples of the membrane retained their physical form throughout the entire experiment and were only slightly brittle after exposure to 2.0E+09 rad. The reader is reminded that the material evaluated was a finely ground (400 mesh) particulate that was engineered to form a polymeric fiber (WWL), not the macroscopic form of the SuperLig® 644 ion exchange resin (20 to 50 mesh).

Pacific Northwest National Laboratory^(a) (PNNL) conducted this study for the Efficient Separations and Processing (ESP) Crosscutting Program, Office of Science and Technology, U.S. Department of Energy. The work was completed under the Technical Task Plan Number RL3-6-C3-42, Test Sorbents; Industrial Contracts.

(a) Pacific Northwest National Laboratory is operated for the U.S. Department of Energy by Battelle under Contract DE-AC06-76RLO 1830.

Acknowledgments

Pacific Northwest National Laboratory (PNNL) is collaborating with universities, national laboratories, and industry to develop and test new materials for the pretreatment of nuclear wastes stored at Hanford. The experimental work described in this report would not have been possible without the encouragement and resources provided by Kurt D. Gerdes, Efficient Separations and Processing (ESP) Crosscutting Program, Office of Science and Technology, U.S. Department of Energy. The authors would like to acknowledge the contributions to this effort of W. Bonner, W. Kuhn, G. Johnson, and M. Telander at PNNL (Richland, WA); D. Boggs, K. Carlson, T. Fredrickson, T. Kafka, D. Seely, I. Shaw-Epperson, N. Stern, L. White, and E. Wisted at 3M (St. Paul, MN); and R. Bruening, R. Decker, and S. Izatt at IBC Advanced Technologies (American Fork, UT). This work was performed by researchers at PNNL under the Technical Task Plan (TTP) RL3-6-C3-42.

Contents

Summary	iii
Acknowledgments	v
1.0 Introduction	1.1
1.1 Background	1.1
1.2 Historical Results	1.1
1.3 Objectives	1.2
1.4 Scope	1.2
2.0 Experimental	2.1
2.1 Ion Exchange Material Selection	2.1
2.2 Simulant Solution Selection	2.1
2.3 Cesium Batch Distribution	2.2
2.4 Sample Irradiation	2.3
3.0 Results and Discussion	3.1
3.1 Irradiation in Water	3.1
3.2 Irradiation in 0.5 M HNO ₃	3.3
3.3 Irradiation in Air	3.3
3.4 Irradiation in NCAW	3.3
3.5 Cesium Batch Distribution as a Function of Irradiation Dose	3.7
4.0 Conclusions and Recommendations	4.1
5.0 References	5.1

Figures

3.1 Cesium Batch Distribution Ratio as a Function of Na/Cs Ratio for Samples of the SuperLig® 644/WWL Web Irradiated in Distilled Water	3.2
3.2 Cesium Batch Distribution Ratio as a Function of Na/Cs Ratio for Samples of the SuperLig® 644/WWL Web Irradiated in 0.5 M HNO ₃	3.4
3.3 Cesium Batch Distribution Ratio as a Function of Na/Cs Ratio for Samples of the SuperLig® 644/WWL Web Irradiated in Air	3.5
3.4 Cesium Batch Distribution Ratio as a Function of Na/Cs Ratio for Samples of the SuperLig® 644/WWL Web Irradiated in NCAW	3.6
3.5 Cesium Batch Distribution Ratio as a Function of Irradiation Dose at a Na/Cs Ratio of 1.0E+05 for Samples of the SuperLig® 644/WWL Web Irradiated in Various Solutions ...	3.8

Table

2.1 NCAW Simulant Composition	2.2
-------------------------------------	-----

1.0 Introduction

1.1 Background

The contents of Hanford's 177 underground storage tanks (UST) include a mixture of sludge, salt cake, and alkaline supernatant liquid. The insoluble sludge fraction of the waste consists of metal oxides and hydroxides and contains the bulk of the ^{90}Sr waste component and many transuranic (TRU) radionuclides. The salt cake, which resulted from extensive evaporation of aqueous solution, consists primarily of dried sodium salts. The supernate consists of concentrated aqueous solutions of sodium nitrate/nitrite salts with smaller quantities of hydroxide, aluminum, potassium, carbonate, sulfate, and phosphate. The bulk of the water-soluble radionuclides such as ^{137}Cs are likely contained in the supernatant solution, interstitial liquid, and salt cake fractions.

Although the pretreatment and disposal strategy for the USTs is still being defined, one of the first steps in most pretreatment scenarios will be a solids/liquid separation of the pumpable waste liquor, followed by ion exchange removal of cesium from the resulting supernatant liquid. Next, a salt cake dissolution and sludge wash step will be initiated, followed by another solids/liquid separation. Most of the cesium is expected to be in the aqueous liquids from these processes and it is these solutions that are the focus of the cesium ion exchange removal process. This process is being designed with the goal of removing enough cesium so the resulting low-level waste (LLW) will meet the U.S. Nuclear Regulatory Commission's (NRC) 10 CFR 61 Class A Limit for ^{137}Cs (1 Ci m^{-3}). However, a greater cesium decontamination and the removal of ^{90}Sr , ^{99}Tc , and TRUs from the alkaline supernate may be required to meet the NRC incidental waste designation or another designation.

1.2 Historical Results

The technology for cesium decontamination of high-level alkaline wastes and sludge wash waters has been investigated at the Pacific Northwest National Laboratory^(a) (PNNL) in Richland, Washington (Bray 1989; Bray et al. 1990; Bray et al. 1992; Bray et al. 1993a; Bray et al. 1993b; Brown et al. 1995c; Kurath et al. 1994); the Westinghouse Savannah River Company (WSRC), Aiken, South Carolina (Bibler et al. 1989; Bibler 1991 and 1994; Bray et al. 1990); and the West Valley Nuclear Services Company, Inc. (WVNS) in West Valley, New York (Bray et al. 1984; Kurath et al. 1989; Bray and Hara 1991).

Many ion exchange materials have demonstrated the ability to remove cesium from various simulated solutions (Marsh et al. 1994a; Marsh et al. 1994b; Marsh et al. 1994c; Marsh et al. 1995). Brown et al. (1995b) investigated the column ion exchange removal of radioactive cesium from actual and simulated 101-SY and 103-SY tank waste using CS-100. In addition, several inorganic and organic

(a) Pacific Northwest National Laboratory is operated for the U.S. Department of Energy by Battelle under Contract DE-AC06-76RLO 1830.

materials have been evaluated for cesium and strontium selectivity using small-scale batch distribution experiments with actual and simulated 101-AW tank waste (Brown et al. 1996).

The chemical and radiolytic stability of several organic ion exchange resins (e.g., SuperLig® 644, resorcinol-formaldehyde [R-F], and CS-100) has been evaluated in simulated alkaline waste solutions using ^{60}Co gamma radiation (Bibler and Crawford 1994; Brown et al. 1995a; Bryan et al. 1993; Carlson et al. 1995; Hubler et al. 1995).

1.3 Objectives

Experimental studies are being conducted by PNNL under the Efficient Separations and Processing (ESP) Crosscutting Program to 1) develop and evaluate newly conceived novel materials for the recovery of cesium, strontium, and technetium from alkaline wastes; 2) determine the loading and elution efficiency of these processes; 3) determine the physical life cycle (including radiation and chemical stability) of these materials; and 4) determine if basic ion exchange data can be applied to a broad range of tank wastes. The goal is to provide the technology to produce a LLW effluent with radioactivity levels that are low enough to permit further treatment in the LLW glass vitrification facility. Ultimately, each process must be evaluated in terms of removal efficiency, process chemical consumption and recycle, chemical and radiation stability of materials, compatibility with other process streams, secondary waste generation, process and maintenance costs, final material disposal, and impact upon the volume and quality of the high-level waste (HLW).

The purpose of this report is to describe the chemical and radiolytic stability of the newly synthesized SuperLig® 644 sequestering agent (IBC Advanced Technologies, American Fork, UT), which has been engineered to form a proprietary web-like matrix called SL644/WWL (3M, St. Paul, MN). Material stability was evaluated under realistic process flow sheet solutions including a simulated Hanford alkaline waste supernate, dilute nitric acid, distilled water, and ambient air.

1.4 Scope

The work described in this report involves the evaluation of a cesium selective material (SuperLig® 644/WWL) based on the results obtained from chemical and radiolytic stability experiments conducted within the material. The material was irradiated to a total dose of $2.0\text{E}+09$ rad at $1.6\text{E}+06$ rad hr^{-1} in either a simulated neutralized current acid waste (NCAW) supernatant liquid, 0.5 M HNO_3 , distilled water, or ambient air. The samples were analyzed for ion exchange selectivity and capacity by cesium batch distribution (K_d) experiments in a simulated NCAW solution containing variable concentrations of cesium and 5.0 M sodium. Prior to the ion exchange K_d contact, the initial sodium-to-cesium molar ratio (Na/Cs) ranged from 500 to 500,000. These K_d data were used to determine the relative stability of the material tested.

2.0 Experimental

Previous experimental work completed prior to Fiscal Year 1996 for cesium recovery included the evaluation of several ion exchange materials (e.g., SuperLig® 644, R-F, and CS-100) in simulated and actual waste matrices using bench-scale column loading and elution tests, small-scale batch distribution contacts, and chemical and radiolytic stability experiments. Brown et al. (1995a) exposed three organic ion exchange resins (SuperLig® 644, R-F, and CS-100) to either ^{60}Co gamma radiation or oxygen in simulated alkaline waste solutions to evaluate each material's relative radiolytic and oxidative stability. Radiolytic stability was deduced by periodic gas generation and cesium batch K_d analysis of each material. Stability toward oxidation was inferred by O_2 uptake measurements, nuclear magnetic resonance (NMR), and cesium batch K_d analysis of the exposed materials.

The focus of the work reported here is to further investigate the chemical and radiolytic stability of engineered SuperLig® 644 entrapped in a web-like polymer matrix and to compare the subsequent results to those obtained previously (Brown et al. 1995a) for the ion exchange resin in the absence of the WWL web matrix. The data described in this report can be found in the PNNL laboratory record book (LRB) BNW55765. Because of the limited availability of actual radioactive waste, simulated solutions have been used for the current stability testing.

2.1 Ion Exchange Material Selection

The removal of radioactive cesium by column ion exchange is considered to be the baseline pretreatment process for cleanup of a majority of the waste currently stored at Hanford. In addition to SuperLig® 644, several materials are capable of removing cesium from highly alkaline solutions, including organic ion exchange resins (CS-100 and R-F), inorganic zeolites (IE-95, IE-96, TIE-96), and other materials (Crystalline Silico-Titanates [CSTs]). The SuperLig® 644 polymer resin is the latest version of the covalently bound SuperLig® macrocycle family of sequestering ligands from IBC Advanced Technologies (American Fork, UT), and has been shown to be highly selective for cesium even in the presence of excess sodium or potassium (Brown et al. 1995c). The SuperLig® 644 polymer has recently become available engineered in a web-like matrix produced by 3M (St. Paul, MN). In the current study, this SuperLig® 644/WWL web material was evaluated for chemical and radiation stability under a variety of solution conditions.

2.2 Simulant Solution Selection

The NCAW simulant described in Table 2.1 was chosen for the current ion exchanger irradiation/stability experiments. This composition is considered to be representative of much of the Hanford tank wastes. It has been previously shown that this composition replicates the chemical environment of actual NCAW tank wastes for radiation and chemical stability experiments (Brown et al. 1995a; Bryan et al. 1993; Carlson et al. 1995). Numerous cesium batch K_d and column loading tests have been completed

Table 2.1. NCAW Simulant Composition

Species	Molarity, M
Na	5.00
K	0.12
Rb	5.00E-05
Cs	Variable
Al	0.43
SO ₄	0.15
OH (Total)	3.40
OH (Free)	1.68
CO ₃	0.23
NO ₂	0.43
NO ₃	1.67
F	0.089
PO ₄	0.025

using this formulation (Bray et al. 1992; Kurath et al. 1994; Brown et al. 1995c). Cesium was absent from the NCAW simulant during material irradiation, but was present during the batch K_d determinations at an initial concentration, which varied from 1.0E-02 to 1.0E-05 M as cesium nitrate.

2.3 Cesium Batch Distribution

The batch K_d ($K_d = [Cs]_{\text{solid}} \div [Cs]_{\text{liquid}}$) is an equilibrium measure of the overall ability of the solid phase ion exchange material to remove an ion from solution under the particular experimental conditions that exist during the contact. In most batch K_d tests, a known quantity of ion exchange material is placed in contact with a known volume of solution containing the particular ions of interest. The material is allowed to contact the solution for a sufficient time to achieve equilibrium at a constant temperature, after which the solid ion exchange material and liquid supernate are separated and analyzed. In this report, the batch K_d s were achieved by contacting 0.07 g of the web material with 10 mL of supernate liquid. The equation for determining the K_d can be simplified by determining the concentration of the analyte before and after contact and calculating the quantity of analyte on the ion exchanger by difference (Equation 1).

$$K_d = \frac{(C_i - C_f)}{C_f} * \frac{V}{M * F} \quad (1)$$

C_i is the initial amount or activity of the ion of interest in the feed solution prior to contact, C_f is the amount or activity after contact, V is the solution volume, M is the exchanger mass, and F is the mass of dry ion exchanger divided by the mass of wet ion exchanger (F-factor). K_d (normal units are mL g^{-1}) represents the theoretical volume of solution (mL) that can be processed per mass of exchanger (dry weight basis) under equilibrium conditions. λ , the theoretical number of bed volumes of solution that can be processed per volume of exchanger, is obtained by multiplying K_d by the exchanger bed density, ρ_b (g of resin per mL of resin) as shown in Equation 2.

$$\lambda = K_d * \rho_b \quad (2)$$

The λ value provides a method for comparing the ion exchange performance of a wide variety of materials on a volume basis (e.g., in an ion exchange column). Brown et al. (1995c) reported that this method is biased against low bed density materials (e. g., SuperLig® 644 $\rho_b = 0.22 \text{ g mL}^{-1}$; R-F $\rho_b = 0.45 \text{ g mL}^{-1}$).

The experimental equipment required to complete the batch K_d determinations included an analytical balance, a constant temperature water bath, an oven for F-factor determinations, a variable speed shaker table, 20-mL scintillation vials, 0.2- μm syringe filters, the appropriate ion exchanger, and simulant solutions. Prior to initiating the batch contact, each material was irradiated to the specified dose in the specified solution (e.g., cesium-deficient NCAW simulant, 0.5 M HNO_3 , distilled water, or air), rinsed with copious amounts of distilled water, and then air dried for a minimum of 48 hours. Approximately 0.07 g of each material was contacted with 10 mL of the stock NCAW solutions (e.g., 5 M Na with variable cesium concentrations). The sample bottles were placed into a 25°C constant temperature bath and shaken lightly for 72 hours. The samples were then filtered with a 0.2- μm pore filter to separate the resin material from the solution and the resulting liquid was analyzed for cesium content by ^{137}Cs gamma counting.

2.4 Sample Irradiation

To evaluate the chemical and radiation stability of the SuperLig® 644/WWL sorbent, samples were contained in glass scintillation vials and exposed to high dose ^{60}Co gamma radiation. The sealed system provided a convenient system for exposing the resin to either an NCAW simulant, 0.5 M HNO_3 , distilled water, or ambient air during the radiolysis process. A single piece of the sorbent web weighing approximately 0.6 g was triple rinsed and placed into 15 mL of the appropriate irradiation solution. No attempt was made to evacuate or purge the entrained oxygen or air from the sample containers. Following irradiation, the samples were rinsed with copious amounts of distilled water and air dried for a minimum of 48 hours.

Small subsample (0.07-g) portions of the sorbent were evaluated at each irradiation dose for cesium uptake using the ^{137}Cs batch distribution coefficient K_d (see Section 2.3). The remainder of the irradiated sample for each solution was dried at 105°C for 24 hours and the fraction (F-factor) of easily removed water was calculated. The samples were contacted with fresh NCAW simulant containing a variable

initial cesium concentration (Na/Cs from 500 to 500,000). The obtained distribution coefficients are used as an indicator of the material cesium loading and an approximation of the radiation damage to the resin material. The materials were exposed to a total radiation dose of approximately $2.0\text{E}+09$ rad at $1.6\text{E}+06$ rad hr^{-1} over the course of several weeks.

The Gamma Irradiation Facility is operated by PNNL and contains 37 stainless steel irradiation tubes positioned in a 7-ft-dia. by 13-ft-, 8-in.-deep stainless steel tank. Two arrays of ^{60}Co with a combined inventory of 32 KCi are located near the bottom of the tank. For radiation shielding purposes, the tank is completely filled with water and a 3.5-ft-tall concrete wall surrounds the top of the tank. The irradiation tubes, which are sealed on the bottom, vary in length and diameter from 16 ft to 18 ft and 1.8 in. to 6 in., respectively. The irradiation flux of the tubes ranges from approximately $2.0\text{E}+06$ rad hr^{-1} to $2.0\text{E}+02$ rad hr^{-1} . The uniform flux region varies from ~6 in. for the tubes closest to the sources to greater than 12 in. for the tubes farthest away from the sources. All flux measurements of the tubes are traceable to the National Institute of Standards and Technology.

All materials and test systems were manually lowered into the irradiation tubes and were left in the tubes for the specific amount of time ($6.25\text{E}-01$, $6.25\text{E}+00$, $6.25\text{E}+01$, $6.25\text{E}+02$, $1.25\text{E}+03$ hour) to achieve the required exposure ($1.0\text{E}+06$, $1.0\text{E}+07$, $1.0\text{E}+08$, $1.0\text{E}+09$, $2.0\text{E}+09$ rad). There is no activation associated with the gamma irradiation, so the materials were transported to other facilities for Cs batch K_d evaluation (Section 2.3) after they were removed from the tubes. The temperature of the test was approximately 15°C to 20°C based on the recorded ambient temperatures in the gamma facility.

3.0 Results and Discussion

IBC Advanced Technologies has developed a new class of sequestering agents (SuperLig®) that can selectively remove various radionuclides (cesium, strontium, etc.) from high ionic-strength alkaline solutions based on molecular recognition technology. Previous tests have demonstrated that one of these materials in resin form (SuperLig® 644) can remove cesium from simulated Hanford tank waste even in the presence of excess sodium and potassium (Brown et al. 1995c). To more accurately assess the potential use of this technology for pretreating nuclear process wastes, the oxidative and radiolytic stability of SuperLig® 644 was tested and compared to that of two current baseline materials (Brown et al. 1995a).

More recently, IBC Advanced Technologies and 3M (St. Paul, MN) have collaborated to develop a novel form of the SuperLig® 644 material. In this case, the organic resin is ground to a fine uniform particle size and entrapped in a web-like fibrous matrix designated WWL. Due to the unique nature of this novel material, the chemical and radiolytic stability has been questioned. The increased surface area-to-mass ratio of the smaller particles raises the potential for reduced stability; conversely, there is also a possibility for an increase in stability because of the greater stability of the inert fibrous matrix. For these reasons, the SuperLig® 644/WWL material was exposed to ^{60}Co gamma radiation in a variety of solutions over several weeks. The irradiated samples were analyzed for cesium selectivity in a simulated NCAW solution by batch distribution (K_d) analysis.

3.1 Irradiation in Water

Cesium batch distribution (K_d) results as a function of equilibrium Na/Cs ratio are displayed in Figure 3.1 for samples of the SuperLig® 644/WWL membrane irradiated in distilled water. Each data curve represents a known irradiation dose from 0 to $2.0\text{E}+09$ rad. It is evident from the data that irradiation in water to $1.0\text{E}+09$ rad does not appreciably change the cesium K_d results. Even after irradiation to $2.0\text{E}+09$ rad, the cesium K_d decreased by less than a factor of two.

The K_d data are presented as a function of the equilibrium Na/Cs ratio (i.e., the Na/Cs ratio remaining after material and solution contact) so the reader can easily extrapolate back to the original composition of the NCAW feed solution. Data displayed in this manner allow evaluation of material loading and extrapolation to column ion exchange performance. The samples were evaluated for cesium uptake in a series of standard NCAW simulants with variable cesium content (500 to 500,000 Na/Cs) as described by previous researchers (Bibler et al. 1989; Bray et al. 1990; Bray et al. 1992; Brown et al. 1996; Kurath et al. 1994).

At a final Na/Cs ratio of $5.0\text{E}+04$ (e.g., the composition of the standard NCAW solution used previously by Brown et al. [1995c]), the cesium K_d was determined to be approximately 220 mL g^{-1} for the nonirradiated samples. The value decreased slightly to 170 mL g^{-1} after irradiation to $2.0\text{E}+09$ rad. Multiplying this value by the estimated SuperLig® 644/WWL bed density




Figure 3.1. Cesium Batch Distribution Ratio as a Function of Na/Cs Ratio for Samples of the SuperLig® 644/WWL Web Irradiated in Distilled Water

($\rho_b = 0.347 \text{ g mL}^{-1}$) yields a lambda (λ) value of nearly 80 column volumes (CV). When the fractional amount of SuperLig® 644 loaded into the WWL membrane is taken into account, this value compares favorably to the 110 CV value reported earlier for nonirradiated SuperLig® 644 resin (Brown et al. 1995c). The percentage of active particle in the WWL membrane is known to vary between 60% and 95%, depending upon production conditions.

3.2 Irradiation in 0.5 M HNO₃

The cesium K_d results for the irradiation of the SuperLig® 644/WWL membrane in dilute nitric acid (0.5 M HNO₃) are displayed in Figure 3.2. The results are analogous and are nearly identical to those displayed in Figure 3.1 for irradiation in distilled water. The similarities are not surprising since the SuperLig® 644/WWL material is obtained from the supplier in the acid form. The manufacturer suggests that if the material is to be stored for an extended time, the acid form is preferred. The equilibrium pH was not measured during the experiment, but it is likely that the distilled water became slightly acidic after contact. At 2.0E+09 rad, the samples irradiated in either water or acid exhibited a moderate weight loss (6%) that was only slightly greater than the 2% weight loss observed for the lower irradiation doses.

3.3 Irradiation in Air

The cesium K_d results for the irradiation of the SuperLig® 644/WWL membrane in ambient air are displayed in Figure 3.3. The results are analogous but more extreme than those described above for the irradiation in dilute nitric acid or distilled water. After irradiation, the cesium K_d results at a Na/Cs ratio of 1.0E+05 drop significantly from approximately 300 mL g⁻¹ at 1.0E+07 rad to less than 30 mL g⁻¹ at 2.0E+09 rad. Evidently, exposure of the material to either dilute acid or distilled water solution during the irradiation process may protect the resin from chemical degradation. Several protection mechanisms can be postulated, including free radical transfer from the resin to a water molecule or a reduction in oxygen availability in solution versus in air. The air-irradiated sample actually displayed a minor weight gain (0.8% and 2.1%) at 1.0E+09 and 2.0E+09 rad, respectively.

3.4 Irradiation in NCAW

The cesium K_d results for irradiation of the SuperLig® 644/WWL membrane in simulated NCAW solutions are displayed in Figure 3.4. The results are analogous and surprisingly similar to those described for irradiation in ambient air. However, after irradiation, the cesium K_d results drop significantly from approximately 70 mL g⁻¹ at 1.0E+07 rad to less than 1 mL g⁻¹ at 2.0E+09 rad. Also evident is the significant reduction in cesium K_d for the nonirradiated material stored in NCAW when compared to storage and irradiation in either distilled water, dilute nitric acid, or ambient air. Evidently, the material is less stable toward radiation in the NCAW than in air or other solutions.




Figure 3.2. Cesium Batch Distribution Ratio as a Function of Na/Cs Ratio for Samples of the SuperLig® 644/WWL Web Irradiated in 0.5 M HNO_3




Figure 3.3. Cesium Batch Distribution Ratio as a Function of Na/Cs Ratio for Samples of the SuperLig® 644/WWL Web Irradiated in Air




Figure 3.4. Cesium Batch Distribution Ratio as a Function of Na/Cs Ratio for Samples of the SuperLig® 644/WWL Web Irradiated in NCAW

A comparison of these results to those described previously (Brown et al. 1995a) for a pure SuperLig® 644 resin irradiated at $1.0\text{E}+09$ rad is also displayed in Figure 3.4. The previous K_d results are significantly higher than the current results. For example, in the current experiment, a cesium K_d value of 14 mL g^{-1} (measured in NCAW at $1.0\text{E}+05$ Na/Cs) was determined for the SuperLig® 644/WWL membrane irradiated in an NCAW solution to $1.0\text{E}+09$ rad. Using the same irradiation solution, the SuperLig® 644 polymeric resin yielded a K_d value of 110 mL g^{-1} (Brown et al. 1995a).

Several important differences between the two experiments could account for the lower cesium K_d results. First, in the current tests, no attempt was made to exclude oxygen or entrained air from the samples. In the previous gas generation experiments (Brown et al. 1995a), the samples were explicitly purged with ultra high purity argon so the generation of various gases could be accurately determined. Secondly, the SuperLig® 644 material is known to swell in caustic solutions, an effect that may enhance diffusion-limited degradation mechanisms as compared to the unswelled sorbent (e.g., irradiated in air, water, or acid). Thirdly, the SuperLig® 644/WWL membrane contained smaller active particles (>400 mesh) than the polymeric resin (20 to 50 mesh), which might also explain the differences. Also, the current membrane samples were irradiated at a higher volume-to-mass phase ratio ($V/M = 30$) than the resin samples ($V/M = 6$) reported by Brown et al. (1995a). Finally, a significant post-irradiation weight increase (50%) from approximately 0.5 g to 0.75 g was observed for these samples and was only partially compensated by the F-factor (0.88) correction. Evidently, the sorbent picked up one or more of the components from the NCAW that could not be easily rinsed out of the web. In this case, the actual sorbent mass would be lower than expected and a reduced cesium K_d would be calculated.

Previous column loading experiments in NCAW at $5.0\text{E}+04$ Na/Cs (Brown et al. 1995c) have indicated a loading of between 80 and 90 CV for the nonirradiated SuperLig® 644 resin. In the current experiment (Figure 3.4), it was estimated that only 21 CV could be processed ($\lambda = \rho_b \times K_d = 0.347 \times 60$) for the SuperLig® 644 membrane. From Section 3.3, samples that were not exposed to NCAW demonstrated a greater performance ($\lambda = \rho_b \times K_d = 0.347 \times 300 = 104$). It is likely that this difference is due to the additional 8-week exposure to the NCAW solution prior to the batch K_d experiment.

3.5 Cesium Batch Distribution as a Function of Irradiation Dose

Cesium batch K_d results for samples of the SuperLig® 644/WWL membrane are displayed in Figure 3.5 as a function of irradiation dose. The data are displayed at a constant equilibrium Na/Cs ratio of $1.0\text{E}+05$ ($5.0\text{E}-05\text{ M}$ cesium). The chosen Na/Cs ratio was entirely arbitrary but represents an approximate estimate of the cesium concentration expected in many of the Hanford waste tanks. The samples were irradiated with an external ^{60}Co source at $1.6\text{E}+06\text{ rad hr}^{-1}$ in a variety of aqueous solutions. The maximum dose was $2.0\text{E}+09$ rad and required nearly eight weeks of exposure.

From the data it is evident that the K_d values are nearly constant for all solution conditions at exposures below $1.0\text{E}+08$ rad. A slight reduction in K_d is noted for the samples irradiated up to $2.0\text{E}+09$ rad in distilled water and dilute nitric acid. However, this degradation appears to be minor when compared to the results for the material irradiated in air or NCAW. In these cases, a significant




Figure 3.5. Cesium Batch Distribution Ratio as a Function of Irradiation Dose at a Na/Cs Ratio of 1.0E+05 for Samples of the SuperLig® 644/WWL Web Irradiated in Various Solutions

reduction in the measured K_d value occurred at exposures greater than $1.0\text{E}+08$ rad. For the air-irradiated sample, K_d decreased more than an order of magnitude from approximately 300 to less than 30 mL g^{-1} . For the NCAW-irradiated sample, a reduction from 80 mL g^{-1} to less than 1 mL g^{-1} was observed. Degradation at these extreme conditions is not unexpected and has been observed previously for the SuperLig® 644 and other organic resins (Brown et al. 1995a).

However, the reduction is minor considering that most organic materials display extreme degradation at these high exposures. The SuperLig® 644/WWL web retained its physical form over the entire exposure range and was only slightly brittle at the highest doses (over $1.0\text{E}+09$ rad). These doses are based on irradiation with an external ^{60}Co source and may or may not accurately predict resin exposure during actual waste processing. However, Penwell et al. (1994) estimated that a maximum radiation field of $2.7\text{E}+05\text{ rad hr}^{-1}$ would exist at the surface of an NCAW-loaded R-F ion exchange column. The NCAW solution is expected to contain the highest cesium concentration and therefore exhibit the highest radiation field. Assuming a loading cycle of 50 hours (e.g., full loading at 300 CV and a process flowrate of 6 CV hr^{-1}) and a total of 10 loading cycles before resin disposal, a conservative maximum for material exposure would be $1.4\text{E}+08$ rad. The time-averaged radiation dose would be approximately one-half this value since the resin is only fully loaded at the end of the cycle. Therefore, it is estimated that 1 to 2 months of continuous operation would be required to reach the $1.0\text{E}+08$ rad dose.

One interesting observation is that the NCAW-irradiated material consistently yields lower K_d values than materials irradiated in other solutions. Even the nonirradiated sample that was exposed to the NCAW simulant exhibited a much lower value (80 mL g^{-1}) compared to the other solutions (300 mL g^{-1}). This effect is attributed to the reduced chemical stability of the SuperLig® 644 material in caustic solutions (Brown et al. 1995a). During the radiation testing, all samples were exposed to the respective solutions for the entire 8 weeks of the experiment. The samples were prepared prior to the start of the irradiation process and were irradiated in reverse order so that all the materials would be removed simultaneously at the end of the test. Therefore, the SuperLig® 644/WWL webs were exposed to the NCAW, distilled water, dilute nitric acid, and air for the entire 8-week irradiation period, irrespective of the dose received. This method allows the separation of chemical degradation (solution exposure) from radiolytic degradation as well as nonsolution degradation (air exposure).

If the NCAW-irradiated samples had been freshly prepared such that the resin was only exposed to the NCAW solution during irradiation, one might observe degradation of the resin based on chemical and radiation damage and would not be able to separate the two effects. With these conditions, the chemical degradation of the SuperLig® 644/WWL is clearly differentiated from the radiolytic stability. If the nonirradiated samples had been placed into the NCAW solution just prior to determining the cesium K_d , one would expect the K_d data to be much closer to that measured for irradiation in ambient air (e.g., constant 250 to 300 mL g^{-1} between 0 and $1.0\text{E}+08$ rad). No evaluation of resin storage methods (e.g., storage under nitrogen or other inert cover gas) was attempted.

Unfortunately, the data suggest that prolonged storage in a caustic solution will enhance chemical degradation of the resin. Due to safety considerations and the concern regarding the potential for organic-nitrate oxidation reactions, cation exchange resins are often converted to the sodium form with

sodium hydroxide to prepare them for storage. Historically, runaway organic-nitrate oxidation reactions have caused significant damage to ion exchange systems. For this reason, following elution with nitric acid, it is recommended that the organic resin be converted to the sodium form as quickly as possible.

4.0 Conclusions and Recommendations

The data among the tests are consistent and indicate the relative stability of the SuperLig® 644/WWL membrane under a variety of chemical and radiolytic conditions. The material was irradiated in ambient air, distilled water, dilute nitric acid, and highly caustic tank waste simulant (NCAW). Following exposure from 0 to $2.0\text{E}+09$ rad, the material was evaluated for cesium uptake in a series of 5 M sodium NCAW simulants with variable cesium concentrations.

- Essentially no decrease in cesium selectivity or capacity (K_d) was observed during the irradiation of the SuperLig® 644/WWL membrane in distilled water or 0.5 M HNO_3 up to a total gamma irradiation (cobalt-60) dose of $2.0\text{E}+09$ rad. The stability of the SuperLig® 644/WWL membrane, as measured by the cesium K_d on a mass equivalent basis, is essentially equivalent to that of the SuperLig® 644 resin in the absence of the WWL membrane.
- Essentially no decrease in cesium selectivity or capacity (K_d) was observed during the irradiation of the SuperLig® 644/WWL membrane in 5 M NCAW or ambient air up to $1.0\text{E}+08$ rad.
- Following irradiation of the SuperLig® 644/WWL membrane in either 5 M NCAW or ambient air, the observed Cs K_d values decreased more than an order of magnitude between $1.0\text{E}+08$ and $2.0\text{E}+09$ rad. These high irradiation dose results portray upper bounding limits and should not be considered representative of typical ion exchange process conditions.
- The cesium K_d results for the SuperLig® 644/WWL membrane irradiated in 5 M NCAW were significantly lower than those results obtained in other solutions (0.5 M HNO_3 , distilled water, or ambient air). K_d s of approximately 80 mL g^{-1} were observed for the NCAW-irradiated membrane and about 300 mL g^{-1} for irradiation in the other matrices. These results suggest that the material is less stable in the caustic NCAW solution than in the other matrices, irrespective of the radiation exposure.

5.0 References

10 CFR 61. 1994. U.S. Nuclear Regulatory Commission, "Disposal of Low-Level Radioactive Wastes." U.S. Code of Federal Regulations.

Bibler, J. P. 1991. *A Comparison of Duolite™ CS-100 and SRS Resorcinol/Formaldehyde Ion Exchange Resins with Three High-Level Waste Simulants Before and After γ -Irradiation.* WSRC-RP-91-1221, Westinghouse Savannah River Company, Savannah, Georgia.

Bibler, J. P. 1994. Year-End Report for UST: Cesium Extraction Testing Project DOE/DT&E TTP No. SR1-03-20-01 (U). WSRC-RP-94-146. Westinghouse Savannah River Company, Aiken, South Carolina.

Bibler, N. E. and C. L. Crawford. 1994. *An Investigation of the Radiolytic Stability of a Resorcinol-Formaldehyde Ion Exchange Resin.* WSRC-RP-94-148. Westinghouse Savannah River Company, Aiken, South Carolina.

Bibler, J. P., R. M. Wallace, and L. A. Bray. 1989. "Testing A New Cesium-Specific Ion Exchange Resin For Decontamination of Alkaline-High Activity Waste." In *Proceedings of the Symposium on Waste Management '90*, February 25 - March 1, 1990. Tucson, Arizona.

Bray, L. A. 1989. *Determination of Batch Sorption Ratios for Ion Exchange Materials Using Radionuclide Tracer Techniques.* WTC-006-21-1, PNL Test Procedure, Pacific Northwest Laboratory, Richland, Washington.

Bray, L. A. and F. T. Hara. 1991. "Use of Titanium-Treated Zeolite for Plutonium, Strontium, and Cesium Removal from West Valley Alkaline Wastes and Sludge Wash Waters." In *First Hanford Separations Science Workshop*. PNL-SA-19697S, pp. II.87-II.91. Pacific Northwest Laboratory, Richland, Washington.

Bray, L. A., C. D. Carlson, K. J. Carson, J. R. DesChane, R. J. Elovich, and D. E. Kurath. 1993a. *Initial Evaluation of Two Organic Resins and Their Ion Exchange Column Performance for the Recovery of Cesium from Hanford Alkaline Wastes.* TWRSP-93-055, Pacific Northwest Laboratory, Richland, Washington.

Bray, L. A., K. J. Carson, and R. J. Elovich. 1993b. *Initial Evaluation of Sandia National Laboratory Prepared Crystalline Silico-Titanates for the Recovery of Cesium.* PNL-8847, Pacific Northwest Laboratory, Richland, Washington.

Bray, L. A., K. J. Carson, R. J. Elovich, and D. E. Kurath. 1992. *Equilibrium Data for Cesium Ion Exchange of Hanford CC and NCAW Tank Waste.* TWRSP-92-020, Pacific Northwest Laboratory, Richland, Washington.

Bray, L. A., K. J. Carson, and R. J. Elovich. 1990. *Cesium Recovery Using Savannah River Laboratory Resorcinol-Formaldehyde Ion Exchange Resin*. PNL-7273, Pacific Northwest Laboratory, Richland, Washington.

Bray, L. A., L. K. Holton, T. R. Meyers, G. M. Richardson, and B. M. Wise. 1984. *Experimental Data Developed to Support the Selection of a Treatment Process for West Valley Alkaline Supernatant*. PNL-4969, Pacific Northwest Laboratory, Richland, Washington.

Brown, G. N., L. A. Bray, C. D. Carlson, K. J. Carson, J. R. DesChane, R. J. Elovich, F. V. Hoopes, D. E. Kurath, L. L. Nenninger, and P. K. Tanaka. 1996. *Comparison of Organic and Inorganic Ion Exchangers for Removal of Cesium and Strontium from Simulated and Actual Hanford 241-AW-101 DSSF Tank Waste*. PNL-10920, Pacific Northwest National Laboratory, Richland, Washington.

Brown, G. N., S. R. Adami, L. A. Bray, S. A. Bryan, C. D. Carlson, K. J. Carson, J. R. DesChane, R. J. Elovich, S. J. Forbes, J. A. Franz, J. C. Linehan, W. J. Shaw, P. K. Tanaka, and M. R. Telander. 1995a. *Chemical and Radiation Stability of SuperLig® 644, Resorcinol-Formaldehyde, and CS-100 Cesium Ion Exchange Materials*. PNL-10772, Pacific Northwest National Laboratory, Richland, Washington.

Brown, G. N., J. R. Bontha, C. D. Carlson, K. J. Carson, J. R. DesChane, R. J. Elovich, D. E. Kurath, P. K. Tanaka, D. W. Edmonson, D. L. Herting, and J. R. Smith. 1995b. *Ion Exchange Removal of Cesium from Simulated and Actual Supernate from Hanford Tanks 241-SY-101 and 241-SY-103*. PNL-10792, Pacific Northwest National Laboratory, Richland, Washington.

Brown, G. N., L. A. Bray, and R. J. Elovich. 1995c. *Evaluation and Comparison of SuperLig® 644, Resorcinol-Formaldehyde and CS-100 Ion Exchange Materials for the Removal of Cesium from Simulated Alkaline Supernate*. PNL-10486, Pacific Northwest Laboratory, Richland, Washington.

Bryan, S. A., S. R. Adami, L. A. Bray, C. D. Carlson, J. R. DesChane, R. J. Elovich, and M. R. Telander. 1993. *Radiation Testing of Organic Ion Exchange Resin, CS-100*. TWRSP-93-073, Pacific Northwest Laboratory, Richland, Washington.

Carlson, C. D., S. R. Adami, L. A. Bray, G. N. Brown, S. A. Bryan, J. R. DesChane, R. J. Elovich, J. A. Franz, D. E. Kurath, J. C. Linehan, W. J. Shaw, and M. R. Telander. 1995. *Radiation Testing of Organic Ion Exchange Resins*. PNL-10767, Pacific Northwest Laboratory, Richland, Washington.

Hubler, T. L., J. A. Franz, W. J. Shaw, S. A. Bryan, R. T. Hallen, G. N. Brown, L. A. Bray, and J. C. Linehan. 1995. *Synthesis, Structural Characterization, and Performance of Resorcinol-Formaldehyde (R-F) Ion-Exchange Resin*. PNL-10744, Pacific Northwest Laboratory, Richland, Washington.

Kurath, D. E., L. A. Bray, K. P. Brooks, G. N. Brown, S. A. Bryan, C. D. Carlson, K. J. Carson, J. R. DesChane, R. J. Elovich, and A. Y. Kim. 1994. *Experimental Data and Analysis to Support the Design of an Ion Exchange Process for the Treatment of Hanford Tank Waste Supernatant Liquids*. PNL-10187, Pacific Northwest Laboratory, Richland, Washington.

Kurath, D. E., L. A. Bray, W. A. Ross, and D. K. Ploetz. 1989. "Correlation of Laboratory Testing and Actual Operations for the West Valley Supernatant Treatment System." Presented at the Fourth International Symposium on Ceramics in Nuclear Waste Management, American Ceramic Society Annual Meeting, April 23-27, 1989. PNL-SA-16871, Pacific Northwest Laboratory, Richland, Washington.

Marsh, S. F., Z. V. Svitra, and S. M. Bowen. 1994a. *Distributions of 14 Elements on 63 Absorbers from Three Simulant Solutions (Acid-Dissolved Sludge, Acidified Supernate, and Alkaline Supernate) for Hanford HLW Tank 102-SY*. LA-12654, Los Alamos National Laboratory, Los Alamos, New Mexico.

Marsh, S. F., Z. V. Svitra, and S. M. Bowen. 1994b. *Distributions of 15 Elements on 58 Absorbers from Simulated Hanford Double-Shell Slurry Feed (DSSF)*. LA-12863, Los Alamos National Laboratory, Los Alamos, New Mexico.

Marsh, S. F., Z. V. Svitra, and S. M. Bowen. 1994c. *Distributions of 12 Elements on 64 Absorbers from Simulated Hanford Neutralized Current Acid Waste (NCAW)*. LA-12889, Los Alamos National Laboratory, Los Alamos, New Mexico.

Marsh, S. F., Z. V. Svitra, and S. M. Bowen. 1995. *Effects of Aqueous-Soluble Organic Compounds on the Removal of Selected Radionuclides from High-Level Waste*. LA-12863, Los Alamos National Laboratory, Los Alamos, New Mexico.

Penwell, D. L., K. M. Eager, and B. J. Knutson. 1994. *Preliminary Flowsheet: Ion Exchange Process for Separation of Cesium from Hanford Tank Waste Using Resorcinol-Formaldehyde Resin*. WHC-SD-WM-TI-638 Rev. 0, Westinghouse Hanford Company, Richland, Washington.

Distribution

**No. of
Copies**

**No. of
Copies**

OFFSITE

- 2 DOE/Office of Scientific and Technical
Information

G. Allen
Department 6607/MS 0756
Sandia National Laboratories
P.O. Box 5800
Albuquerque, NM 87185-0756

D. H. Bandy
U.S. Department of Energy
P.O. Box 5400
Albuquerque, NM 87115

J. E. Baublitz, EM-40
DOE/Office of Environmental
Restoration
Forrestal Building
U.S. Department of Energy
1000 Independence Ave. SW
Washington, DC 20585

J. P. Bibler
Westinghouse Savannah River Co.
Building 773 A
Aiken, SC 29802

- 2 W. W. Bixby, EM-60
DOE/Office of the Deputy Assistant
Secretary Facility
Transition and Management
U.S. Department of Energy
1000 Independence Ave. SW
Washington, DC 20585

N. E. Brown
6608 Loftus, NE
Albuquerque, NM 87109

R. L. Bruening
505 East 1860 South
IBC Advanced Technologies, Inc.
American Fork, UT 84603

J. Coronas
Ames Laboratory
329 Wilhelm Hall
Iowa State University
Ames, IA 50011

R. Craig
HAZWRA
P.O. Box 2003, MS 7606
Oak Ridge, TN 37831-7606

- 6 DOE/Office of Technology Development
Trevion II Building
12800 Middlebrook Road
Germantown, MD 20874
ATTN: G. G. Boyd EM-50
S. T. Lien EM-53
R. T. Parker EM-52
P. J. Ritzcovan EM-542
W. C. Schutte EM-54
S. M. Wolfe EM-532

- 5 DOE/Office of Waste Management
Trevion II Building
12800 Middlebrook Road
Germantown, MD 20874
ATTN: J. O. Boda EM-32
J. A. Coleman EM-35
S. P. Cowan EM-30
S. L. Domotor EM-35
H. F. Walter EM-34

**No. of
Copies**

N. Egan
Program Development Division
MSE Inc.
P.O. Box 3767
Butte, MT 59702

D. Emilia
Strategic Planning Dept.
Chem-Nuclear Geotech
P.O. Box 1400
2597B-3/4 Road (81503)
Grand Junction, CO 81502-2567

B. Erdal
Los Alamos National Laboratory
MS D446
Los Alamos, NM 87545

D. J. Fennelly
UOP Corp.
307 Fellowship Road
Suite 207
Mt. Laurel, NJ 08054

2. J. J. Fiore, EM-42
DOE/Office of Environmental
Restoration
Trevion II Building
12800 Middlebrook Road
Germantown, MD 20874

C. W. Frank, EM-50
DOE/Office of Technology Development
Forrestal Building
U.S. Department of Energy
1000 Independence Ave. SW
Washington, DC 20585

E. Franz
Brookhaven National Laboratory
Building 830
Upton, NY 11973

**No. of
Copies**

K. D. Gerdes, EM-532
DOE/Office of Technology Development
19901 Germantown Road
Germantown, MD 20874

J. E. Helt
Office of Waste Management Programs
9700 South Cass Avenue
Argonne, IL 60439-4837

R. Jacobson
Desert Research Institute
P.O. Box 19040
Las Vegas, NV 89132

- 3 T. M. Kafka
3M Center
Bldg. 209-1W-24
St. Paul, MN 55144-1000

K. Kibbe
Martin Marietta Energy Systems
P.O. Box 2003
Bldg. K-1011, MS 7172
Highway 58
Oak Ridge, TN 37831-7172

K. Kostelnik
EG&G Idaho, Inc., MS 3930
P.O. Box 1625
200 South Woodruff
Idaho Falls, ID 83415-3970

J. E. Lytle, EM-30
DOE/Office of Waste Operations
Forrestal Building
U.S. Department of Energy
1000 Independent Ave. SW
Washington, DC 20585

J. F. McGlynn
SAIC
555 Quince Orchard Road, Suite 500
Gaithersburg, MD 20878

No. of
Copies

No. of
Copies

K. McWilliam
U.S. Department of Energy
Nevada Operations Office
P.O. Box 98518
Las Vegas, NV 89109

P. J. Pettit
P.O. Box 538704
Mailstop 81-2
Cincinnati, OH 45253-8704

J. Moore
U.S. Department of Energy
Oak Ridge Operations Office
P.O. Box E
Oak Ridge, TN 37831

R. W. Rice
MSE, Inc.
307 Quincy
El Paso, TX 79922

K. Nuhfer
FERMCO
P.O. Box 398704
Cincinnati, OH 45239-8704

2 Sandia National Laboratories
P.O. Box 5800
Albuquerque, NM 87185-5800
ATTN: J. E. Miller MS-0709
J. Nelson MS-6621

9 Oak Ridge National Laboratory
P.O. Box 2008
Oak Ridge, TN 378731-6223
ATTN: J. B. Berry MS-6044
J. L. Collins MS-6221
B. Z. Egan MS-6223
R. D. Hunt MS-6273
D. Lee MS-6221
A. P. Malinauskas MS-7271
C. P. McGinnis MS-6273
J. F. Walker MS-6149
J. S. Watson MS-6149

G. Staats
U.S. Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, PA 15236-0940

J. L. Steele
Savannah River Site
SRL, 773 A, A208
Aiken, SC 29802

D. Olona
U.S. Department of Energy
Albuquerque Operations office
P.O. Box 5400
Albuquerque, NM 87115

S. L. Stein
Battelle Seattle Research Center
4000 NE 41st Street
Seattle, WA 98105

B. Park
MSE Inc.
P.O. Box 4078
Butte, MT 59702

K. Stevenson
U.S. Department of Energy
376 Hudson Street
New York, NY 10014-3621

J. L. Swanson
1318 Cottonwood Drive
Richland, WA 99352

**No. of
Copies**

J. Sweeney
U.S. Department of Energy
Oak Ridge Operations Office
P.O. Box E
Oak Ridge, TN 37831

I. R. Tasker
Waste Policy Institute
Quince Diamond Executive Center
555 Quince Orchard Road
Gaithersburg, MD 20878-1437

M. C. Thompson
Savannah River Technology Center
P.O. Box 616
Aiken, SC 29802

2 T. A. Todd
Lockheed Idaho Technology Company
P.O. Box 1625, MS 5213
Idaho Falls, ID 83415

C. Tsang
Earth Sciences Division
Bldg. 50E
Lawrence Berkeley Laboratory
Berkeley, CA 94720

S. Turner
BNFL
2261 Stevens Drive
Richland, WA 99352

UOP Corp.
50 East Algonquin
Des Plaines, IL 60017-5016
ATTN: J. Sherman
R. Braun

S. Webster
U.S. Department of Energy
Chicago Field Office
9800 South Cass Avenue
Argonne, IL 60439-4837

**No. of
Copies**

T. Williams
U.S. Department of Energy
Idaho Operations Office
785 DOE Place
Idaho Falls, ID 83402

J. Wright
U.S. Department of Energy
Savannah River Operations Office
RFD #1, Bldg. 703A, Rm. E208 North
P.O. Box A
Aiken, SC 29802

S. Yates
AlliedSignal
50 East Algonquin Road
Des Plaines, IL 60017-5016

J. Yow
Lawrence Livermore National Laboratory
7000 East Avenue
P.O. Box 808
Livermore, CA 94550

C. Zeh
Morgantown Energy Technology Center
3610 Collins Ferry Road
Morgantown, WV 26507-0880

ONSITE

7 DOE Richland Operations Office

J. A. Frey	K8-50
J. P. Hanson	K8-50
P. E. Lamont	S7-53
C. S. Louie	S7-53
B. M. Mauss	K8-50
D. E. Trader	K8-50
L. S. Walder	S7-53

**No. of
Copies**

**No. of
Copies**

7 Bechtel Hanford, Incorporated

A. G. Duda	HO-18
M. H. Hyman	H4-80
S. A. Hobart	H4-80
K. J. Koegler	HO-18
S. Kretzschmar	X5-54
M. J. Lauterbach	X5-54
S. K. Pulsford	X5-53

2 CH2M Hill Hanford, Inc.

T. E. Moody	H9-03
D. J. Vaught	H9-01

MACTEC

D. J. Swanberg	K8-50
----------------	-------

15 Westinghouse Hanford Company

J. N. Appel	G3-21
S. A. Barker	R2-11
W. B. Barton	R2-11
G. T. Berlin	H6-34
J. D. Berger	L0-18
M. D. Britton	S4-25
K. M. Eager	H5-27
K. A. Gasper	G3-21
D. L. Herting	T6-09
C. V. King	S4-25
R. A. Kirkbride	H5-27
M. J. Klem	H5-27
D. L. Penwell	H5-27
I. E. Reep	G3-21
D. J. Washenfelter	H5-27

46 Pacific Northwest National Laboratory

J. E. Amonette	K9-77
W. F. Bonner	K9-14
L. A. Bray	P7-25
K. P. Brooks	P7-43
T. M. Brouns	K9-08
G. N. Brown (10)	P7-25
G. H. Bryan	P7-25
S. A. Bryan	P7-25
B. C. Bunker	K2-45
K. J. Carson	P7-25
C. D. Carlson	P7-25
R. J. Elovich	P7-25
J. A. Franz	K2-44
J. M. Gephart	K2-21
L. K. Holton	K9-73
T. L. Hubler	P8-38
W. L. Kuhn	K2-21
D. E. Kurath	P7-20
J. P. LaFemina	K2-25
M. E. Peterson	K2-47
R. K. Quinn	K9-69
W. G. Richmond	K9-33
L. J. Sealock	K2-10
J. T. Slankas	K9-81
S. O. Slate	P8-44
Technical Report Files (5)	
PNL Information Release	
Office (7)	K1-11