


JUN 13 1966

NAS-CR-54973

MASTER



RELEASED FOR ANNOUNCEMENT
IN NUCLEAR SCIENCE ABSTRACTS

GENERATION OF LONG TIME CREEP DATA ON REFRACTORY ALLOYS AT ELEVATED TEMPERATURES

ELEVENTH QUARTERLY REPORT

Prepared for
**NATIONAL AERONAUTICS AND SPACE ADMINISTRATION
LEWIS RESEARCH CENTER
UNDER CONTRACT NAS 3-2545**

TRW EQUIPMENT LABORATORIES
CLEVELAND, OHIO

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the National Aeronautics and Space Administration (NASA), nor any person acting on behalf of NASA:

- A.) Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or
- B.) Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method or process disclosed in this report.

As used above, "person acting on behalf of NASA" includes any employee or contractor of NASA, or employee of such contractor, to the extent that such employee or contractor of NASA, or employee or such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with NASA, or his employment with such contractor.

Request for copies of this report should be referred to
National Aeronautics and Space Administration
Office of Scientific and Technical Information
Attention: AFSS-A
Washington, D. C. 20546

ELEVENTH QUARTERLY REPORT

for

26 December 1965 to 26 March 1966

RELEASED FOR ANNOUNCEMENT
IN NUCLEAR SCIENCE ABSTRACTS

GENERATION OF LONG TIME CREEP DATA
OF REFRACTORY ALLOYS AT ELEVATED TEMPERATURES

Prepared by:

J.C. Sawyer and E. A. Steigerwald

Prepared for:

National Aeronautics and Space Administration

Contract No. NAS 3-2545

Technical Management

Paul E. Moorhead
NASA - Lewis Research Center
Space and Power Systems

April 15, 1966


Materials Research and Development Department
TRW Equipment Laboratories
TRW Inc.
23555 Euclid Avenue
Cleveland, Ohio 44117

FOREWORD

The work described herein is being performed by TRW Inc. under the sponsorship of the National Aeronautics and Space Administration under Contract NAS 3-2545. The purpose of this study is to obtain design creep data on refractory metal alloys for use in advanced space power systems.

The program is administered for TRW Inc. by E. A. Steigerwald, Program Manager. J. C. Sawyer is the Principal Investigator, and R. R. Ebert contributed to the program. The NASA technical director is Paul E. Moorhead.

Prepared by



J. C. Sawyer
Sr. Research Metallurgist

Approved by



E. A. Steigerwald
Research Supervisor

TABLE OF CONTENTS

		<u>Page No.</u>
I	INTRODUCTION	1
II	MATERIALS AND PROCEDURE.....	1
III	RESULTS AND DISCUSSION.....	5
	Molybdenum Base Alloys.....	5
	Tantalum Base Alloys.....	19
	Tungsten.....	19
IV	FUTURE WORK.....	29
	APPENDIX I.....	32

I INTRODUCTION

Space electric power systems depend upon the use of refractory metals in a variety of component areas. A critical property parameter in the design of these systems is the long-time creep strength at very low pressures. Since oxygen contamination of refractory metal alloys can occur under conditions of 1×10^{-6} Torr, vacuums better than 1×10^{-8} Torr must be used to obtain creep measurements which are employed in the design of space components. The purpose of this program is to generate long-time creep data on selected refractory alloys which have potential use in advanced power systems. Emphasis has been placed on testing sheet alloys which can be employed for cladding or tubing applications and on forgeable, high-strength turbine alloys.

This report presents the creep data obtained during the eleventh quarter on arc-cast and vapor-deposited tungsten, the molybdenum base alloys TZC, TZM, and columbium modified TZM, and the tantalum base alloys T-111 and T-222.

II MATERIALS AND PROCEDURE

A summary of the composition, heat treatments, and current tests of the alloys discussed in this report is presented in Tables 1, 2, and 3. A detailed review of the processing history and microstructure has been previously presented in the Ninth Quarterly Progress Report, NASA CR-54773. Tungsten was evaluated both as 0.030" sheet and as vapor-deposited material. Two heats of TZM and TZC material were tested. The TZM was obtained from two different vendors while the TZC came from the same vendor but had significantly different processing histories. In the TZC Heat M-91 material, three different heat treatments were evaluated at similar test conditions to provide an indication of possible effects produced by structural variations. The tantalum base alloys T-111 and T-222, were both evaluated as sheet material after selected recrystallization treatments.

The test procedure involved obtaining a vacuum of 5×10^{-10} Torr or better at room temperature, then heating the specimen at a rate so that the pressure never went above 1×10^{-6} Torr. Heat treatment was performed on the materials in situ, prior to load application. After heat treatment the specimens were cooled to room temperature and then reheated to the test temperature which was maintained for two hours to insure equilibrium. During testing the vacuum was less than 1×10^{-8} Torr and generally decreased with test time.

TABLE 1

Chemical Composition of Alloys Being Evaluated in Creep Program (Weight %)

Material	W	Mo	Ta	Hf	C	N ₂	Ti	Zr	ppm	
									O ₂	H ₂
Tungsten (arc-cast)	Bal.				.0058				9	4
Tungsten(vapor-deposited) (General Atomics)	Bal.				.0012				12-14	1-3
TZM (Climax Heat 7502)		Bal.			.013	.011	.47	.091	20	7
TZM- Heat KDTZM-1175 (AiResearch)		Bal.			.031 (.024)	.0043	.61 (.49)	.12 (.144)	34	9(note 1) (note 2)
TZC (Heat M-80)		Bal.			.140	.0018	1.02	.130	41	5
TZC (Heat M-91)		Bal.			.145	.003	1.17	.274	37	10
Cb Modified TZM (Heat 4305-4)		Bal.			.06		.50	.32		+1.62Cb
T-222	9.57		Bal.	2.93	.012	.0026			35	11
T-111	8.5		Bal.	2.30	.004	.002			55	6

Note 1 - TRW Analysis

Note 2 - AiResearch Analysis

TABLE 2

Summary of Material Variables Being Evaluated in Creep Program¹

Material	Form	Test Temperature	Test Condition
Tungsten	Arc-Melted 0.030" Sheet	3200°F (1760°C)	Recrystallized 1 hour at 2800°F (1538°C)
Tungsten	Vapor-deposited ² 1/8" dia. Bars	3200°F (1760°C)	As-received
TZM Climax Heat 7502)	"Pancake" Forging	2000°F (1093°C)	(Cond. 1) As-received (stress-relieved condition.)(Cond. 2) Annealed 1 hour, 2850°F (1566°C)
TZM-Heat KDTZM-1175 (AiResearch) ³	"Pancake" Forging	1600-1856°F (871-1013°C)	As-received (stress-relieved, 2300°F (1260°C), 1 hour
ω Cb Modified TZM	5/8" dia. Bar	2000-2200°F (1093-1204°C)	As-received (stress-relieved, 2500°F (1371°C), 1 hour
TZC (Heat M-80) TZC (Heat M-91)	3/4" Plate	1800-2200°F (982-1204°C)	Three conditions: stress-relieved 2300°F (1260°C) 1 hour; annealed 3092°F (1700°C) 1 hour; or annealed 3092°F (1700°C), 1 hour age 2400°F (1315°C), 5 hours
T-222 ⁴	0.030" Sheet	1800-2200°F	Recrystallized 3000°F (1649°C), 1 hour
T-111	0.030" Sheet	1800, 2000, 2200°F (982, 1093, 1204°C)	Recrystallized 2600°F (1426°C), 1 hour or Recrystallized 3000°F (1649°C), 1 hour

1. More detailed processing history given in 9th Quarterly Report, NASA-CR 54773.

2. Vapor deposition procedure described in detail in NASA-CR 54715, GA-6522; Studies of Thermionic Mat.; October 15, 1965.

3. Forging of this material described in detail in AFAPL-TR-65-51; Materials Investigation, SNAP 50/SPUR Program, Mechanical Properties of TZM, R. L. Salley and E. A. Kovacevich, June, 1965.

4. Originally scheduled to be tested as ST-222 plate material, program plan revised to include material as T-222 grade applicable for tubing.

TABLE 3

Summary of Creep Tests Completed or in Progress During the Eleventh Quarter

Material	Unit	Test No.	Condition	Test Temperature		Stress		Time (Hrs.)	Creep %
				(°F)	(°C)	Ksi	N/m ²		
TZC (M-80)	2	B-9	Annealed 1700°C, 1 Hr.	2000	1093	20	1.38 x 10 ⁸	9137	0.462
TZC (M-80)	8	B-11	Annealed 1700°C, 1 Hr.	1856	1013	25	1.72 x 10 ⁸	8430	0.168
TZC (M-80)	13	B-12	Annealed 1700°C, 1 Hr.	2056	1124	19	1.31 x 10 ⁸	8207	0.228
TZC (M-91)	11	B-19	S-R, 1260°C, 1 Hr.	1800	982	44	3.03 x 10 ⁸	4604	1.015*
TZC (M-91)	9	B-20	Annealed 1700°C, 1 Hr.	2000	1093	20	1.38 x 10 ⁸	3379	0.482
TZC (M-91)	1	B-22	Annealed 1700°C, 1 Hr.	2000	1093	20	1.38 x 10 ⁸	1123	1.010*
			Aged 1316°C, 5 Hrs.						
TZC (M-91)	6	B-26	Annealed 1700°C, 1 Hr.	1800	982	44	3.03 x 10 ⁸	Broke on loading	
TZM (Climax) (7502)	6	B-3	S-R, 1204°C, 1 Hr.	2000	1093	10	6.90 x 10 ⁷	10,048	0.375*
TZM (Climax) (7502)	12	B-4	Annealed 1566°C, 1 Hr.	2000	1093	10	6.90 x 10 ⁷	10,012	0.368*
TZM (AiRes) (1175)	14	B-21	S-R, 1260°C, 1 Hr.	1600	871	65	4.48 x 10 ⁸	1630	0.085*
TZM (AiRes) (1175)	14	B-25	S-R, 1260°C, 1 Hr.	1800	982	44	3.03 x 10 ⁸	1145	0.088
Cb-TZM (4305-4)	10	B-23A	S-R, 1371°C, 1 Hr.	2000	1093	20	1.38 x 10 ⁸	686	0.032*
Cb-TZM (4305-4)	10	B-23B	S-R, 1371°C, 1 Hr.	2000	1093	28	1.93 x 10 ⁸	307	0.028*
Cb-TZM (4305-4)	10	B-23C	S-R, 1371°C, 1 Hr.	2000	1093	40	2.76 x 10 ⁸	161	0.172*
Cb-TZM (4305-4)	10	B-23D	S-R, 1371°C, 1 Hr.	1800	982	46	3.17 x 10 ⁸	403	0.078*
Cb-TZM (4305-4)	10	B-23E	S-R, 1371°C, 1 Hr.	2100	1149	34	2.41 x 10 ⁸	64	0.060
Cb-TZM (4305-4)	6	B-27	S-R, 1371°C, 1 Hr.	2000	1093	41	2.82 x 10 ⁸	401	0.162
T-111	7	S-19	Annealed 1649°C, 1 Hr.	2200	1204	8	5.51 x 10 ⁷	2395	1.290
T-111	3	S-21	Annealed 1649°C, 1 Hr.	2200	1204	12	8.26 x 10 ⁷	1865	2.092
T-111	4	S-22	Annealed 1649°C, 1 Hr.	2000	1093	20	1.38 x 10 ⁸	1099	2.010*
T-222	5	S-20	Annealed 1538°C, 1 Hr.	2200	1204	12	8.26 x 10 ⁷	1384	5.060*
W (Arc Melted)	4	S-18	Annealed 1538°C, 1 Hr.	2800	1538	3	2.06 x 10 ⁷	908	5.535*
W (Vapor Deposited)	1	S-24	Annealed 1538°C, 1 Hr.	2800	1538	2	1.38 x 10 ⁷	1313	0.915

* Test Completed

Specimen extension was measured over a two-inch gauge length with an optical extensometer that determined the distance between two reference marks to an accuracy of $\pm 50 \mu$ -inches. The program plan involves testing the plate or forged alloys at temperatures between 1600 and 2250°F (871 and 1235°C) until a 1% total elongation is obtained. The tungsten materials are being tested at 2800 and 3200°F (1566 and 1760°C) for total extensions between 3 and 5% while the tantalum-base materials are being evaluated in the 1800 to 2200°F (982 to 1204°C) range to an elongation of approximately 2 to 5%. The applied stress levels have been selected with the goal of obtaining creep data over total test times between 1000 and 10,000 hours.

III RESULTS AND DISCUSSION

In this section, creep data generated during the eleventh quarter are graphically presented as percent total elongation in the two-inch gauge section as a function of time at the applied stress. Reference marks are placed on the curves to indicate the chamber pressure during the test period. The specific data for each test which was in progress or completed during this quarter are given in detail in Appendix I.

Molybdenum Base Alloys

The three classes of molybdenum-base alloys being examined are TZC, TZM, and columbium-modified TZM.

A summary of the treatments which have been included in the evaluation during this quarter is presented below.

TZC (Heat M-80)

Annealed 3092°F (1700°C), 1 hour

TZC (Heat M-91)

Stress relieved 2300°F (1204°C), 1 hour

Annealed 3092°F (1700°C), 1 hour

Annealed 3092°F (1700°C), 1 hour; Age 2400°F (1316°C), 5 hours

TZM (Heat 7502)

Stress relieved 2200°F (1204°C), 1 hour

Annealed 2850°F (1566°C), 1 hour

TZM (Heat 1175)

Stress relieved 2300°F (1260°C), 1 hour

Columbium Modified TZM (Heat 4305-4)

Stress relieved 2500°F (1371°C), 1 hour

TZC (Heat M-80) is currently being tested at three different temperatures and stresses (see Table 3). The data given in Figure 1 show that creep does not occur in a uniform manner, but exhibits periods of rapid extension followed by an absence of creep or even contraction of the specimen. The discontinuities in the creep curve which occur over several thousand test hours are believed to be a real material effect since they are significantly greater than differences that can be attributed to variations in either temperature or extension measurements. The occurrence of the specimen contraction, coupled with the limited post-test examination indicate that strain-induced precipitation is producing the very low average creep rate in the TZC material.

TZC Heat M-91 is distinguished from Heat M-80 by the greater percent reduction per pass during the rolling operation. This processing treatment resulted in greater room temperature ductility than obtained in the Heat M-80. To determine the effect of heat treatment on the creep properties of TZC, specimens from Heat M-91 are being tested at the conditions shown in Figure 2.

A comparison between the data obtained on the annealed and aged material with the material in the unaged condition indicates that a significant increase in creep rate occurred as a result of aging five hours at 2400°F (1360°C).

Post test examination of the specimen heat treated by annealing at 3092°F (1700°C) and aging five hours at 2400°F (1360 °C) indicated that a longitudinal crack existed in the gauge section (see Figure 3). Further visual examination showed that in some areas a high degree of localized distortion had occurred which can be seen in Figure 3 located approximately 1-1/2 inches from the left side of the bottom photograph. This surface area, shown at 500X in Figure 4, consists of grains exhibiting pronounced slip. A review of the creep curve, Figure 2, gives no indication that cracking occurred during test. On the basis of this examination, plus the fact that cracking during annealing has been reported on material from this same heat*, the conclusion was reached that the creep specimen cracked during the heat treatment performed in situ prior to testing. Since the longitudinal crack did not reduce the cross-sectional area of the specimen, the possibility exists that the aging treatment was the major factor in the increased creep rate. If strain-induced precipitation during the test is a significant factor in reducing creep then this would indicate that a strain induced precipitate is more effective than the precipitate formed by the

* NAS CR-54916






FIGURE 1. CREEP TEST DATA, TZC (HEAT M-80), ANNEALED 3092°F (1700°C) 1 HOUR
TESTED IN VACUUM ENVIRONMENT $< 1 \times 10^{-8}$ TORR






FIGURE 2. CREEP TEST DATA, TZC (HEAT M-91), TESTED IN VACUUM ENVIRONMENT $< 1 \times 10^{-8}$ TORR



Overall Specimen Appearance

1.5X



Close-Up of Longitudinal Crack

3X

Figure 3. TZC Specimen B-22, Heat M-91, Cracked During Creep Testing.

aging heat treatment. On this basis the aged material also would exhibit a higher apparent creep rate.

Microstructural examination was made in an effort to identify the mode of cracking. Figure 5, which shows the defect at 100 and 500X, indicates that the crack is preferentially located in the grain boundary. The microstructure at 6000X, shown in Figure 6, does not reveal any apparent microstructural characteristics which would account for the defect. Since the chemistry of Heat M-91 did not exhibit any abnormalities and since cracks of a similar type have not been observed in Heat M-80, it appears that the higher degree of warm working applied to Heat M-91 renders the alloy susceptible to cracking during the recrystallization operation.

During this report period two 10,000 hour tests of forged TZM (Heat 7502) were completed at 2000°F (1093°C) and 10 Ksi ($6.90 \times 10^7 \text{ N/m}^2$). In one case the specimen was stress relieved at 2200°F (1204°C) for one hour prior to testing while in the other test the specimen was recrystallized for one hour at 2850°F (1566°C). The data, shown in Figure 7A, and summarized in Table 4 indicate that after a rapid extension of almost 0.3% during the first 500 hours, the recrystallized material exhibited a relatively low creep rate and after 10,000 hours the total creep for each condition was comparable.


TABLE 4

Summary of Creep Data, TZM, Heat 7502


Test Temperature 2000°F (1093°C), Stress 10 Ksi ($6.90 \times 10^7 \text{ N/m}^2$)

	<u>Stress Relieved</u> <u>2200°F (1204°C) 1 Hour</u>	<u>Annealed</u> <u>2850°F (1566°C) 1 Hour</u>
Non-linear Creep	0.16% - 1650 Hours	0.32% - 2750 Hours
Steady State Creep Rate	$2.6 \times 10^{-7} \text{ in/in-hr.}$	$8 \times 10^{-8} \text{ in/in-hr.}$
Total Creep - 10,000 Hrs.	0.38%	0.37%

Following the 10,000 hour tests at 2000°F (1093°C) the stress relieved specimen of TZM (Heat 7502) was subjected to both chemical and metallurgical examination. A comparison of the material composition before and after test, presented in Table 5, indicates that the only differences were an increase in the nitrogen and a decrease in the zirconium content.




100X



500X

Figure 5. Photomicrographs of Crack in TZC (M-91) Specimen B-22,
Etchant: 15% HF, 15% H₂SO₄, 8% HNO₃, 62% H₂O



6000X

Figure 6. Microstructure of TZC (M-91) Annealed at 1700°C (3092°F),
1 Hour and Aged 1316°C (2400°F), 5 Hours.
Etchant: 15% HF, 15% H₂SO₄, 8% HNO₃, 62% H₂O




FIGURE 7A. CREEP TEST DATA, TZM HEAT 7502, TESTED AT 2000°F (1093°C) AND 10 Ksi (6.90×10^7 N/m²) IN VACUUM ENVIRONMENT $< 1 \times 10^{-8}$ TORR




FIGURE 7B. CREEP TEST DATA, TZM HEAT 1175, STRESS RELIEVED 2300°F (1260°C) 1 HOUR, TESTED IN VACUUM ENVIRONMENT $< 1 \times 10^{-8}$ TORR

TABLE 5
CHEMICAL ANALYSIS TZM FORGED DISC (HEAT 7502)
(Weight Percent)

<u>Element</u>	<u>TAP - DMS*</u> <u>070</u>	<u>Vendor</u> <u>Certification</u>	<u>TRW</u> <u>Analysis</u>	<u>Analysis After</u> <u>10,048 hrs. at 2000°F</u> <u>(Stress-relieved specimen)</u>
Al	<0.0080	<0.001	<0.008	<0.008
C	0.01 - 0.04	0.013	0.010	0.012
Cb	<0.0100	<0.005	<0.010	<0.010
Co	<0.0025	<0.001	<0.0025	<0.0025
Cr	<0.0025	<0.001	<0.0025	<0.0025
Cu	<0.0025	<0.001	<0.0025	<0.0025
Fe	<0.0050	<0.001	<0.005	<0.005
H ₂	<0.0010	<0.0001	0.0007	0.0007
Mg	<0.0025	<0.001	<0.0025	<0.0025
Mn	<0.0050	<0.001	<0.005	<0.005
Mo	Balance	Balance	Balance	Balance
N ₂	<0.0050	0.0011	0.001	0.004
Ni	<0.0050	<0.001	<0.005	<0.005
O ₂	<0.0050	<0.0002	0.002	0.0031
Pb	<0.0050	<0.001	<0.005	<0.005
Si	<0.0050	<0.002	<0.005	<0.005
Sn	<0.0100	<0.001	<0.01	<0.010
Ti	0.40 - 0.55	0.47	0.44	0.50
V	<0.0050	<0.001	<0.005	-
Zr	0.06 - 0.12	0.091	0.10	0.05

* TRW Material Laboratory Specification

Round robin chemical analyses conducted by the Materials Advisory Board* have indicated that with TZM the following variations in composition can be expected from scatter of all combined data from cooperating laboratories.

<u>Element</u>	<u>Standard Deviation (S) ppm</u>	<u>Mean ($\bar{X}$) ppm</u>	<u>Coefficient of Variation ($S/\bar{X}$)</u>
C	30.6	228	13.4%
N ₂	5.9	14	42.1%
Zr	76.0	900	8.5%

On the basis of these statistical data the differences in carbon analyses would not be significant while the changes in both the nitrogen and zirconium content shown in Table 5 are real effects.

A second lot of TZM, designated as Heat 1175, was received from NASA in the form of a forged disc. Creep tests were conducted on this material in the stress relieved condition at 1600°F (871°C), 65 Ksi ($4.48 \times 10^8 \text{ N/m}^2$) and at 1800°F (982°C), 44 Ksi ($3.03 \times 10^8 \text{ N/m}^2$). The results shown in Figure 7B indicate that at both conditions exceptionally low creep rates were obtained. In fact at 1800°F (982°C) the applied stress on the TZM in the stress relieved condition is actually greater than the tensile strength of the recrystallized TZC (Heat M-91) at that temperature.

Columbium modified TZM was procured from Climax Molybdenum Company to compare its creep properties to those of conventional TZM. Since disc forgings were not available, the material was obtained in the form of 5/8-inch diameter wrought bar. Chemical analyses indicated that the material had a composition comparable to the TZM shown in Table 1 with the exception that 1% columbium was added. The first test of the stress relieved alloy was carried out at 2000°F (1093°C) and 20 Ksi ($1.38 \times 10^8 \text{ N/m}^2$). After 686 hours of testing only 0.032% creep occurred and the test was terminated. Because of the limited amount of material, this specimen was retested at various temperatures and stresses and the creep data were extrapolated to 1% to establish a tentative Larson-Miller curve which could be used to select future test conditions. Based upon these results a test was initiated on the stress relieved material at 2000°F (1093°C) and 41 Ksi ($2.82 \times 10^8 \text{ N/m}^2$). After 400 hours a total creep of 0.162% has been obtained.

The currently available creep data on the molybdenum base alloys is summarized in Figure 8 using the Larson-Miller parameter. Although some of the data involve extrapolations to 0.5% creep, several trends are apparent.

* D. L. Chase, "Comparison of Chemical Analyses of Refractory Alloys", (MAB Survey), DMIC 220, (September 10, 1965).




FIGURE 8 LARSON-MILLER PLOT OF DATA FOR 0.5% CREEP IN VARIOUS MOLYBDENUM-BASE ALLOYS

At the low values of the parameter the stress-relieved TZM material with its relatively high tensile strength exhibits the greatest creep resistance. At higher temperatures the recrystallized TZC appears to have the greatest creep resistance. Although the Cb-modified TZM appears to have good properties at higher temperature the data have been obtained from relatively long extrapolations and must be considered tentative.

Tantalum-Base Alloys

The influence of annealing temperature on the creep properties of T-111 and T-222 are evaluated in an effort to select the optimum heat treatment. A comparison of the creep properties of T-222 annealed at 2800°F (1538°C) and 3000°F (1649°C) are shown in Figure 9 while the creep data for T-111 after 2600°F (1427°C) and 3000°F (1649°C) anneals are given in Figure 10. In each case, the 3000°F (1649°C) annealing treatment produced a structure with the greatest resistance to creep extension.

Creep data for T-111 annealed at 3000°F (1649°C) and tested at a variety of conditions are summarized in Figure 11. The data show an increasing creep rate with increasing test time. A direct comparison of the creep behavior of T-111 and T-222, both annealed at 3000°F (1649°C) is presented in Figures 12 and 13. Although under specific test conditions (high temperature, low stress) the T-111 alloy had greater creep resistance. The data are not sufficient to determine whether the differences are due to compositional effects or are the result of normal heat-to-heat variations.

A comparison of the grain size variations produced by selected annealing treatments performed on the T-111 and T-222 alloys is given in Table 6. Typical microstructures for the T-111 and T-222 alloys after the 3000°F (1649°C) anneal are shown in Figure 14. The T-111 was characterized by fine grains at the surface and the appearance of darker etching striations parallel to the rolling direction. As shown by the electron micrograph in Figure 15, the striations are not typical stringers since no definite interface exists with the matrix. On this basis they are believed to be associated with a preferential etching of the microstructure. The preferential etching effect, although minimized, is not completely eliminated by recrystallization at 3000°F (1649°C).

Tungsten

The final test on the arc-melted tungsten sheet at 2800°F (1538°C) and 3 ksi ($2.07 \times 10^7 \text{ N/m}^2$) has been completed and the creep curve is shown in Figure 16. The results are in agreement with the predictions obtained from the Larson-Miller plot given in the Tenth Quarterly Report.




FIGURE 9. CREEP TEST DATA FOR T-222 ALLOY, TESTED AT 2000°F (1204°C), 12 KSI (8.26×10^7 N/m²) IN VACUUM ENVIRONMENT $< 1 \times 10^{-8}$ TORR




FIGURE 10. CREEP TEST DATA, T-111 ALLOY, TESTED AT 2200°F (1204°C) AND 8 Ksi, (5.51×10^7 N/m²), TESTED IN VACUUM ENVIRONMENT $< 1 \times 10^{-8}$ TORR




FIGURE 11. CREEP TEST DATA, T-111 (HEAT 70616) ANNEALED 3000°F (1649°C) 1 HOUR, TESTED IN VACUUM ENVIRONMENT $< 1 \times 10^{-8}$ TORR




FIGURE 12. CREEP TEST DATA FOR T-222 AND T-111, ANNEALED 3000°F, (1649°C), 1 HR, TESTED AT 2200°F (1204°C), 12 ksi (8.26×10^7 N/m²) IN VACUUM ENVIRONMENT $<1 \times 10^{-8}$ TORR






FIGURE 13 LARSON MILLER PLOT, 1% CREEP FOR T-111 AND T-222 ALLOYS ANNEALED 1 HOUR 3000°F (1649°C), TESTED IN VACUUM ENVIRONMENT $<1 \times 10^{-8}$ TORR



T-111



T-222

100X

FIGURE 14. Cross-Sections of Tantalum Base Alloys Taken Parallel to Rolling Direction, Material Annealed at 3000°F (1649°C) for One Hour, Etchant: 15% HF, 15% H₂SO₄, 8% HNO₃, 62% H₂O

TABLE 6

Comparison of Grain Size for T-111 and T-222

Annealed at Various Temperatures

<u>Treatment</u>	<u>T-111</u>	<u>T-222</u>
	<u>ASTM Grain Size</u>	<u>ASTM Grain Size</u>
2400°F - 1 hour	8	-
2600°F - 1 hour	7 - 8	6
2800°F - 1 hour	-	6
3000°F - 1 hour	5 - 6	5 - 6
3000°F - 16 hours	5	5 - 6
3500°F - 1 hour	2 - 3	1 - 2



6000X

Figure 15. T-111, Annealed at 2600°F (1427°C) for One Hour,
Cross Section Showing Details of Striations.
Etchant: 15% HF, 15% H₂SO₄, 8% HNO₃, 62% H₂O




Figure 16. CREEP DATA FOR ARC-MELTED TUNGSTEN, TESTED AT 2800°F (1538°C) IN VACUUM ENVIRONMENT 1 X 10⁻⁸ TORR

Vapor deposited tungsten is currently being evaluated at 2800°F (1538°C) and a stress of 2 ksi ($1.38 \times 10^7 \text{N/m}^2$). The data shown in Figure 17 indicate the trend of slightly decreasing creep rate with increasing test time which has been characteristic of all the test conditions for the tungsten materials. A photomicrograph of the specimen of vapor deposited tungsten removed from test after 2883 hours at 3200°F (1760°C) and 1000 psi ($6.89 \times 10^6 \text{N/m}^2$) is presented in Figure 18. The microstructure is fine grained along one surface which is presumably the interface between the mandrel and deposited tungsten. The microstructure after test contains some apparent porosity which appears preferentially located at the fine grain-coarse grain interface. In addition, the microstructure after test has lost the characteristic columnar structure which is usually associated with vapor deposited materials.

IV FUTURE WORK

Tests will be continued on the molybdenum base alloys. Additional tests will be initiated on the T-111 material to allow the determination of Manson-Haferd constants.





FIGURE 17. CREEP TEST DATA, VAPOR DEPOSITED TUNGSTEN, TESTED AT 2800°F (1538°C) AND 2000 PSI, (1.38×10^8 N/m²) IN VACUUM ENVIRONMENT $< 1 \times 10^{-8}$ TORR



413 DPH

100X

FIGURE 18. Vapor Deposited Tungsten, Creep Tested 2863 Hours
at 3200°F (1760°C) and 1000 psi (6.89×10^6 N/m²), Unetched

APPENDIX I

CREEP TEST DATA

TABLE I

CREEP TEST DATA, TZC PLATE, HEAT M-80, RECRYSTALLIZED AT 3092°F (1700°C) FOR 1 HOUR,

TESTED AT 2000°F (1093°C), 20,000 PSI ($1.38 \times 10^8 \text{ N/m}^2$)

<u>Time</u>	<u>Length Change</u> <u>ΔL (inch)</u> <u>(2" G. L.)</u>	<u>Creep</u> <u>(%)</u>	<u>Pressure</u> <u>(Torr)</u>
1 minutes	.00000	.000	1.2×10^{-9}
2	-.00020	-.010	
3	-.00040	-.020	
4	-.00030	-.015	
5	-.00030	-.015	
10	-.00005	-.002	
15	.00005	.002	
20	.00005	.002	
25	.00010	.005	
30	.00010	.005	
60	.00005	.002	
90	-.00005	-.002	
17.2 hours	.00040	.020	2.6×10^{-9}
41.3	.00060	.030	2.2×10^{-9}
65.2	.00080	.040	2.2×10^{-9}
89.2	.00115	.058	2.0×10^{-9}
161.3	.00110	.055	1.3×10^{-9}
185.7	.00130	.065	1.7×10^{-9}
209.1	.00125	.068	1.7×10^{-9}
233.2	.00125	.062	1.4×10^{-9}
257.3	.00130	.065	1.3×10^{-9}
329.2	.00140	.070	2.0×10^{-9}
355.9	.00145	.072	3.2×10^{-9}
377.0	.00145	.072	3.4×10^{-9}
401.1	.00145	.072	2.4×10^{-9}
425.0	.00150	.075	1.5×10^{-9}
497.2	.00170	.085	1.9×10^{-9}
521.4	.00170	.085	3.1×10^{-9}
545.4	.00165	.082	4.8×10^{-9}
569.2	.00170	.085	4.5×10^{-9}
593.1	.00170	.085	4.6×10^{-9}
665.2	.00165	.082	5.0×10^{-9}
713.3	.00160	.080	4.6×10^{-9}
762.8	.00170	.085	--
833.4	.00175	.088	1.5×10^{-8}
881.4	.00185	.092	6.1×10^{-9}
905.2	.00175	.088	5.8×10^{-9}

TABLE I (Continued)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G.L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
1001.1 hours	.00185	.092	3.9×10^{-9}
1049.2	.00185	.092	6.4×10^{-9}
1097.3	.00190	.095	--
1168.4	.00195	.098	4.2×10^{-9}
1216.2	.00200	.100	7.5×10^{-9}
1264.3	.00195	.098	7.0×10^{-9}
1336.7	.00210	.105	7.5×10^{-9}
1389.5	.00250	.125	--
1433.4	.00255	.128	7.2×10^{-9}
1504.2	.00260	.130	1.3×10^{-8}
1552.3	.00270	.135	1.2×10^{-8}
1600.2	.00265	.132	2.6×10^{-9}
1672.4	.00270	.135	5.5×10^{-9}
1720.4	.00275	.138	3.8×10^{-9}
1768.5	.00285	.142	4.6×10^{-9}
1840.1	.00305	.152	4.4×10^{-9}
1894.6	.00310	.155	4.4×10^{-9}
1936.3	.00315	.158	3.8×10^{-9}
1985.6	.00310	.155	3.8×10^{-9}
2032.2	.00325	.162	4.0×10^{-9}
2057.0	.00330	.165	4.0×10^{-9}
2104.1	.00335	.168	3.8×10^{-9}
2176.1	.00345	.172	3.5×10^{-9}
2248.4	.00370	.185	4.2×10^{-9}
2272.2	.00360	.180	7.5×10^{-9}
2344.2	.00375	.188	2.4×10^{-9}
2396.9	.00380	.190	4.6×10^{-9}
2440.2	.00390	.195	4.4×10^{-9}
2512.0	.00400	.200	2.7×10^{-9}
2584.4	.00400	.200	2.9×10^{-9}
2680.2	.00400	.200	7.4×10^{-9}
2752.2	.00405	.202	5.4×10^{-9}
2872.4	.00415	.208	3.8×10^{-9}
2920.8	.00420	.210	6.2×10^{-9}
3016.1	.00425	.212	3.8×10^{-9}
3088.4	.00435	.218	2.6×10^{-9}
3184.6	.00440	.220	4.2×10^{-9}
3256.3	.00450	.225	4.4×10^{-9}

TABLE I (Continued)

<u>Time</u>	<u>Length Change</u> <u>L (inch)</u> <u>(2" G. L.)</u>	<u>Creep</u> <u>%</u>	<u>Pressure</u> <u>(Torr)</u>
3355.4 hours	.00460	.230	--
3429.1	.00460	.230	--
3530.3	.00490	.245	--
3593.5	.00495	.247	7.8 x 10 ⁻⁹
3689.9	.00500	.250	8.0 x 10 ⁻⁹
3760.5	.00510	.255	8.0 x 10 ⁻⁹
3856.2	.00515	.257	8.2 x 10 ⁻⁹
3928.5	.00525	.262	8.2 x 10 ⁻⁹
4024.1	.00575	.282	8.7 x 10 ⁻⁹
4096.3	.00620	.310	8.2 x 10 ⁻⁹
4192.3	.00640	.320	8.2 x 10 ⁻⁹
4264.1	.00640	.320	8.2 x 10 ⁻⁹
4384.3	.00640	.320	8.4 x 10 ⁻⁹
4432.3	.00640	.320	9.0 x 10 ⁻⁹
4528.3	.00630	.315	8.6 x 10 ⁻⁹
4600.5	.00640	.320	9.4 x 10 ⁻⁹
4696.7	.00625	.312	9.5 x 10 ⁻⁹
4769.2	.00640	.320	8.5 x 10 ⁻⁹
4866.4	.00635	.318	9.2 x 10 ⁻⁹
4936.5	.00630	.315	9.2 x 10 ⁻⁹
5032.5	.00635	.318	9.2 x 10 ⁻⁹
5104.4	.00660	.330	8.4 x 10 ⁻⁹
5200.9	.00660	.330	9.5 x 10 ⁻⁹
5272.3	.00670	.335	8.8 x 10 ⁻⁹
5368.8	.00675	.338	9.4 x 10 ⁻⁹
5440.3	.00685	.342	9.4 x 10 ⁻⁹
5536.2	.00700	.350	1.0 x 10 ⁻⁸
5608.0	.00705	.352	3.4 x 10 ⁻⁹
5705.8	.00715	.358	6.4 x 10 ⁻⁹
5777.0	.00720	.360	4.9 x 10 ⁻⁹
5873.3	.00730	.365	4.9 x 10 ⁻⁹
5945.1	.00745	.372	3.4 x 10 ⁻⁹
6041.2	.00750	.375	2.8 x 10 ⁻⁹
6113.2	.00770	.385	3.4 x 10 ⁻⁹
6209.9	.00770	.385	3.3 x 10 ⁻⁹
6305.5	.00775	.388	3.5 x 10 ⁻⁹
6377.5	.00780	.390	6.3 x 10 ⁻⁹
6449.2	.00775	.388	7.0 x 10 ⁻⁹
6545.7	.00770	.385	8.2 x 10 ⁻⁹
6617.2	.00780	.390	7.4 x 10 ⁻⁹
6713.2	.00780	.390	7.9 x 10 ⁻⁹
6785.3	.00780	.390	7.8 x 10 ⁻⁹
6881.6	.00810	.405	8.0 x 10 ⁻⁹
6953.4	.00790	.395	8.3 x 10 ⁻⁹
7052.7	.00805	.402	8.2 x 10 ⁻⁹
7125.5	.00810	.405	8.1 x 10 ⁻⁹

TABLE I (Continued)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G.L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
7217.2 hours	.00810	.410	8.2×10^{-9}
7386.0	.00815	.408	7.9×10^{-9}
7457.2	.00825	.412	7.5×10^{-9}
7553.3	.00830	.415	7.6×10^{-9}
7625.7	.00835	.418	7.0×10^{-9}
7721.9	.00845	.422	7.0×10^{-9}
7793.6	.00845	.422	7.3×10^{-9}
7889.4	.00850	.425	6.5×10^{-9}
7961.2	.00855	.428	7.1×10^{-9}
8057.4	.00855	.428	7.4×10^{-9}
8129.4	.00860	.430	7.3×10^{-9}
8225.3	.00870	.435	5.2×10^{-9}
8297.5	.00875	.438	4.3×10^{-9}
8393.2	.00880	.440	1.6×10^{-9}
8465.6	.00885	.442	4.8×10^{-9}
8561.4	.00890	.445	4.8×10^{-9}
8633.1	.00895	.448	4.6×10^{-9}
8729.1	.00900	.450	5.3×10^{-9}
8801.3	.00905	.452	5.2×10^{-9}
8969.3	.00915	.458	6.0×10^{-9}
9065.3	.00920	.460	7.5×10^{-9}
9137.2	.00925	.462	9.6×10^{-9}

Test in progress
Specimen B-9

TABLE II

CREEP TEST DATA, TZC PLATE, RECRYSTALLIZED AT 3092°F (1700°C), FOR 1 HOUR,
 TESTED AT 1856°F (1013°C). 25,000 psi (1.72×10^8 N/m²)
HEAT M-80

Time	Length Change ΔL (inch) (2" G.L.)	Creep (%)	Pressure (Torr)
1 minute(s)	-.00005	-.002	
2	.00000	.000	
3	-.00005	-.002	
4	.00005	.002	
5	.00005	.002	
6	.00010	.005	
7	.00005	.002	
8	.00000	.000	
9	.00000	.000	
10	.00005	.002	
15	-.00005	-.002	
20	.00015	.008	
25	.00015	.008	
30	.00025	.012	
60	.00065	.032	
19.3 hours	.00085	.042	1.4×10^{-8}
42.1	.00095	.048	1.3×10^{-8}
68.2	.00095	.048	1.1×10^{-8}
138.4	.00090	.045	5.8×10^{-9}
162.8	.00085	.042	6.6×10^{-9}
186.0	.00085	.042	6.8×10^{-9}
210.3	.00080	.040	5.8×10^{-9}
306.2	.00075	.038	5.2×10^{-9}
330.2	.00090	.045	4.4×10^{-9}
354.2	.00085	.042	3.4×10^{-9}
381.6	.00095	.048	--
402.4	.00095	.048	3.6×10^{-9}
460.7	.00105	.052	2.5×10^{-9}
484.5	.00105	.052	2.8×10^{-9}
508.5	.00125	.062	3.4×10^{-9}
532.4	.00105	.052	3.8×10^{-9}
556.8	.00105	.052	3.2×10^{-9}
628.9	.00105	.052	3.0×10^{-9}
681.7	.00115	.058	--
725.6	.00125	.062	3.1×10^{-9}
796.4	.00130	.065	2.0×10^{-9}
844.8	.00145	.072	2.2×10^{-9}
892.4	.00145	.072	1.6×10^{-9}
964.6	.00140	.070	2.8×10^{-9}

TABLE II (Continued)

<u>Time</u>	<u>Length Change</u> <u>ΔL (inch)</u> <u>(2" G. L.)</u>	<u>Creep</u> <u>%</u>	<u>Pressure</u> <u>(Torr)</u>
1012.6 hours	.00155	.078	2.7×10^{-9}
1060.7	.00170	.085	2.6×10^{-9}
1132.3	.00165	.082	2.4×10^{-9}
1186.9	.00165	.082	2.0×10^{-9}
1228.6	.00170	.085	1.8×10^{-9}
1277.8	.00170	.085	2.2×10^{-9}
1324.4	.00165	.082	2.3×10^{-9}
1349.2	.00175	.088	1.4×10^{-9}
1396.3	.00185	.092	1.8×10^{-9}
1468.3	.00185	.092	2.5×10^{-9}
1516.4	.00180	.090	2.6×10^{-9}
1564.4	.00185	.092	3.1×10^{-9}
1636.4	.00195	.098	2.5×10^{-9}
1689.1	.00205	.102	2.2×10^{-9}
1732.4	.00195	.098	2.8×10^{-9}
1804.3	.00200	.100	2.0×10^{-9}
1876.7	.00215	.108	2.0×10^{-9}
1972.6	.00210	.105	2.3×10^{-9}
2044.4	.00225	.112	9.6×10^{-10}
2164.7	.00225	.112	2.5×10^{-9}
2213.1	.00235	.118	1.4×10^{-9}
2308.3	.00230	.115	1.2×10^{-9}
2380.7	.00235	.118	2.5×10^{-9}
2479.4	.00235	.118	1.2×10^{-9}
2548.4	.00235	.118	2.6×10^{-9}
2647.3	.00245	.122	1.8×10^{-9}
2720.0	.00245	.122	1.1×10^{-9}
2822.6	.00260	.130	9.1×10^{-10}
2886.4	.00305	.152	2.2×10^{-9}
2982.1	.00295	.148	1.6×10^{-9}
3052.8	.00320	.160	1.6×10^{-9}
3148.7	.00315	.158	1.6×10^{-9}
3220.7	.00315	.158	1.6×10^{-9}
3316.4	.00310	.155	1.9×10^{-9}
3388.8	.00315	.158	1.8×10^{-9}
3484.6	.00335	.168	1.6×10^{-9}
3556.4	.00330	.165	1.4×10^{-9}
3676.5	.00335	.168	1.5×10^{-9}
3724.5	.00330	.165	1.9×10^{-9}
3820.7	.00330	.165	1.6×10^{-9}
3892.7	.00320	.160	1.7×10^{-9}
3988.9	.00315	.158	2.8×10^{-9}
4061.4	.00315	.158	1.3×10^{-9}
4158.8	.00300	.150	1.8×10^{-9}
4228.7	.00300	.150	6.0×10^{-10}
4325.1	.00300	.150	1.5×10^{-9}
4396.7	.00315	.158	1.8×10^{-9}
4493.1	.00315	.158	2.0×10^{-9}

TABLE II (Continued)

<u>Time</u>	<u>Length Change L (inch) (2" G. L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
4564.6 hours	.00310	.155	2.0×10^{-9}
4661.2	.00315	.158	1.4×10^{-9}
4732.6	.00320	.160	2.0×10^{-9}
4828.5	.00305	.152	1.7×10^{-9}
4900.3	.00310	.155	1.7×10^{-9}
4998.1	.00305	.152	1.4×10^{-9}
5069.3	.00305	.152	2.4×10^{-9}
5165.5	.00305	.152	1.6×10^{-9}
5237.4	.00310	.155	1.2×10^{-9}
5333.5	.00310	.155	1.1×10^{-9}
5405.5	.00305	.152	1.6×10^{-9}
5502.2	.00305	.152	1.1×10^{-9}
5598.0	.00310	.155	1.4×10^{-9}
5669.8	.00310	.155	1.8×10^{-9}
5741.4	.00320	.160	1.6×10^{-9}
5838.0	.00315	.158	1.6×10^{-9}
5909.4	.00325	.162	1.5×10^{-9}
6005.6	.00315	.158	1.5×10^{-9}
6077.5	.00315	.158	1.6×10^{-9}
6173.9	.00315	.158	1.6×10^{-9}
6245.7	.00320	.160	1.6×10^{-9}
6345.0	.00325	.162	1.0×10^{-9}
6417.7	.00335	.168	1.3×10^{-9}
6509.4	.00335	.168	1.5×10^{-9}
6582.0	.00340	.170	1.0×10^{-9}
6678.2	.00335	.168	1.6×10^{-9}
6749.4	.00340	.170	1.5×10^{-9}
6845.6	.00345	.172	1.6×10^{-9}
6917.9	.00350	.175	2.2×10^{-9}
7014.1	.00355	.178	1.4×10^{-9}
7085.9	.00350	.175	2.1×10^{-9}
7181.9	.00345	.172	2.3×10^{-9}
7253.6	.00355	.178	3.0×10^{-9}
7350.0	.00345	.172	1.4×10^{-9}
7421.6	.00345	.172	1.4×10^{-9}
7517.6	.00345	.172	7.8×10^{-10}
7589.7	.00350	.175	1.8×10^{-9}
7685.4	.00345	.172	1.6×10^{-9}
7757.8	.00340	.170	2.2×10^{-9}
7853.8	.00345	.172	1.8×10^{-9}
7925.4	.00340	.170	1.6×10^{-9}
8021.3	.00340	.170	1.3×10^{-9}
8093.4	.00340	.170	1.6×10^{-9}
8189.3	.00345	.172	1.7×10^{-9}
8261.5	.00345	.172	1.9×10^{-9}
8357.5	.00335	.168	1.1×10^{-9}
8429.5	.00335	.168	1.6×10^{-9}

Test in progress
Specimen B-11

TABLE III

CREEP TEST DATA, TZC PLATE, HEAT M-80, RECRYSTALLIZED AT 3092°F (1700°C), 1 HOUR,
TESTED AT 2056°F (1124°C), 19,000 PSI ($1.31 \times 10^8 \text{ N/m}^2$)

<u>Time</u>	<u>Length Change</u> <u>ΔL (inch)</u> <u>(2" G.L.)</u>	<u>Creep</u> <u>(%)</u>	<u>Pressure</u> <u>(Torr)</u>
1 minutes	.00010	.005	7.0×10^{-8}
2	.00020	.010	
3	.00030	.015	
4	.00050	.025	
5	.00055	.028	
6	.00065	.032	
7	.00085	.042	
8	.00095	.048	
9	.00105	.052	
10	.00120	.060	
12	.00130	.065	
13	.00140	.070	
14	.00150	.075	
15	.00160	.080	6.9×10^{-8}
20	.00165	.082	
25	.00170	.085	
30	.00170	.085	6.9×10^{-8}
40	.00175	.088	
45	.00175	.088	
60	.00180	.090	6.8×10^{-8}
90	.00180	.090	6.7×10^{-8}
15.7 hours	.00180	.090	3.5×10^{-8}
87.1	.00180	.090	1.4×10^{-8}
111.2	.00100	.050	9.8×10^{-9}
133.4	.00140	.070	7.0×10^{-9}
159.0	.00135	.068	3.0×10^{-9}
181.6	.00130	.065	--
239.9	.00135	.068	4.2×10^{-9}
263.7	.00130	.065	5.1×10^{-9}
287.7	.00150	.075	4.5×10^{-9}
309.9	.00140	.070	3.8×10^{-9}
334.3	.00150	.075	3.2×10^{-9}
406.5	.00145	.072	3.5×10^{-9}
459.3	.00155	.078	--
503.2	.00150	.075	2.2×10^{-9}
573.9	.00175	.088	1.2×10^{-9}

TABLE III (Continued)

<u>Time</u>	<u>Length Change</u> <u>ΔL (inch)</u> <u>(2" G. L.)</u>	<u>Creep</u> <u>(%)</u>	<u>Pressure</u> <u>(Torr)</u>
622.5 hours	.00175	.088	1.1×10^{-9}
669.9	.00180	.090	3.8×10^{-9}
742.3	.00185	.092	2.8×10^{-9}
790.2	.00190	.095	2.8×10^{-9}
838.3	.00185	.092	1.8×10^{-9}
909.9	.00195	.098	3.2×10^{-9}
964.8	.00205	.102	2.6×10^{-9}
1006.2	.00210	.105	2.6×10^{-9}
1055.3	.00215	.108	2.7×10^{-9}
1102.0	.00220	.110	2.9×10^{-9}
1126.8	.00220	.110	1.7×10^{-9}
1173.9	.00220	.110	1.0×10^{-9}
1245.9	.00215	.108	4.2×10^{-10}
1294.0	.00225	.112	2.1×10^{-9}
1342.0	.00235	.118	2.1×10^{-10}
1414.1	.00235	.118	1.4×10^{-9}
1466.7	.00235	.118	2.5×10^{-9}
1509.0	.00225	.112	2.0×10^{-9}
1581.8	.00245	.122	7.5×10^{-10}
1654.2	.00245	.122	1.2×10^{-9}
1750.2	.00240	.120	1.3×10^{-9}
1822.1	.00235	.118	7.0×10^{-10}
1942.2	.00235	.118	8.4×10^{-10}
1990.6	.00240	.120	7.4×10^{-10}
2086.2	.00250	.125	1.6×10^{-9}
2158.2	.00260	.130	1.4×10^{-9}
2254.4	.00265	.132	7.2×10^{-10}
2326.1	.00265	.132	2.0×10^{-9}
2424.7	.00280	.140	1.4×10^{-9}
2497.4	.00305	.152	1.2×10^{-9}
2600.1	.00310	.155	8.0×10^{-10}
2664.7	.00325	.162	2.4×10^{-9}
2759.8	.00345	.172	2.6×10^{-9}
2854.3	.00355	.178	1.5×10^{-9}
2926.3	.00355	.178	1.5×10^{-9}
2998.2	.00355	.178	2.1×10^{-9}
3094.0	.00365	.182	2.1×10^{-9}
3166.4	.00360	.180	2.2×10^{-9}
3262.2	.00355	.178	9.2×10^{-9}

TABLE III (Continued)

<u>Time</u>	<u>Length Change</u> <u>ΔL (inch)</u> <u>(2" G. L.)</u>	<u>Creep</u> <u>%</u>	<u>Pressure</u> <u>(Torr)</u>
3334.1 hours	.00360	.180	2.2×10^{-9}
3454.1	.00340	.170	1.6×10^{-9}
3502.1	.00365	.182	2.0×10^{-9}
3598.2	.00315	.158	1.1×10^{-9}
3670.3	.00315	.158	1.0×10^{-9}
3766.6	.00300	.150	9.0×10^{-10}
3839.0	.00305	.152	2.5×10^{-9}
3936.4	.00300	.150	9.1×10^{-10}
4006.3	.00295	.148	2.0×10^{-9}
4102.6	.00305	.152	2.1×10^{-9}
4174.3	.00310	.155	1.9×10^{-9}
4270.6	.00320	.160	1.0×10^{-9}
4342.2	.00330	.165	2.0×10^{-9}
4438.7	.00330	.165	2.5×10^{-9}
4510.1	.00355	.178	1.4×10^{-9}
4606.2	.00340	.170	2.0×10^{-9}
4677.8	.00345	.172	1.8×10^{-9}
4775.6	.00345	.172	1.8×10^{-9}
4846.8	.00335	.168	1.6×10^{-9}
4943.1	.00335	.168	1.6×10^{-9}
5015.0	.00355	.178	1.7×10^{-9}
5111.1	.00340	.170	1.6×10^{-9}
5183.2	.00345	.172	1.0×10^{-9}
5279.7	.00350	.175	1.6×10^{-9}
5375.6	.00355	.178	1.5×10^{-9}
5447.3	.00355	.178	2.5×10^{-9}
5518.9	.00355	.178	2.5×10^{-9}
5615.6	.00355	.178	1.0×10^{-9}
5687.0	.00360	.180	2.5×10^{-9}
5783.8	.00355	.178	2.4×10^{-9}
5855.1	.00365	.182	2.4×10^{-9}
5951.5	.00375	.188	2.4×10^{-9}
6023.3	.00380	.190	2.5×10^{-9}
6122.5	.00395	.198	9.0×10^{-10}
6195.3	.00390	.195	2.4×10^{-9}
6286.9	.00400	.200	2.5×10^{-9}

TABLE III (Continued)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G.L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
6359.5 hours	.00405	.202	1.0 x 10 ⁻⁹
6455.8	.00410	.205	1.7 x 10 ⁻⁹
6527.0	.00415	.208	2.5 x 10 ⁻⁹
6623.2	.00410	.205	1.6 x 10 ⁻⁹
6695.6	.00410	.205	2.3 x 10 ⁻⁹
6791.8	.00420	.210	1.6 x 10 ⁻⁹
6864.8	.00420	.210	1.6 x 10 ⁻⁹
6959.5	.00415	.208	1.4 x 10 ⁻⁹
7031.2	.00420	.210	2.4 x 10 ⁻⁹
7127.6	.00435	.218	1.0 x 10 ⁻⁹
7199.2	.00430	.215	2.2 x 10 ⁻⁹
7295.2	.00430	.215	7.2 x 10 ⁻¹⁰
7367.3	.00430	.215	1.1 x 10 ⁻⁹
7463.2	.00425	.212	1.0 x 10 ⁻⁹
7535.5	.00430	.215	1.6 x 10 ⁻⁹
7631.3	.00440	.220	1.6 x 10 ⁻⁹
7702.9	.00440	.220	1.6 x 10 ⁻⁹
7798.9	.00440	.220	1.5 x 10 ⁻⁹
7870.9	.00440	.220	1.7 x 10 ⁻⁹
7966.8	.00445	.222	1.6 x 10 ⁻⁹
8039.1	.00440	.220	1.6 x 10 ⁻⁹
8135.2	.00450	.225	1.4 x 10 ⁻⁹
8207.0	.00455	.228	1.4 x 10 ⁻⁹

Test in progress
Specimen B-12

TABLE IV

CREEP TEST DATA, TZC PLATE, HEAT M-91, ANNEALED 2300°F (1260°C) 1 HOUR,

TESTED 1800°F (982°C), 44,000 PSI ($3.03 \times 10^8 \text{ N/m}^2$)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G.L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
1 Minutes	-.00010	-.005	3.2×10^{-8}
2	-.00020	-.010	3.2×10^{-8}
4	-.00025	-.012	3.2×10^{-8}
5	-.00025	-.012	3.2×10^{-8}
6	-.00030	-.015	3.2×10^{-8}
7	-.00015	-.008	3.2×10^{-8}
8	-.00015	-.008	3.2×10^{-8}
9	-.00015	-.008	3.2×10^{-8}
10	-.00015	-.008	3.2×10^{-8}
15	-.00020	-.010	3.2×10^{-8}
30	-.00015	-.008	3.2×10^{-8}
45	-.00010	-.005	3.2×10^{-8}
60	-.00010	-.005	3.2×10^{-8}
67.3 Hours	.00270	.135	1.1×10^{-8}
91.1	.00305	.152	1.0×10^{-8}
114.9	.00385	.192	1.1×10^{-8}
139.7	.00380	.190	1.0×10^{-8}
162.8	.00405	.202	9.6×10^{-9}
237.1	.00515	.258	9.0×10^{-9}
258.7	.00530	.265	8.2×10^{-9}
282.6	.00550	.275	3.6×10^{-9}
307.0	.00560	.280	3.2×10^{-9}
331.2	.00600	.300	3.1×10^{-9}
403.4	.00675	.338	3.7×10^{-9}
426.7	.00645	.322	3.4×10^{-9}
450.9	.00665	.332	2.6×10^{-9}
475.0	.00715	.358	2.4×10^{-9}
498.9	.00775	.388	3.4×10^{-9}
571.4	.00745	.372	3.0×10^{-9}
595.3	.00745	.372	2.8×10^{-9}
619.1	.00820	.410	2.8×10^{-9}
642.9	.00795	.398	2.8×10^{-9}
667.0	.00765	.382	2.8×10^{-9}
739.5	.00840	.420	3.0×10^{-9}
763.1	.00845	.422	2.5×10^{-9}
788.4	.00875	.438	2.2×10^{-9}
810.9	.00890	.445	2.4×10^{-9}
835.1	.00880	.440	2.3×10^{-9}

TABLE IV (Continued)

Time	Length Change L (inch) (2" G.L.)	Creep (%)	Pressure (Torr)
906.9	.00890	.445	2.3×10^{-9}
978.6	.00965	.482	2.2×10^{-9}
1076.4	.01005	.502	2.2×10^{-9}
1147.6	.01020	.510	4.8×10^{-9}
1243.8	.01045	.522	4.4×10^{-9}
1315.7	.01065	.532	4.3×10^{-9}
1411.9	.01100	.550	4.4×10^{-9}
1580.5	.01170	.585	2.7×10^{-9}
1676.3	.01205	.602	4.0×10^{-9}
1748.1	.01220	.610	4.2×10^{-9}
1819.7	.01255	.628	2.8×10^{-9}
1916.3	.01285	.642	3.2×10^{-9}
1987.7	.01310	.655	2.0×10^{-9}
2084.2	.01345	.672	3.2×10^{-9}
2155.8	.01365	.682	2.4×10^{-9}
2252.2	.01375	.688	3.1×10^{-9}
2324.0	.01405	.702	2.3×10^{-9}
2423.3	.01455	.728	2.0×10^{-9}
2496.0	.01465	.732	1.9×10^{-9}
2587.7	.01495	.748	2.6×10^{-9}
2660.3	.01505	.752	1.9×10^{-9}
2756.5	.01515	.758	2.5×10^{-9}
2827.7	.01525	.762	2.0×10^{-9}
2923.9	.01590	.795	3.4×10^{-9}
2996.4	.01610	.805	5.4×10^{-9}
3092.4	.01640	.820	1.9×10^{-9}
3164.2	.01640	.820	2.4×10^{-9}
3260.2	.01665	.832	4.8×10^{-9}
3331.9	.01690	.845	2.2×10^{-9}
3428.4	.01705	.852	2.6×10^{-9}
3500.0	.01730	.865	1.8×10^{-9}
3595.9	.01745	.872	1.3×10^{-9}
3668.0	.01770	.885	2.4×10^{-9}
3763.9	.01795	.898	2.6×10^{-9}
3836.2	.01820	.910	3.4×10^{-9}
3932.0	.01845	.922	3.5×10^{-9}
4003.7	.01865	.932	3.5×10^{-9}
4099.6	.01875	.938	3.4×10^{-9}
4172.0	.01885	.942	3.6×10^{-9}
4267.6	.01925	.962	3.6×10^{-9}
4339.9	.01950	.975	3.7×10^{-9}
4435.9	.01960	.980	3.3×10^{-9}
4507.8	.01975	.988	3.2×10^{-9}
4603.6	.02030	1.015	3.3×10^{-9}

Test Terminated - 1% Creep

Specimen B-19

TABLE V

CREEP TEST DATA, TZC PLATE, HEAT M-91, ANNEALED AT 3092°F (1700°C) FOR 1 HOUR,
TESTED AT 2000°F (1093°C), 20,000 PSI ($1.38 \times 10^8 \text{ N/m}^2$)

<u>Time</u>	<u>Length Change</u> <u>ΔL (inch)</u> <u>(2" G.L.)</u>	<u>Creep</u> <u>(%)</u>	<u>Pressure</u> <u>(Torr)</u>
1 Minutes	.00000	.000	8.2×10^{-9}
2	.00005	.002	8.2×10^{-9}
3	.00010	.005	8.2×10^{-9}
4	.00010	.005	8.2×10^{-9}
5	.00015	.008	8.2×10^{-9}
6	.00020	.010	8.2×10^{-9}
7	.00020	.010	8.2×10^{-9}
8	.00020	.010	8.2×10^{-9}
9	.00015	.008	8.2×10^{-9}
10	.00020	.010	8.2×10^{-9}
15	.00025	.012	8.2×10^{-9}
20	.00020	.010	8.2×10^{-9}
25	.00025	.012	8.2×10^{-9}
30	.00025	.012	8.2×10^{-9}
60	.00020	.010	8.2×10^{-9}
1.7 Hours	.00030	.015	8.2×10^{-9}
19.0	.00075	.038	8.4×10^{-9}
43.9	.00100	.050	7.2×10^{-9}
115.2	.00155	.078	4.0×10^{-9}
139.2	.00185	.092	3.2×10^{-9}
163.6	.00210	.105	2.6×10^{-9}
187.1	.00220	.110	2.4×10^{-9}
211.4	.00240	.120	2.1×10^{-9}
283.2	.00270	.135	1.4×10^{-9}
307.3	.00290	.145	1.2×10^{-9}
331.2	.00300	.150	1.1×10^{-9}
355.2	.00295	.148	9.7×10^{-10}
379.3	.00295	.148	9.6×10^{-10}
451.9	.00310	.155	7.9×10^{-10}
499.6	.00350	.175	6.7×10^{-10}
547.7	.00355	.178	6.1×10^{-10}
619.5	.00360	.180	9.2×10^{-10}
643.4	.00365	.182	6.3×10^{-10}
667.4	.00365	.182	8.1×10^{-10}
691.1	.00365	.182	8.2×10^{-10}
715.5	.00375	.188	7.8×10^{-10}

TABLE V (Continued)

<u>Time</u>	<u>Length Change</u> <u>L (inch)</u> <u>(2" G.L.)</u>	<u>Creep</u> <u>(%)</u>	<u>Pressure</u> <u>(Torr)</u>
787.7 Hours	.00410	.205	7.4×10^{-10}
811.6	.00420	.210	7.1×10^{-10}
835.3	.00435	.218	7.2×10^{-10}
859.2	.00440	.220	7.0×10^{-10}
883.2	.00445	.222	7.0×10^{-10}
956.3	.00460	.230	6.6×10^{-10}
980.0	.00470	.235	6.4×10^{-10}
1003.4	.00455	.228	6.4×10^{-10}
1027.2	.00465	.232	6.2×10^{-10}
1123.7	.00485	.242	6.0×10^{-10}
1195.5	.00490	.245	5.7×10^{-10}
1294.7	.00515	.258	6.0×10^{-10}
1367.4	.00525	.262	5.8×10^{-10}
1459.1	.00560	.280	5.6×10^{-10}
1531.7	.00585	.292	5.4×10^{-10}
1627.9	.00600	.300	5.4×10^{-10}
1699.2	.00620	.310	5.4×10^{-10}
1795.3	.00640	.320	5.4×10^{-10}
1867.8	.00655	.328	5.1×10^{-10}
1963.9	.00665	.332	5.1×10^{-10}
2035.6	.00695	.348	4.7×10^{-10}
2131.6	.00720	.360	4.8×10^{-10}
2203.3	.00740	.370	4.9×10^{-10}
2299.8	.00745	.372	4.9×10^{-10}
2371.4	.00755	.378	4.8×10^{-10}
2467.3	.00760	.380	3.6×10^{-10}
2539.5	.00770	.385	2.6×10^{-10}
2635.2	.00800	.400	3.8×10^{-10}
2707.6	.00820	.410	3.4×10^{-10}
2803.4	.00880	.440	3.4×10^{-10}
2875.1	.00900	.450	3.4×10^{-10}
2971.0	.00910	.455	3.1×10^{-10}
3043.1	.00920	.460	3.6×10^{-10}
3139.0	.00935	.468	3.3×10^{-10}
3211.3	.00930	.465	3.4×10^{-10}
3307.3	.00960	.480	3.3×10^{-10}
3379.2	.00965	.482	3.2×10^{-10}

Test in progress

Specimen B-20

TABLE VI

CREEP TEST DATA, TZC PLATE, HEAT M-91, ANNEALED AT 3092°F (1700°C) FOR 1 HOUR

AGED AT 2400°F (1316°C) FOR 5 HOURS

TESTED AT 2000°F (1093°C) 20,000 PSI ($1.38 \times 10^8 \text{ N/m}^2$)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G.L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
1 Minutes	-.00010	-.005	6.0×10^{-9}
2	.00000	.000	6.0×10^{-9}
3	.00000	.000	6.0×10^{-9}
4	.00000	.000	6.0×10^{-9}
5	.00000	.000	6.0×10^{-9}
6	.00005	.002	6.0×10^{-9}
7	.00005	.002	6.0×10^{-9}
8	.00000	.000	6.0×10^{-9}
9	.00000	.000	6.0×10^{-9}
10	-.00005	-.002	6.0×10^{-9}
15	.00000	.000	6.0×10^{-9}
30	.00020	.010	6.0×10^{-9}
45	.00040	.020	6.0×10^{-9}
60	.00040	.020	6.0×10^{-9}
2 Hours	.00085	.042	6.0×10^{-9}
3	.00120	.060	6.0×10^{-9}
19.2	.00295	.148	6.0×10^{-9}
91.2	.00640	.320	3.4×10^{-9}
115.4	.00715	.358	2.6×10^{-9}
139.3	.00800	.400	2.5×10^{-9}
163.3	.00840	.420	2.4×10^{-9}
187.3	.00855	.428	2.4×10^{-9}
259.6	.01020	.510	1.9×10^{-9}
283.3	.01050	.525	1.7×10^{-9}
307.3	.01070	.535	1.8×10^{-9}
331.4	.01110	.555	1.8×10^{-9}
430.7	.01245	.622	1.8×10^{-9}
503.5	.01345	.672	1.7×10^{-9}
595.2	.01465	.732	1.4×10^{-9}

TABLE VI (Continued)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G.L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
619.6 hours	.01490	.745	1.4×10^{-9}
643.4	.01520	.760	1.4×10^{-9}
667.8	.01530	.765	1.4×10^{-9}
691.3	.01570	.785	1.3×10^{-9}
764.0	.01680	.840	1.3×10^{-9}
811.4	.01725	.862	1.3×10^{-9}
835.2	.01735	.868	1.3×10^{-9}
859.4	.01760	.880	1.3×10^{-9}
931.3	.01815	.908	1.1×10^{-9}
955.2	.01825	.912	1.3×10^{-9}
979.3	.01850	.925	1.1×10^{-9}
1003.7	.01885	.942	1.1×10^{-9}
1027.6	.01900	.950	1.1×10^{-9}
1102.2	.02000	1.000	1.0×10^{-9}
1123.4	.02020	1.010	1.1×10^{-9}

Test Terminated - 1% Creep
Specimen B-22

TABLE VII

CREEP TEST DATA, STRESS-RELIEVED TZM FORGED DISC, CLIMAX HEAT NO. 7502

TESTED AT 2000°F (1093°C), 10,000 PSI ($6.89 \times 10^7 \text{N/m}^2$)

<u>Time</u>	<u>Length Change Δ L (inch) (2" G. L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
1 minutes	-.00030	-.015	1.6×10^{-7}
2	-.00015	-.008	
3	-.00015	-.008	
4	-.00015	-.008	
5	-.00005	-.002	
6	.00010	.005	
7	.00005	.002	
8	.00000	.000	
9	.00010	.005	
10	.00005	.002	
15	.00005	.002	
20	.00010	.005	
25	.00005	.002	
30	.00000	.000	
45	.00010	.005	
60	.00015	.008	
75	.00005	.002	
90	.00010	.005	
20.0 hours	-.00005	-.002	6.7×10^{-8}
74.7	.00030	.015	1.0×10^{-8}
125.7	.00100	.050	1.4×10^{-8}
136.5	.00800	.040	1.0×10^{-8}
160.3	.00085	.042	5.7×10^{-9}
184.4	.00085	.042	4.4×10^{-9}
208.5	.00090	.045	4.0×10^{-9}
232.2	.00090	.045	3.4×10^{-9}
304.4	.00100	.050	2.2×10^{-9}
328.3	.00100	.050	2.0×10^{-9}
352.2	.00105	.052	1.9×10^{-9}
376.6	.00105	.052	1.3×10^{-9}
400.8	.00110	.055	2.1×10^{-9}
457.5	.00130	.065	1.3×10^{-9}
472.6	.00135	.068	1.2×10^{-9}
497.0	.00140	.070	1.2×10^{-9}

Table VII (continued)

<u>Time</u>	<u>Length Change Δ L (inch) (2" G. L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
520.2 hours	.00145	.072	1.2×10^{-9}
544.1	.00145	.072	1.2×10^{-9}
568.2	.00150	.075	1.2×10^{-9}
640.2	.00155	.078	1.5×10^{-9}
664.3	.00170	.085	9.2×10^{-10}
688.6	.00175	.088	6.0×10^{-10}
712.3	.00175	.088	7.4×10^{-10}
736.3	.00170	.085	7.6×10^{-10}
810.2	.00175	.088	1.3×10^{-9}
832.2	.00185	.092	9.0×10^{-10}
856.1	.00180	.090	9.2×10^{-10}
880.1	.00200	.100	7.5×10^{-10}
904.0	.00205	.102	7.7×10^{-10}
982.8	.00210	.105	8.1×10^{-10}
1000.2	.00210	.105	7.6×10^{-10}
1024.2	.00210	.105	8.2×10^{-10}
1048.3	.00220	.110	8.0×10^{-10}
1072.1	.00220	.110	1.3×10^{-9}
1144.0	.00230	.115	6.9×10^{-10}
1168.3	.00235	.118	6.9×10^{-10}
1192.2	.00240	.120	6.6×10^{-10}
1216.4	.00250	.125	6.4×10^{-10}
1240.2	.00250	.125	5.8×10^{-10}
1336.2	.00250	.125	5.9×10^{-9}
1360.3	.00250	.125	5.8×10^{-10}
1384.3	.00250	.125	5.2×10^{-10}
1408.5	.00250	.125	4.4×10^{-10}
1480.3	.00260	.130	4.6×10^{-10}
1552.2	.00270	.135	4.6×10^{-10}
1648.3	.00320	.160	4.0×10^{-10}
1696.4	.00320	.160	3.8×10^{-10}
1720.6	.00320	.160	4.4×10^{-10}
1816.4	.00320	.160	5.7×10^{-10}
1864.2	.00315	.158	3.8×10^{-10}
1912.3	.00325	.162	4.0×10^{-10}
1984.3	.00330	.165	2.6×10^{-10}
2032.2	.00335	.168	3.6×10^{-10}
2080.1	.00340	.170	3.1×10^{-10}
2152.3	.00340	.170	2.8×10^{-10}

Table VII (continued)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G. L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
2200.6 hours	.00335	.168	2.3×10^{-10}
2248.4	.00340	.170	1.6×10^{-10}
2320.4	.00350	.175	2.7×10^{-10}
2369.4	.00345	.172	2.0×10^{-10}
2418.3	.00355	.178	9.2×10^{-11}
2488.4	.00345	.172	4.0×10^{-10}
2536.1	.00350	.175	1.7×10^{-10}
2560.3	.00345	.172	2.6×10^{-10}
2656.3	.00355	.178	2.6×10^{-10}
2704.3	.00350	.175	--
2752.4	.00350	.175	--
2823.5	.00355	.178	2.5×10^{-10}
2871.3	.00365	.182	1.1×10^{-11}
2919.5	.00375	.188	1.7×10^{-10}
2991.7	.00380	.190	7.2×10^{-11}
3044.5	.00380	.190	--
3088.4	.00380	.190	1.8×10^{-11}
3159.2	.00385	.192	1.6×10^{-11}
3231.2	.00390	.195	1.4×10^{-10}
3327.5	.00385	.192	1.2×10^{-10}
3399.4	.00395	.198	2.0×10^{-11}
3495.1	.00400	.200	8.2×10^{-12}
3568.1	.00400	.200	9.5×10^{-11}
3640.6	.00410	.205	3.4×10^{-11}
3687.2	.00410	.205	1.9×10^{-11}
3735.3	.00415	.208	1.0×10^{-11}
3831.1	.00420	.210	1.2×10^{-11}
3903.5	.00425	.212	2.1×10^{-11}
3999.2	.00440	.220	1.0×10^{-11}
4071.3	.00450	.225	2.1×10^{-11}
4167.1	.00450	.225	1.8×10^{-10}
4239.4	.00465	.232	1.8×10^{-11}
4335.4	.00460	.230	1.8×10^{-10}
4407.3	.00465	.232	1.0×10^{-11}
4527.5	.00465	.232	1.2×10^{-11}
4575.9	.00475	.238	1.0×10^{-11}

TABLE VII (Continued)

<u>Time</u>	<u>Length Change</u> <u>ΔL (inch)</u> <u>(2" G. L.)</u>	<u>Creep</u> <u>%</u>	<u>Pressure</u> <u>(Torr)</u>
4671.2 hours	.00470	.235	7.5×10^{-11}
4743.5	.00475	.238	1.0×10^{-11}
4839.7	.00470	.235	1.8×10^{-11}
4911.3	.00470	.235	1.0×10^{-11}
5010.3	.00475	.238	8.5×10^{-11}
5084.1	.00475	.238	1.8×10^{-10}
5185.4	.00485	.242	3.4×10^{-10}
5249.1	.00490	.245	9.3×10^{-10}
5344.9	.00480	.240	4.2×10^{-10}
5415.6	.00500	.250	4.2×10^{-10}
5511.5	.00505	.252	1.1×10^{-9}
5583.5	.00500	.250	1.3×10^{-9}
5679.3	.00500	.250	1.7×10^{-9}
5751.4	.00510	.255	1.7×10^{-9}
5847.5	.00515	.258	4.4×10^{-9}
5919.3	.00520	.260	2.0×10^{-9}
6039.4	.00530	.265	2.0×10^{-9}
6087.4	.00540	.270	1.8×10^{-9}
6183.4	.00545	.272	4.3×10^{-10}
6255.6	.00550	.275	4.5×10^{-10}
6351.8	.00550	.275	2.0×10^{-9}
6424.3	.00555	.278	2.4×10^{-9}
6521.5	.00560	.280	2.0×10^{-9}
6591.6	.00550	.275	2.5×10^{-9}
6687.5	.00555	.278	3.0×10^{-9}
6759.6	.00565	.282	3.7×10^{-9}
6855.9	.00570	.285	4.2×10^{-10}
6927.5	.00580	.290	3.8×10^{-10}
7024.0	.00585	.292	4.1×10^{-10}
7095.4	.00590	.295	2.5×10^{-10}
7191.3	.00595	.298	4.5×10^{-10}
7263.1	.00595	.298	3.0×10^{-10}
7360.9	.00595	.298	5.2×10^{-10}
7432.1	.00605	.302	9.4×10^{-10}
7528.3	.00600	.300	8.8×10^{-10}
7600.2	.00605	.302	9.3×10^{-10}
7696.3	.00610	.305	9.7×10^{-10}
7768.3	.00605	.302	1.0×10^{-9}
7865.0	.00615	.308	5.0×10^{-10}
7960.5	.00620	.310	1.2×10^{-9}
8032.6	.00620	.310	9.0×10^{-10}
8104.2	.00630	.315	8.6×10^{-10}

TABLE VII (Continued)

<u>Time</u>	<u>Length Change</u> <u>L (Inch)</u> <u>(2" G. L.)</u>	<u>Creep</u> <u>%</u>	<u>Pressure</u> <u>(Torr)</u>
8200.8 hours	.00635	.318	1.1×10^{-9}
8272.3	.00640	.320	1.1×10^{-9}
8368.3	.00650	.325	1.0×10^{-9}
8440.3	.00640	.320	1.2×10^{-9}
8536.7	.00655	.328	1.5×10^{-9}
8608.5	.00665	.332	1.6×10^{-9}
8707.8	.00665	.332	1.2×10^{-9}
8780.5	.00665	.332	1.6×10^{-9}
8872.2	.00675	.338	1.2×10^{-9}
8944.8	.00680	.340	1.6×10^{-9}
9041.1	.00700	.350	1.3×10^{-9}
9112.2	.00705	.352	1.2×10^{-9}
9208.4	.00705	.352	1.4×10^{-9}
9280.8	.00700	.350	1.5×10^{-9}
9377.0	.00715	.358	1.4×10^{-9}
9448.7	.00725	.362	1.4×10^{-9}
9544.6	.00730	.365	1.5×10^{-9}
9616.3	.00740	.370	1.7×10^{-9}
9712.5	.00745	.372	1.4×10^{-9}
9784.5	.00745	.372	1.6×10^{-9}
9880.4	.00745	.372	1.3×10^{-9}
9952.6	.00745	.372	1.8×10^{-9}
10,048.3	.00750	.375	1.7×10^{-9}

Test Terminated - 10,000 Hours

Specimen B-3

TABLE VIII

CREEP TEST DATA, TZM FORGED DISC, CLIMAX NO. 7502, ANNEALED AT 2850°F (1566°C)

FOR 1 HOUR AT 2000°F (1093°C), 10,000 PSI ($6.89 \times 10^7 \text{N/m}^2$)

Time	Length Change ΔL (inch) (2" G.L.)	Creep (%)	Pressure (Torr)
1 minute(s)	.00030	.015	
2	.00045	.022	
3	.00040	.020	
4	.00030	.015	
5	.00025	.012	
6	.00015	.008	
7	.00015	.008	
8	.00010	.005	
9	.00020	.010	
10	.00030	.015	
11	.00030	.015	
12	.00025	.012	
13	.00030	.015	
14	.00030	.015	
15	.00035	.018	
20	.00045	.022	
25	.00050	.025	
30	.00055	.028	
35	.00050	.025	
40	.00050	.025	
45	.00050	.025	
60	.00050	.025	
16.6 hours	.00040	.020	6.2×10^{-9}
40.7	.00055	.028	3.1×10^{-9}
114.5	.00095	.048	5.1×10^{-9}
136.5	.00105	.052	3.0×10^{-9}
160.4	.00120	.060	3.4×10^{-9}
184.4	.00130	.065	2.4×10^{-9}
208.3	.00140	.070	2.3×10^{-9}
287.5	.00180	.090	2.2×10^{-9}
304.7	.00235	.118	1.8×10^{-9}
328.7	.00505	.252	1.6×10^{-9}
336.5	.00485	.242	--
352.6	.00515	.258	1.6×10^{-9}
376.4	.00525	.262	2.2×10^{-9}
448.3	.00525	.262	1.4×10^{-9}
472.7	.00525	.262	1.0×10^{-9}
496.6	.00530	.265	1.0×10^{-9}

TABLE VIII (Continued)

Time	Length Change ΔL (inch) (2" G.L.)	Creep (%)	Pressure (Torr)
520.8 hours	.00535	.268	1.6×10^{-9}
544.6	.00565	.282	1.2×10^{-9}
616.6	.00560	.280	6.2×10^{-10}
640.5	.00555	.278	7.2×10^{-10}
664.6	.00560	.280	7.2×10^{-10}
688.7	.00560	.280	7.3×10^{-10}
712.8	.00565	.282	1.3×10^{-9}
784.6	.00560	.280	5.6×10^{-10}
808.7	.00555	.278	5.5×10^{-10}
832.6	.00565	.282	5.8×10^{-10}
856.6	.00575	.288	5.8×10^{-10}
880.6	.00580	.290	6.6×10^{-10}
952.6	.00480	.240	4.3×10^{-10}
977.0	.00485	.242	1.4×10^{-9}
1000.7	.00485	.242	4.2×10^{-10}
1025.0	.00505	.252	7.2×10^{-10}
1049.3	.00440	.220	4.6×10^{-10}
1120.8	.00465	.232	3.2×10^{-10}
1145.2	.00485	.242	4.3×10^{-10}
1168.5	.00505	.252	5.0×10^{-10}
1192.7	.00515	.258	8.0×10^{-10}
1216.6	.00515	.258	3.0×10^{-10}
1288.6	.00510	.255	1.6×10^{-10}
1315.5	.00525	.262	2.2×10^{-10}
1336.5	.00525	.262	1.5×10^{-10}
1360.7	.00520	.260	1.6×10^{-10}
1384.5	.00525	.262	2.1×10^{-10}
1456.6	.00540	.270	4.4×10^{-10}
1480.9	.00520	.260	1.6×10^{-9}
1505.0	.00505	.252	9.7×10^{-11}
1528.5	.00510	.255	1.3×10^{-9}
1552.8	.00520	.260	1.3×10^{-9}
1649.0	.00530	.265	9.3×10^{-10}
1696.6	.00535	.268	--
1722.7	.00530	.265	--
1792.8	.00530	.265	3.2×10^{-12}
1840.7	.00530	.265	8.8×10^{-11}
1864.8	.00530	.265	1.2×10^{-9}

TABLE VIII (Continued)

<u>Time</u>	<u>Length Change</u> <u>ΔL (inch)</u> <u>(2" G.L.)</u>	<u>Creep</u> <u>(%)</u>	<u>Pressure</u> <u>(Torr)</u>
1960.8 hours	.00540	.270	9.6×10^{-10}
1984.8	.00545	.272	3.6×10^{-10}
2008.6	.00545	.272	1.5×10^{-9}
2056.9	.00550	.275	--
2115.2	.00555	.278	3.2×10^{-10}
2163.0	.00550	.275	8.0×10^{-10}
2211.2	.00545	.272	1.4×10^{-9}
2283.4	.00560	.280	1.1×10^{-9}
2336.3	.00560	.280	--
2380.1	.00550	.275	1.4×10^{-11}
2450.9	.00555	.278	1.4×10^{-11}
2523.0	.00570	.285	1.0×10^{-9}
2619.2	.00570	.285	8.6×10^{-10}
2691.0	.00610	.305	--
2786.8	.00635	.318	2.5×10^{-10}
2859.8	.00640	.320	8.8×10^{-11}
2932.3	.00640	.320	1.4×10^{-10}
2978.9	.00640	.320	2.2×10^{-10}
3027.0	.00580	.290	1.2×10^{-10}
3122.9	.00630	.315	2.6×10^{-10}
3195.2	.00605	.302	2.8×10^{-10}
3291.1	.00640	.320	3.5×10^{-11}
3363.0	.00650	.325	1.2×10^{-9}
3458.8	.00645	.322	2.4×10^{-10}
3531.2	.00655	.328	9.2×10^{-10}
3627.1	.00640	.320	2.4×10^{-11}
3699.0	.00655	.328	4.2×10^{-10}
3819.2	.00630	.315	5.6×10^{-10}
3891.0	.00620	.310	6.6×10^{-10}
3963.1	.00640	.320	4.3×10^{-11}
4035.2	.00640	.320	1.0×10^{-11}
4131.4	.00670	.335	8.4×10^{-10}
4203.0	.00685	.342	1.9×10^{-11}
4301.7	.00690	.345	3.0×10^{-10}
4374.3	.00680	.340	1.7×10^{-10}
4477.1	.00700	.350	2.0×10^{-10}
4541.4	.00700	.350	2.3×10^{-9}
4636.7	.00700	.350	2.4×10^{-9}
4707.2	.00700	.350	2.6×10^{-9}

TABLE VIII (Continued)

<u>Time</u>	<u>Length Change</u> <u>ΔL (inch)</u> <u>(2" G. L.)</u>	<u>Creep</u> <u>%</u>	<u>Pressure</u> <u>(Torr)</u>
4803.3 hours	.00705	.352	1.2×10^{-9}
4875.2	.00705	.352	3.1×10^{-9}
4970.9	.00710	.355	1.7×10^{-9}
5043.3	.00715	.358	3.0×10^{-9}
5139.1	.00690	.345	2.6×10^{-9}
5210.0	.00730	.365	2.6×10^{-9}
5331.1	.00725	.362	3.4×10^{-9}
5379.1	.00720	.360	2.1×10^{-9}
5475.2	.00720	.360	2.0×10^{-9}
5547.3	.00720	.360	2.1×10^{-9}
5643.5	.00730	.365	1.9×10^{-9}
5715.9	.00730	.365	2.3×10^{-9}
5813.3	.00720	.360	2.0×10^{-9}
5883.2	.00725	.362	1.9×10^{-9}
5979.6	.00720	.360	3.2×10^{-9}
6051.2	.00725	.362	1.9×10^{-9}
6147.6	.00715	.358	2.6×10^{-9}
6219.2	.00730	.365	2.6×10^{-9}
6315.7	.00725	.362	4.4×10^{-9}
6387.1	.00740	.370	2.6×10^{-9}
6483.1	.00730	.365	2.6×10^{-9}
6554.8	.00730	.365	5.0×10^{-9}
6652.6	.00735	.368	5.4×10^{-9}
6723.8	.00725	.362	3.2×10^{-9}
6820.1	.00720	.360	3.2×10^{-9}
6891.9	.00730	.365	3.2×10^{-9}
6988.1	.00735	.368	3.4×10^{-9}
7060.2	.00730	.365	3.2×10^{-9}
7156.7	.00730	.365	3.8×10^{-9}
7252.5	.00720	.360	3.5×10^{-9}
7324.3	.00730	.365	5.8×10^{-9}
7395.9	.00720	.360	4.0×10^{-9}
7492.5	.00735	.368	4.8×10^{-9}
7564.0	.00730	.365	5.0×10^{-9}
7660.8	.00710	.355	3.7×10^{-9}
7732.1	.00710	.355	3.8×10^{-9}
7828.5	.00700	.350	3.7×10^{-9}
7900.2	.00700	.350	4.0×10^{-9}
7999.5	.00710	.355	4.9×10^{-9}
8072.2	.00730	.365	3.7×10^{-9}
8163.9	.00720	.360	3.8×10^{-9}

TABLE VIII (Continued)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G.L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
8236.5 hours	.00730	.365	4.7 x 10 ⁻⁹
8332.8	.00720	.360	3.7 x 10 ⁻⁹
8404.0	.00720	.360	3.9 x 10 ⁻⁹
8500.1	.00710	.355	4.0 x 10 ⁻⁹
8572.6	.00725	.362	4.9 x 10 ⁻⁹
8668.7	.00730	.365	3.7 x 10 ⁻⁹
8740.6	.00720	.360	3.8 x 10 ⁻⁹
8836.4	.00735	.368	3.8 x 10 ⁻⁹
8908.1	.00720	.360	4.0 x 10 ⁻⁹
9004.6	.00715	.358	4.0 x 10 ⁻⁹
9076.2	.00720	.360	3.9 x 10 ⁻⁹
9172.1	.00715	.358	3.6 x 10 ⁻⁹
9244.3	.00730	.365	1.1 x 10 ⁻⁹
9304.1	.00725	.362	1.3 x 10 ⁻⁹
9412.4	.00730	.365	3.8 x 10 ⁻⁹
9508.2	.00735	.368	4.0 x 10 ⁻⁹
9579.9	.00735	.368	4.0 x 10 ⁻⁹
9675.9	.00720	.360	4.1 x 10 ⁻⁹
9747.9	.00730	.365	4.2 x 10 ⁻⁹
9843.8	.00710	.355	4.0 x 10 ⁻⁹
9916.1	.00735	.368	2.0 x 10 ⁻⁹
10,012.1	.00735	.368	2.4 x 10 ⁻⁹

Test Terminated - 10,000 Hours

Specimen B-4

TABLE IX

CREEP TEST DATA, TZM FORGED DISC, HEAT NO. 1175, TESTED AT 1600°F (871°C)

65,000 PSI ($4.48 \times 10^8 \text{ N/m}^2$)

Time	Length Change ΔL (inch) (2" G.L.)	Creep (%)	Pressure (Torr)
1 Minutes	.00005	.002	5.3×10^{-8}
2	-.00005	-.002	5.3×10^{-8}
3	.00005	.002	5.3×10^{-8}
4	.00010	.005	5.3×10^{-8}
5	.00015	.008	5.3×10^{-8}
6	.00015	.008	5.3×10^{-8}
7	.00020	.010	5.3×10^{-8}
8	.00025	.012	5.3×10^{-8}
9	.00020	.010	5.3×10^{-8}
10	.00025	.012	5.3×10^{-8}
15	.00025	.012	5.3×10^{-8}
20	.00030	.015	5.3×10^{-8}
25	.00025	.012	5.3×10^{-8}
30	.00020	.010	5.3×10^{-8}
45	.00025	.012	5.3×10^{-8}
60	.00020	.010	5.3×10^{-8}
65.3 Hours	.00110	.055	1.0×10^{-8}
89.3	.00095	.048	5.5×10^{-9}
113.2	.00100	.050	6.5×10^{-9}
136.9	.00105	.052	4.3×10^{-9}
161.4	.00105	.052	4.4×10^{-9}
233.5	.00105	.052	4.7×10^{-9}
257.4	.00100	.050	4.6×10^{-9}
281.1	.00100	.050	4.5×10^{-9}
305.0	.00110	.055	4.4×10^{-9}
329.0	.00110	.055	4.6×10^{-9}
401.8	.00100	.050	4.1×10^{-9}
425.8	.00095	.048	4.0×10^{-9}
449.1	.00105	.052	4.1×10^{-9}
473.1	.00115	.058	4.0×10^{-9}
497.0	.00115	.058	4.0×10^{-9}
569.5	.00115	.058	3.9×10^{-9}
593.2	.00120	.060	4.5×10^{-9}
616.9	.00115	.058	4.3×10^{-9}
641.2	.00110	.055	4.3×10^{-9}
740.5	.00115	.058	4.0×10^{-9}
813.2	.00120	.060	4.4×10^{-9}
904.9	.00120	.060	3.8×10^{-9}
929.7	.00125	.062	3.9×10^{-9}

TABLE IX (Continued)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G.L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
953.1	.00120	.060	4.4 x 10 ⁻⁹
977.5	.00120	.060	4.1 x 10 ⁻⁹
1073.8	.00125	.062	3.8 x 10 ⁻⁹
11145.0	.00135	.068	3.8 x 10 ⁻⁹
1241.3	.00165	.082	4.0 x 10 ⁻⁹
1313.6	.00155	.078	7.6 x 10 ⁻⁹
1409.7	.00170	.085	4.3 x 10 ⁻⁹
1482.7	.00165	.082	5.0 x 10 ⁻⁹
1577.4	.00170	.085	5.2 x 10 ⁻⁹
1629.6	.00170	.085	5.0 x 10 ⁻⁹

Test Terminated - Low Creep Rate

Specimen B-21

TABLE X

CREEP TEST DATA, TZM FORGED DISC, HEAT NO. 1175, TESTED AT 1800°F (982°C)

44,000 PSI ($3.03 \times 10^8 \text{N/m}^2$)

Time	Length Change ΔL (inch) (2" G. L.)	Creep (%)	Pressure (Torr)
1 minute(s)	.00000	.000	4.8×10^{-7}
2	.00010	.005	4.8×10^{-7}
3	.00020	.010	4.8×10^{-7}
4	.00025	.012	4.8×10^{-7}
5	.00015	.008	4.8×10^{-7}
6	.00015	.008	4.8×10^{-7}
7	.00010	.005	4.8×10^{-7}
8	.00015	.008	4.8×10^{-7}
9	.00020	.010	4.8×10^{-7}
10	.00020	.010	4.8×10^{-7}
15	.00020	.010	4.8×10^{-7}
30	.00025	.012	4.8×10^{-7}
45	.00025	.012	4.8×10^{-7}
60	.00030	.015	4.8×10^{-7}
65.5 hours	.00055	.028	3.0×10^{-7}
89.1	.00070	.035	2.8×10^{-7}
113.1	.00095	.048	1.1×10^{-8}
137.1	.00100	.050	2.1×10^{-8}
161.1	.00100	.050	1.7×10^{-9}
233.0	.00100	.050	1.0×10^{-9}
257.3	.00105	.052	8.4×10^{-10}
280.9	.00105	.052	1.3×10^{-9}
305.2	.00110	.055	1.6×10^{-9}
329.4	.00110	.055	1.4×10^{-9}
401.0	.00115	.058	1.4×10^{-9}
426.7	.00115	.058	4.0×10^{-10}
449.2	.00120	.060	5.8×10^{-10}
473.4	.00130	.065	7.6×10^{-10}
497.0	.00135	.068	3.8×10^{-10}
569.2	.00145	.072	3.9×10^{-10}
593.1	.00140	.070	5.5×10^{-10}
616.9	.00145	.072	8.4×10^{-10}
640.8	.00140	.070	7.8×10^{-10}
664.8	.00150	.075	5.0×10^{-10}

TABLE X (Continued)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G. L.)</u>	<u>Creep (%)</u>	<u>Pressure</u>
736.8	.00150	.075	8.8 x 10 ⁻¹⁰
761.7	.00150	.075	8.6 x 10 ⁻¹⁰
785.0	.00150	.075	5.0 x 10 ⁻¹⁰
808.8	.00155	.078	9.0 x 10 ⁻¹⁰
833.8	.00155	.078	5.0 x 10 ⁻¹⁰
904.7	.00160	.080	8.4 x 10 ⁻¹⁰
928.8	.00160	.080	8.9 x 10 ⁻¹⁰
953.1	.00160	.080	7.0 x 10 ⁻¹⁰
977.0	.00165	.082	6.0 x 10 ⁻¹⁰
1001.0	.00180	.090	9.2 x 10 ⁻¹⁰
1073.0	.00180	.090	9.1 x 10 ⁻¹⁰
1144.9	.00175	.088	8.2 x 10 ⁻¹⁰

Test in Progress

Specimen B-25

TABLE XI

CREEP TEST DATA, Cb MODIFIED T2M WROUGHT BAR, HEAT NO. 4305-4, TESTED AT
2000°F (1093°C), 20,000 PSI ($1.38 \times 10^8 \text{N/m}^2$)

<u>Time</u>	<u>Length Change</u> <u>ΔL (inch)</u> <u>(2" G. L.)</u>	<u>Creep</u> <u>(%)</u>	<u>Pressure</u> <u>(Torr)</u>
1 minute(s)	.00000	.000	1.8×10^{-7}
2	.00015	.008	1.8×10^{-7}
3	.00010	.005	1.8×10^{-7}
4	.00015	.008	1.8×10^{-7}
5	.00010	.005	1.8×10^{-7}
6	.00015	.008	1.8×10^{-7}
7	.00020	.010	1.8×10^{-7}
8	.00020	.010	1.8×10^{-7}
9	.00025	.012	1.8×10^{-7}
10	.00015	.008	1.8×10^{-7}
15	.00025	.012	1.8×10^{-7}
30	.00020	.010	1.8×10^{-7}
45	.00025	.012	1.8×10^{-7}
60	.00020	.010	1.8×10^{-7}
14.3 hours	.00035	.018	2.6×10^{-8}
86.2	.00065	.032	7.2×10^{-9}
110.1	.00040	.020	6.2×10^{-9}
134.2	.00045	.022	4.4×10^{-9}
158.8	.00045	.022	4.6×10^{-9}
182.5	.00040	.020	3.8×10^{-9}
254.8	.00040	.020	3.0×10^{-9}
278.5	.00040	.020	2.8×10^{-9}
302.2	.00045	.022	2.3×10^{-9}
326.5	.00050	.025	2.2×10^{-9}
350.5	.00050	.025	2.1×10^{-9}
422.5	.00055	.028	2.1×10^{-9}
446.4	.00050	.025	2.4×10^{-9}
470.5	.00055	.028	1.8×10^{-9}
494.3	.00055	.028	2.0×10^{-9}
518.4	.00050	.025	1.8×10^{-9}
590.7	.00060	.030	1.5×10^{-9}
614.3	.00050	.025	1.4×10^{-9}
638.3	.00050	.025	1.4×10^{-9}
662.3	.00055	.028	1.4×10^{-9}
686.2	.00065	.032	1.4×10^{-9}

Test Terminated

Specimen B-23A

TABLE XII

CREEP TEST DATA, Cb MODIFIED TZM WROUGHT BAR, HEAT NO. 4305-4, TESTED AT

2000°F (1093°C), 28,000 PSI ($1.93 \times 10^8 \text{N/m}^2$)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G. L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
1 minute(s)	.00010	.005	1.3×10^{-9}
2	.00010	.005	1.3×10^{-9}
3	.00000	.000	1.3×10^{-9}
4	.00000	.000	1.3×10^{-9}
5	.00000	.000	1.3×10^{-9}
6	-.00005	-.002	1.3×10^{-9}
7	.00005	.002	1.3×10^{-9}
8	.00000	.000	1.3×10^{-9}
9	.00000	.000	1.3×10^{-9}
10	.00005	.002	1.3×10^{-9}
15	.00000	.000	1.3×10^{-9}
30	.00005	.002	1.3×10^{-9}
45	.00010	.005	1.3×10^{-9}
60	.00010	.005	1.3×10^{-9}
66.7 hours	.00015	.008	8.6×10^{-10}
91.0	.00035	.018	8.7×10^{-10}
114.6	.00035	.018	1.1×10^{-9}
138.9	.00030	.015	5.1×10^{-10}
163.1	.00035	.018	4.8×10^{-10}
234.7	.00045	.022	4.9×10^{-10}
259.0	.00050	.025	1.1×10^{-9}
282.9	.00045	.022	1.5×10^{-9}
307.0	.00055	.028	1.5×10^{-9}

Test Terminated

Specimen B-23B

TABLE XIII

CREEP TEST DATA, Cb MODIFIED TZM WROUGHT BAR, HEAT NO. 4305-4, TESTED AT

2000°F (1093°C), 40,000 PSI ($2.76 \times 10^8 \text{N/m}^2$)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G. L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
1 minute(s)	.00000	.000	1.5×10^{-9}
2	.00005	.002	1.5×10^{-9}
3	.00010	.005	1.5×10^{-9}
4	.00010	.005	1.5×10^{-9}
5	.00010	.005	1.5×10^{-9}
6	.00015	.008	1.5×10^{-9}
7	.00010	.005	1.5×10^{-9}
8	.00010	.005	1.5×10^{-9}
9	.00015	.008	1.5×10^{-9}
10	.00020	.010	1.5×10^{-9}
15	.00015	.008	1.5×10^{-9}
30	.00015	.008	1.5×10^{-9}
45	.00020	.010	1.5×10^{-9}
60	.00020	.010	1.5×10^{-9}
17.3 hours	.00100	.050	1.4×10^{-9}
89.5	.00255	.128	1.4×10^{-9}
113.4	.00270	.135	1.4×10^{-9}
137.3	.00305	.152	1.3×10^{-9}
161.2	.00345	.172	1.3×10^{-9}
185.2	.00375	.188	1.3×10^{-9}

Test Terminated

Specimen B-23C

TABLE XIV

CREEP TEST DATA, Cb MODIFIED TZM WROUGHT BAR, HEAT NO. 4305-4, TESTED AT

1800°F (982°C), 46,000 PSI ($3.17 \times 10^8 \text{ N/m}^2$)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G. L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
1 minute(s)	.00005	.002	1.1×10^{-9}
2	.00010	.005	1.1×10^{-9}
3	.00005	.002	1.1×10^{-9}
4	.00000	.000	1.1×10^{-9}
5	.00005	.002	1.1×10^{-9}
6	.00000	.000	1.1×10^{-9}
7	-.00005	-.002	1.1×10^{-9}
8	.00000	.000	1.1×10^{-9}
9	.00000	.000	1.1×10^{-9}
10	.00005	.002	1.1×10^{-9}
15	.00005	.002	1.1×10^{-9}
30	.00000	.000	1.1×10^{-9}
45	.00000	.000	1.1×10^{-9}
60	.00000	.000	1.1×10^{-9}
66.4 hours	.00010	.005	1.2×10^{-9}
91.3	.00025	.012	1.1×10^{-9}
114.5	.00050	.025	1.1×10^{-9}
138.4	.00080	.040	1.1×10^{-9}
163.4	.00110	.055	1.1×10^{-9}
234.3	.00125	.062	1.0×10^{-9}
258.3	.00135	.068	1.1×10^{-9}
282.6	.00140	.070	1.1×10^{-9}
306.6	.00140	.070	1.1×10^{-9}
330.5	.00145	.072	9.5×10^{-10}
402.6	.00155	.078	1.1×10^{-9}

Test Terminated

Specimen B-23D

TABLE XV

CREEP TEST DATA. Cb MODIFIED TZM WROUGHT BAR, HEAT NO. 4305-4, TESTED AT
2100°F (1149°C) 34,000 PSI ($2.41 \times 10^8 \text{N/m}^2$)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G. L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
1 minute(s)	.00010	.005	1.6×10^{-9}
2	.00010	.005	1.6×10^{-9}
5	-.00005	-.002	1.6×10^{-9}
6	.00000	.000	1.6×10^{-9}
7	-.00005	-.002	1.6×10^{-9}
8	.00005	.002	1.6×10^{-9}
9	.00010	.005	1.6×10^{-9}
10	.00000	.000	1.6×10^{-9}
15	.00005	.002	1.6×10^{-9}
30	.00010	.005	1.6×10^{-9}
45	.00005	.002	1.6×10^{-9}
60	.00010	.005	1.6×10^{-9}
16.1 hours	.00015	.008	1.7×10^{-9}
40.0	.00075	.038	1.6×10^{-9}
64.2	.00120	.060	1.4×10^{-9}
88.2	.00160	.080	1.4×10^{-9}
160.0	.00195	.098	1.4×10^{-9}
184.5	.00210	.105	1.4×10^{-9}
214.8	.00260	.130	1.2×10^{-9}
232.4	.00270	.135	1.7×10^{-9}
256.3	.00290	.145	1.7×10^{-9}
328.7	.00340	.170	1.8×10^{-9}

Test Terminated

Specimen B-23E

TABLE XVI

CREEP TEST DATA, Cb MODIFIED TZM WROUGHT BAR, HEAT NO. 4305-4, TESTED AT

2000°F (1093°C), 41,000 PSI ($2.82 \times 10^8 \text{N/m}^2$)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G. L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
1 minute(s)	.00005	.002	2.5×10^{-7}
2	.00005	.002	2.5×10^{-7}
3	.00000	.000	2.5×10^{-7}
4	.00005	.002	2.5×10^{-7}
5	.00010	.005	2.5×10^{-7}
6	.00010	.005	2.5×10^{-7}
7	.00010	.005	2.5×10^{-7}
8	.00015	.008	2.5×10^{-7}
9	.00010	.005	2.5×10^{-7}
10	.00010	.005	2.5×10^{-7}
15	.00015	.008	2.5×10^{-7}
30	.00015	.008	2.5×10^{-7}
45	.00020	.010	2.5×10^{-7}
60	.00025	.012	2.5×10^{-7}
17.7 hours	.00070	.035	2.0×10^{-8}
40.8	.00110	.055	9.9×10^{-9}
64.9	.00155	.078	6.4×10^{-9}
89.9	.00195	.098	3.9×10^{-9}
160.7	.00250	.125	2.3×10^{-9}
184.8	.00255	.128	2.3×10^{-9}
208.9	.00265	.132	2.0×10^{-9}
233.0	.00275	.138	1.7×10^{-9}
256.9	.00285	.142	2.8×10^{-9}
329.0	.00305	.152	2.5×10^{-9}
352.8	.00310	.155	1.3×10^{-9}
376.7	.00315	.158	1.1×10^{-9}
400.9	.00325	.162	1.2×10^{-9}

Test in progress

Specimen B-27

TABLE XVII

CREEP TEST DATA, T-111 SHEET, HEAT NO. 70616, ANNEALED 3000°F (1649°C) FOR 1 HOUR

TESTED AT 2200°F (1204°C), 8,000 PSI ($5.52 \times 10^7 \text{N/m}^2$)

Time	Length Change ΔL (inch) (2" G. L.)	Creep (%)	Pressure (Torr)
1 minute(s)	.00005	.002	2.6×10^{-9}
2	.00010	.005	2.6×10^{-9}
3	.00015	.008	2.6×10^{-9}
4	.00010	.005	2.6×10^{-9}
5	.00005	.002	2.6×10^{-9}
6	.00005	.002	2.6×10^{-9}
7	.00005	.002	2.6×10^{-9}
8	.00000	.000	2.6×10^{-9}
9	.00005	.002	2.6×10^{-9}
10	.00005	.002	2.6×10^{-9}
15	.00000	.000	2.6×10^{-9}
30	.00010	.005	2.6×10^{-9}
45	.00010	.005	2.6×10^{-9}
60	.00005	.002	2.6×10^{-9}
2.4 hours	.00005	.002	2.6×10^{-9}
19.2	.00010	.005	2.0×10^{-9}
43.1	.00010	.005	1.6×10^{-9}
48.3	.00035	.018	1.6×10^{-9}
67.1	.00060	.030	1.5×10^{-9}
139.4	.00135	.068	1.4×10^{-9}
163.0	.00155	.078	1.4×10^{-9}
187.0	.00175	.088	1.2×10^{-9}
211.3	.00190	.095	1.3×10^{-9}
310.5	.00215	.108	1.2×10^{-9}
383.3	.00245	.122	1.3×10^{-9}
474.9	.00320	.160	1.3×10^{-9}
499.3	.00370	.185	1.2×10^{-9}
523.1	.00390	.195	1.3×10^{-9}
547.6	.00405	.202	1.2×10^{-9}
572.0	.00470	.235	1.3×10^{-9}
643.8	.00530	.265	1.4×10^{-9}
691.2	.00545	.272	1.3×10^{-9}
714.9	.00560	.280	1.2×10^{-9}
739.2	.00565	.282	1.2×10^{-9}
811.1	.00625	.312	1.3×10^{-9}
835.0	.00640	.320	1.2×10^{-9}
859.1	.00655	.328	1.4×10^{-9}
883.5	.00675	.338	1.3×10^{-9}

TABLE XVII (Continued)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G. L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
907.3 hours	.00685	.342	1.3 x 10 ⁻⁹
979.7	.00750	.375	1.3 x 10 ⁻⁹
1051.4	.00835	.418	1.2 x 10 ⁻⁹
1147.3	.00975	.488	1.3 x 10 ⁻⁹
1219.0	.01050	.525	1.3 x 10 ⁻⁹
1315.7	.01125	.562	1.1 x 10 ⁻⁹
1387.2	.01150	.575	1.1 x 10 ⁻⁹
1483.1	.01375	.688	8.3 x 10 ⁻⁹
1555.3	.01410	.705	1.3 x 10 ⁻⁹
1651.0	.01515	.758	7.0 x 10 ⁻¹⁰
1723.4	.01615	.808	8.2 x 10 ⁻¹⁰
1819.2	.01755	.878	9.0 x 10 ⁻¹⁰
1890.9	.01830	.915	7.4 x 10 ⁻¹⁰
1986.9	.01980	.990	7.9 x 10 ⁻¹⁰
2059.0	.02080	1.040	8.3 x 10 ⁻¹⁰
2154.8	.02230	1.115	7.0 x 10 ⁻¹⁰
2227.1	.02315	1.158	6.9 x 10 ⁻¹⁰
2323.1	.02445	1.222	7.5 x 10 ⁻¹⁰
2395.0	.02580	1.290	7.0 x 10 ⁻¹⁰

Test in Progress

Specimen S-19

TABLE XVIII

CREEP TEST DATA, T-111 SHEET, HEAT NO. 70616, ANNEALED 3000°F (1649°C) FOR 1 HOUR,

TESTED AT 2200°F (1204°C), 12,000 PSI ($8.27 \times 10^7 \text{ N/m}^2$)

Time	Length Change ΔL (Inch) (2" G.L.)	Creep (%)	Pressure (Torr)
1 minute(s)	.00000	.000	2.9×10^{-7}
2	.00005	.002	2.9×10^{-7}
3	.00010	.005	2.9×10^{-7}
4	.00010	.005	2.9×10^{-7}
5	.00010	.005	2.9×10^{-7}
6	.00015	.008	2.9×10^{-7}
7	.00020	.010	2.9×10^{-7}
8	.00015	.008	2.9×10^{-7}
9	.00020	.010	2.9×10^{-7}
10	.00020	.010	2.9×10^{-7}
15	.00015	.008	2.9×10^{-7}
30	.00020	.010	2.9×10^{-7}
45	.00015	.008	2.9×10^{-7}
60	.00015	.008	2.9×10^{-7}
17.7 hours	.00045	.022	2.1×10^{-8}
42.1	.00085	.042	1.1×10^{-8}
113.9	.00180	.090	6.4×10^{-9}
161.3	.00220	.110	4.9×10^{-9}
185.1	.00270	.135	4.4×10^{-9}
209.3	.00280	.140	4.4×10^{-9}
281.3	.00300	.150	3.9×10^{-9}
305.1	.00370	.185	3.8×10^{-9}
329.2	.00435	.218	3.2×10^{-9}
353.6	.00480	.240	2.6×10^{-9}
377.5	.00510	.255	2.1×10^{-9}
449.8	.00625	.312	2.8×10^{-9}
473.3	.00660	.330	3.2×10^{-9}
497.1	.00700	.350	3.1×10^{-9}
521.5	.00735	.368	2.3×10^{-9}
545.4	.00775	.388	2.2×10^{-9}
617.3	.00905	.452	2.0×10^{-9}
641.4	.00960	.480	2.1×10^{-9}
665.2	.01040	.520	2.0×10^{-9}
689.1	.01080	.540	2.1×10^{-9}
713.4	.01125	.562	1.9×10^{-9}
785.3	.01270	.635	2.5×10^{-9}
809.2	.01300	.650	2.5×10^{-9}
833.3	.01340	.670	1.8×10^{-9}
857.3	.01420	.710	2.0×10^{-9}

TABLE XVIII (Continued)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G. L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
881.1	.01435	.718	2.0 x 10 ⁻⁹
953.2	.01615	.807	5.1 x 10 ⁻¹⁰
977.5	.01680	.840	1.0 x 10 ⁻⁹
1001.1	.01740	.870	1.4 x 10 ⁻⁹
1025.4	.01790	.895	1.0 x 10 ⁻⁹
1049.2	.01840	.920	1.5 x 10 ⁻⁹
1121.1	.01985	.992	1.6 x 10 ⁻⁹
1193.5	.02205	1.102	1.8 x 10 ⁻⁹
1289.3	.02460	1.230	1.8 x 10 ⁻⁹
1361.0	.02635	1.318	8.0 x 10 ⁻¹⁰
1457.0	.02920	1.460	1.8 x 10 ⁻⁹
1529.2	.03070	1.535	1.9 x 10 ⁻⁹
1624.9	.03415	1.708	7.2 x 10 ⁻¹⁰
1697.2	.03660	1.830	8.1 x 10 ⁻¹⁰
1793.2	.03985	1.992	6.7 x 10 ⁻¹⁰
1865.1	.04185	2.092	1.8 x 10 ⁻⁹

Test in Progress

Specimen S-21

TABLE XIX

CREEP TEST DATA, T-111 SHEET, HEAT NO. 70616, ANNEALED 3000°F (1649°C) FOR 1 HOUR,

TESTED AT 2000°F (1093°C), 20,000 PSI ($1.38 \times 10^8 \text{N/m}^2$)

Time	Length Change ΔL (inch) (2" G. L.)	Creep (%)	Pressure (Torr)
1 minute(s)	.00015	.008	7.3×10^{-8}
2	.00010	.005	7.3×10^{-8}
3	.00010	.005	7.3×10^{-8}
4	.00005	.002	7.3×10^{-8}
5	.00010	.005	7.3×10^{-8}
6	.00015	.008	7.3×10^{-8}
7	.00015	.008	7.3×10^{-8}
8	.00015	.008	7.3×10^{-8}
9	.00015	.008	7.3×10^{-8}
10	.00015	.008	7.3×10^{-8}
15	.00020	.010	7.3×10^{-8}
30	.00015	.008	7.3×10^{-8}
45	.00015	.008	7.3×10^{-8}
60	.00015	.008	7.3×10^{-8}
67.4 hours	.00125	.062	1.1×10^{-8}
91.3	.00140	.070	9.9×10^{-9}
115.3	.00155	.078	7.2×10^{-9}
139.4	.00195	.098	6.8×10^{-9}
163.2	.00250	.125	6.6×10^{-9}
235.3	.00450	.225	4.1×10^{-9}
259.5	.00495	.248	3.3×10^{-9}
283.1	.00540	.270	3.0×10^{-9}
307.4	.00605	.302	2.6×10^{-9}
331.3	.00690	.345	1.0×10^{-9}
403.1	.00930	.465	2.5×10^{-9}
427.5	.01040	.520	3.1×10^{-9}
451.3	.01100	.550	2.8×10^{-9}
475.6	.01215	.608	2.8×10^{-9}
499.2	.01295	.648	2.9×10^{-9}
571.4	.01615	.807	2.8×10^{-9}
595.3	.01680	.840	2.7×10^{-9}
619.2	.01760	.880	2.8×10^{-9}
643.0	.01875	.938	2.6×10^{-9}
667.0	.01990	.995	2.8×10^{-9}
739.0	.02315	1.158	2.6×10^{-9}
763.9	.02435	1.218	2.5×10^{-9}
787.1	.02535	1.268	3.1×10^{-9}

TABLE XIX (Continued)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G. L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
811.2 hours	.02640	1.320	3.1×10^{-9}
836.1	.02770	1.385	2.6×10^{-9}
907.0	.03085	1.542	2.6×10^{-9}
931.0	.03200	1.600	2.6×10^{-9}
955.1	.03310	1.655	2.7×10^{-9}
979.2	.03430	1.715	2.2×10^{-9}
1033.1	.03570	1.785	2.4×10^{-9}
1075.2	.03890	1.945	2.4×10^{-9}
1099.1	.04020	2.010	2.3×10^{-9}

Test Terminated - 2% Creep

Specimen S-22

TABLE XX

CREEP TEST DATA, T-222 SHEET, ANNEALED AT 2800°F (1538°C) FOR 1 HOUR, TESTED AT
 2200°F (1204°C), 12,000 PSI ($8.27 \times 10^7 \text{N/m}^2$)

Time	Length Change ΔL (inch) (2" G. L.)	Creep (%)	Pressure (Torr)
1 minute(s)	.00000	.000	1.2×10^{-8}
2	-.00010	-.005	1.2×10^{-8}
3	-.00015	-.008	1.2×10^{-8}
4	-.00005	-.002	1.2×10^{-8}
5	.00000	.000	1.2×10^{-8}
6	.00005	.002	1.2×10^{-8}
7	.00005	.002	1.2×10^{-8}
8	.00005	.002	1.2×10^{-8}
9	.00010	.005	1.2×10^{-8}
10	.00005	.002	1.2×10^{-8}
15	.00010	.005	1.2×10^{-8}
30	.00000	.000	1.2×10^{-8}
45	.00000	.000	1.2×10^{-8}
60	.00005	.002	1.2×10^{-8}
16.3 hours	.00025	.012	8.5×10^{-9}
40.7	.00085	.042	9.6×10^{-9}
64.6	.00175	.088	1.2×10^{-9}
136.6	.00490	.245	6.3×10^{-10}
160.6	.00635	.318	6.4×10^{-10}
184.4	.00760	.380	6.1×10^{-10}
208.3	.00930	.465	1.7×10^{-9}
232.6	.01010	.505	6.0×10^{-10}
304.5	.01440	.720	6.0×10^{-10}
328.5	.01560	.780	5.8×10^{-10}
352.5	.01670	.835	5.7×10^{-10}
376.5	.01815	.908	5.6×10^{-10}
400.4	.01960	.980	6.5×10^{-10}
472.4	.02430	1.215	5.0×10^{-10}
496.7	.02575	1.288	3.6×10^{-10}
520.3	.02730	1.365	4.7×10^{-10}
544.6	.02900	1.450	2.1×10^{-10}
568.5	.03035	1.518	1.6×10^{-10}
640.3	.03600	1.800	2.0×10^{-10}
664.7	.03780	1.890	1.6×10^{-9}
688.5	.03955	1.978	4.9×10^{-9}
712.8	.04100	2.050	1.2×10^{-9}
736.4	.04290	2.145	4.5×10^{-10}
808.6	.04870	2.435	1.4×10^{-9}
832.5	.05085	2.542	1.4×10^{-9}
856.4	.05260	2.680	1.4×10^{-9}
880.2	.05450	2.725	1.5×10^{-9}

TABLE XX (Continued)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G.L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
904.2	.05675	2.838	1.5 x 10 ⁻⁹
976.2	.06290	3.145	1.4 x 10 ⁻⁹
1001.1	.06535	3.268	1.4 x 10 ⁻⁹
1024.3	.06735	3.368	1.5 x 10 ⁻⁹
1048.4	.06910	3.455	1.4 x 10 ⁻⁹
1073.3	.07150	3.575	5.1 x 10 ⁻¹⁰
1114.2	.07765	3.882	4.9 x 10 ⁻⁹
1168.2	.08000	4.000	1.4 x 10 ⁻⁹
1192.3	.08280	4.140	4.8 x 10 ⁻¹⁰
1216.4	.08540	4.270	4.7 x 10 ⁻¹⁰
1240.3	.08710	4.355	4.6 x 10 ⁻¹⁰
1312.4	.09435	4.718	5.6 x 10 ⁻¹⁰
1336.3	.09635	4.818	4.8 x 10 ⁻¹⁰
1360.2	.09835	4.918	5.3 x 10 ⁻¹⁰
1389.0	.10120	5.060	5.0 x 10 ⁻¹⁰

Test Terminated - 5% Creep

Specimen S-20

TABLE XXI

CREEP TEST DATA, ARC-MELTED TUNGSTEN SHEET, ANNEALED 2800°F (1538°C)

1 HOUR, TESTED AT 2800°F (1538°C), 3,000 PSI ($2.07 \times 10^7 \text{ N/m}^2$)

Time	Length Change ΔL (inch) (2" G.L.)	Creep (%)	Pressure (Torr)
1 minute(s)	.00010	.005	2.4×10^{-7}
2	.00000	.000	2.4×10^{-7}
3	.00005	.002	2.4×10^{-7}
4	.00000	.000	2.4×10^{-7}
5	.00000	.000	2.4×10^{-7}
6	.00010	.005	2.4×10^{-7}
7	.00015	.008	2.4×10^{-7}
8	.00005	.002	2.4×10^{-7}
9	.00010	.005	2.4×10^{-7}
10	.00010	.005	2.4×10^{-7}
15	.00005	.002	2.4×10^{-7}
30	.00010	.005	2.4×10^{-7}
45	.00015	.008	2.4×10^{-7}
60	.00010	.005	2.4×10^{-7}
3.1 hour(s)	.00060	.030	2.4×10^{-7}
23.95	.00535	.218	1.0×10^{-7}
46.95	.00830	.415	2.9×10^{-8}
67.4	.01205	.602	2.0×10^{-8}
91.2	.01435	.718	1.7×10^{-8}
114.9	.01835	.918	1.0×10^{-8}
138.8	.02190	1.095	8.7×10^{-9}
162.8	.02355	1.178	8.9×10^{-9}
234.8	.03280	1.640	7.2×10^{-9}
259.0	.03665	1.832	7.4×10^{-9}
282.9	.04075	2.038	7.2×10^{-9}
306.8	.04340	2.170	6.8×10^{-9}
330.8	.04750	2.375	6.4×10^{-9}
403.2	.05605	2.802	3.8×10^{-9}
426.8	.05845	2.922	3.9×10^{-9}
450.8	.06065	3.032	4.1×10^{-9}
479.9	.06370	3.185	4.0×10^{-9}
574.3	.07495	3.748	3.0×10^{-9}
647.0	.08195	4.098	1.7×10^{-9}
738.7	.09155	4.578	1.5×10^{-9}
763.1	.09445	4.722	1.6×10^{-9}
786.9	.09690	4.845	3.1×10^{-9}
811.3	.09880	4.940	1.6×10^{-9}
835.8	.10160	5.080	1.5×10^{-9}
907.5	.11070	5.535	3.0×10^{-9}

Test Terminated - 5% Creep

Specimen S-18

TABLE XXII

CREEP TEST DATA, VAPOR DEPOSITED TUNGSTEN, RECRYSTALLIZED 1 HOUR 2800°F (1538°C)

TESTED AT 2800°F (1538°C), 2000 PSI ($1.38 \times 10^7 \text{ N/m}^2$)

Time	Length Change ΔL (inch) (2" G. L.)	Creep (%)	Pressure (Torr)
1 minute(s)	.00020	.010	3.5×10^{-7}
2	.00025	.012	3.5×10^{-7}
3	.00025	.012	3.5×10^{-7}
4	.00025	.012	3.5×10^{-7}
5	.00025	.012	3.5×10^{-7}
6	.00030	.015	3.5×10^{-7}
7	.00040	.020	3.5×10^{-7}
8	.00035	.018	3.5×10^{-7}
9	.00040	.020	3.5×10^{-7}
10	.00035	.018	3.5×10^{-7}
15	.00000	.000	3.5×10^{-7}
30	-.00005	-.002	3.5×10^{-7}
45	.00000	.000	3.5×10^{-7}
60	-.00005	-.002	3.5×10^{-7}
64.9 hours	.00175	.088	8.0×10^{-8}
88.9	.00210	.105	6.4×10^{-8}
112.8	.00260	.130	4.6×10^{-8}
136.7	.00310	.155	4.1×10^{-8}
161.0	.00370	.185	3.8×10^{-8}
232.8	.00480	.240	3.4×10^{-8}
256.8	.00525	.262	3.1×10^{-8}
280.8	.00550	.275	2.9×10^{-8}
304.8	.00570	.285	2.7×10^{-8}
328.7	.00635	.318	2.6×10^{-8}
400.8	.00750	.375	1.6×10^{-8}
425.0	.00760	.380	1.3×10^{-8}
448.6	.00775	.388	7.8×10^{-9}
472.8	.00795	.398	6.3×10^{-9}
496.8	.00830	.415	5.6×10^{-9}
568.7	.00930	.465	5.0×10^{-9}
600.1	.00990	.495	1.1×10^{-9}
616.7	.01040	.520	1.2×10^{-8}
641.1	.01015	.508	1.1×10^{-8}
664.7	.00980	.490	1.0×10^{-8}
736.8	.01150	.575	9.9×10^{-9}
760.7	.01190	.595	8.6×10^{-9}
784.7	.01310	.655	9.7×10^{-9}

TABLE XXII (Continued)

<u>Time</u>	<u>Length Change ΔL (inch) (2" G. L.)</u>	<u>Creep (%)</u>	<u>Pressure (Torr)</u>
808.5	.01235	.618	9.4×10^{-9}
832.5	.01270	.635	9.4×10^{-9}
904.5	.01350	.675	9.2×10^{-9}
929.4	.01370	.685	8.6×10^{-9}
952.6	.01410	.705	8.5×10^{-9}
976.8	.01445	.722	7.0×10^{-9}
1001.8	.01460	.730	8.2×10^{-9}
1072.5	.01540	.770	8.0×10^{-9}
1144.8	.01660	.830	7.8×10^{-9}
1240.7	.01775	.888	7.8×10^{-9}
1312.7	.01830	.915	5.6×10^{-9}

Test in Progress

Specimen B-24

EXTERNAL DISTRIBUTION

National Aeronautics and Space Administration
Washington, D. C. 20546
Attn: Walter C. Scott
Attn: James J. Lynch (RN)
Attn: George C. Deutsch (RR)

National Aeronautics and Space Administration
Scientific and Technical Information Facility
Box 5700
Bethesda, Maryland 21811

2 copies + 2 reproducible

National Aeronautics and Space Administration
Ames Research Center
Moffet Field, California 94035
Attn: Librarian

National Aeronautics and Space Administration
Goddard Space Flight Center
Greenbelt, Maryland 20771
Attn: Librarian

National Aeronautics and Space Administration
Langley Research Center
Hampton, Virginia 23365
Attn: Librarian

National Aeronautics and Space Administration
Manned Spacecraft Center
Houston, Texas 77001
Attn: Librarian

National Aeronautics and Space Administration
George C. Marshall Space Flight Center
Huntsville, Alabama 35812
Attn: Librarian

National Aeronautics and Space Administration
Jet Propulsion Laboratory
4800 Oak Grove Drive
Pasadena, California 91103
Attn: Librarian

National Aeronautics and Space Administration
21000 Brookpark Road
Cleveland, Ohio 44135

Attn: Librarian

Dr. Bernard Lubarsky (SPSD) MS 86-1

Roger Mather (NPTB)

G. M. Ault MS 105-1

Joe Joyce (NPTB) MS 86-5

Paul Moorhead (NPTB)

10 copies

John Creagh MS 86-5

John E. Dilley (SPSPS) MS 85-1

Norman T. Musial MS 77-1

Thomas Strom MS 5-8

T. A. Moss (NPTB) MS 86-5

Dr. Louis Rosenblum (MSD) (106-1)

R. Titran MS 105-1

R. Hall MS 105-1

George Tulisiak MS 14-1

National Aeronautics and Space Administration
Western Operations Office
150 Pico Boulevard
Santa Monica, California 90406
Attn: Mr. John Keeler

National Bureau of Standards
Washington 25, D. C.
Attn: Librarian

Aeronautical Systems Division
Wright-Patterson Air Force Base, Ohio
Attn: Charles Armbruster (ASRPP-10)
T. Cooper
Librarian
John L. Morris
H J. Middendorp ASNRG 33143

Army Ordnance Frankford Arsenal
Bridesburg Station
Philadelphia 37, Pennsylvania
Attn: Librarian

I. I. T. Research Institute
10 W. 35th Street
Chicago, Illinois 60616

Atomics International
8900 DeSoto Avenue
Canoga Park, California

AVCO
Research and Advanced Development Department
201 Lowell Street
Wilmington, Massachusetts
Attn: Librarian

Babcock and Wilcox Company
Research Center
Alliance, Ohio
Attn: Librarian

Battelle Memorial Institute
505 King Avenue
Columbus, Ohio
Attn: C. M. Allen
Attn: Librarian

The Bendix Corporation
Research Laboratories Division
Southfield, Detroit 1, Michigan
Attn: Librarian

The Boeing Company
Seattle, Washington
Attn: Librarian

Brush Beryllium Company
Cleveland, Ohio
Attn: Librarian

Carborundum Company
Niagara Falls, New York
Attn: Librarian

General Dynamics/Fort Worth
P. O. Box 748
Fort Worth, Texas
Attn: Librarian

General Motors Corporation
Allison Division
Indianapolis 6, Indiana
Attn: Librarian

Hamilton Standard
Division of United Aircraft Corporation
Windsor Locks, Connecticut
Attn: Librarian

Hughes Aircraft Company
Engineering Division
Culver City, California
Attn: Librarian

Lockheed Missiles and Space Division
Lockheed Aircraft Corporation
Sunnyvale, California
Attn: Librarian

Marquardt Aircraft Company
P. O. Box 2013
Van Nuys, California
Attn: Librarian

The Martin Company
Baltimore 3, Maryland
Attn: Librarian

The Martin Company
Nuclear Division
P. O. Box 5042
Baltimore 20, Maryland
Attn: Librarian

Chance Vought Aircraft Inc.
P. O. Box 5907
Dallas 22, Texas
Attn: Librarian

Clevite Corporation
Mechanical Research Division
540 East 105th Street
Cleveland 8, Ohio
Attn: Mr. N. C. Beerli,
Project Administrator

Climax Molybdenum Company of Michigan
Detroit, Michigan
Attn: Librarian

Convair Astronautics
5001 Kerrny Villa Road
San Diego 11, California
Attn: Librarian

Curtiss-Wright Corporation
Research Division
Tuehanna, Pennsylvania
Attn: Librarian

E. I. dePont de Nemours and Company, Inc.
Wilmington 98, Delaware
Attn: W. E. Lusby, Jr.
Defense Contracts Supervisor

Electro-Optical Systems, Incorporated
Advanced Power Systems Division
Pasadena, California
Attn: Librarian

Fansteel Metallurgical Corporation
North Chicago, Illinois
Attn: Librarian
Attn: Henry L. Kohn

Ford Motor Company
Aeronutronics
Newport Beach, California
Attn: Librarian

General Atomic
John Jay Hopkins Laboratory
P. O. Box 608
San Diego 12, California
Attn: Librarian

General Electric Company
Atomic Power Equipment Division
P. O. Box 1131
San Jose, California

General Electric Company
Missile and Space Vehicle Dept.
3198 Chestnut Street
Philadelphia 4, Pennsylvania

General Electric Company
Vallecitos Atomic Laboratory
Pleasanton, California
Attn: Librarian

General Electric Company
Evendale, Ohio 45215
FPD Technical Information Center
Bldg. 100, Mail Drop F-22

General Electric Company
Reentry Systems Dept.
Cincinnati, Ohio 45215
Attn: Dr. J. W. Semmel
E. E. Hoffman

2 copies

Bureau of Ships
Department of the Navy
Washington 25, D. C.
Attn: Librarian

Bureau of Weapons
Research and Engineering
Material Division
Washington 25, D. C.
Attn: Librarian

U. S. Naval Research Laboratory
Washington 25, D. C.
Attn: Librarian

Advanced Technology Laboratories
Division of American Standard
369 Whisman Road
Mountain View, California
Attn: Librarian

Aerojet General Nucleonics
P. O. Box 77
San Ramon, California
Attn: Librarian

AiResearch Manufacturing Company
Sky Harbor Airport
402 South 36th Street
Pheonix, Arizona
Attn: Librarian
E. A. Kovacevich

AiResearch Manufacturing Company
9851-9951 Sepulveda Boulevard
Los Angeles 45, California
Attn: Librarian

Martin Marietta Corporation
Metals Technology Laboratory
Wheeling, Illinois

Massachusetts Institute of Technology
Cambridge 39, Massachusetts
Attn: Librarian

Materials Research and Development
Manlabs, Inc.
21 Erie Street
Cambridge 39, Massachusetts

Materials Research Corporation
Orangeburg, New York
Attn: Librarian

McDonnell Aircraft
St. Louis, Missouri
Attn: Librarian

MSA Research Corporation
Callery, Pennsylvania
Attn: Librarian

National Research Corporation
70 Memorial Drive
Cambridge 42, Massachusetts
Attn: Librarian

North American Aviation
Los Angeles Division
Los Angeles 9, California
Attn: Librarian

Norton Company
Worcester, Massachusetts
Attn: Librarian

Pratt & Whitney Aircraft
400 Main Street
East Hartford 8, Connecticut
Attn: Librarian

Pratt & Whitney Aircraft
Materials Development Laboratory
P.O. Box 611
Middletown, Connecticut
Attn: Librarian

RCA
Defense Electronics Products
Astro-Electronics Division
Princeton, New Jersey
Attn: S. H. Winkler

Lawrence Radiation Lab
Technical Information Division
Livermore, California 94550
Attn: W. Blake Myers

General Electric Company
Nuclear Materials & Propulsion Operation
P. O. Box 132
Cincinnati, Ohio 45215
Attn: J. W. Stephenson (2 copies)

Dr. James Hadley
Head, Reactor Division
Lawrence Radiation Laboratory
P.O. Box 808
Livermore, California

H. F. Conrad
Process and Materials Division
Chemistry Department
Lawrence Radiation Laboratory
P.O. Box 808
Livermore, California

Matthew King
TRW SYSTEMS INC.
1 Space Park
Redondo Beach, California

ATTN: Nuclear Technology Dept.

Republic Aviation Corporation
Farmingdale, Long Island, New York
Attn: Librarian

Solar
2200 Pacific Highway
San Diego 12, California
Attn: Frank Hill
Manager
Aerospace Sales

Southwest Research Institute
8500 Culebra Road
San Antonio 6, Texas
Attn: Librarian

Rocketdyne
Canoga Park, California
Attn: Librarian

Attn: N. Hoffman

Superior Tube Company
Norristown, Pennsylvania
Attn: Mr. A. Bound

Sylvania Electric Products, Inc.
Chemical and Metallurgical
Towanda, Pennsylvania
Attn: Librarian

Temescal Metallurgical
Berkeley, California
Attn: Librarian

Union Carbide Corporation
Parma Research Center
Technical Information Service
P. O. Box 6116
Cleveland, Ohio 44101

Ultek Corporation
Kingston Building, Rm. 211
1373 Grandview Avenue
Columbus, Ohio
Attn: Bruce Weber

General Electric Company
Materials Applied Research
Materials Development Laboratory
Mail Zone M78
Evendale, Ohio
Attn: W. H. Chang

R. C. A.
Astron-Electronics Division
Post Office Box 500
Princeton, New Jersey
Attn: Librarian, Mr. Fred Meigs

Dr. Alan Lawley
Franklin Institute
Philadelphia 3, Pennsylvania

L. J. Goetz
General Electric Co.
Refractory Metals Plant
21801 Tungsten Road
Cleveland, Ohio 44117

Union Carbide Metals
Niagara Falls, New York
Attn: Librarian

Union Carbide Stellite Corporation
Kokomo, Indiana
Attn: Librarian

Union Carbide Nuclear Company
P. O. Box X
Oak Ridge, Tennessee
Attn: X-10 Laboratory Records Department 2 copies

United Nuclear Corporation
5 New Street
White Plains, New York
Attn: Librarian
Attn: Mr. Albert Weinstein,
Sr. Engineer

Universal Cyclops Steel Corporation
Refractomet Division
Bridgeville, Pennsylvania
Attn: C. P. Mueller

University of Michigan
Department of Chemical and Metallurgical Eng.
Ann Arbor, Michigan
Attn: Librarian

U. S. Atomic Energy Commission
Technical Reports Library
Washington 25, D. C.
Attn: J. M. O'Leary

U. S. Atomic Energy Commission
Germantown, Maryland
Attn: Col. E. L. Douthett
SNAP 50/SPUR Project Office
Attn: H. Rothen
SNAP 50/SPUR Project Office
Attn: Socrates Christofer
Attn: Major Gordon Dicker
SNAP 50/SPUR Project Office

U. S. Atomic Energy Commission
Technical Information Service Extension
P. O. Box 62
Oak Ridge, Tennessee

3 copies

U. S. Atomic Energy Commission
Washington 25, D. C.
Attn: M. J. Whitman

Argonne National Laboratory
9700 South Cross Avenue
Argonne, Illinois
Attn: Librarian

Brookhaven National Laboratory
Upton Long Island, New York
Attn: Librarian

Oak Ridge National Laboratory
Oak Ridge, Tennessee
Attn: Dr. W. O. Harms
Attn: Dr. A. J. Miller
Attn: Librarian

Office of Naval Research
Power Division
Washington 25, D. C.
Attn: Librarian

Vought Astronautics
P. O. Box 5907
Dallas 22, Texas
Attn: Librarian

Wah Chang Corporation
Albany, Oregon
Attn: Librarian
Attn: S. Worcester

Westinghouse Electric Corporation
Astronuclear Laboratory
P. O. Box 10864
Pittsburgh, Pennsylvania 15236
Attn: R. Begley

Westinghouse Electric Corporation
Materials Manufacturing Division
RD No. 2 Box 25
Blairsville, Pennsylvania
Attn: Librarian
Attn: F. L. Orrell

Wolverine Tube Division
Calumet and Hecla, Inc.
17200 Southfield Road
Allen Park, Michigan
Attn: Mr. Eugene F. Hill

Wyman-Gordon Company
North Grafton, Massachusetts
Attn: Librarian

Westinghouse Electric
Aerospace Electrical Division
Lima, Ohio
Attn: Paul Kueser

Air Force Materials Laboratory
Research and Technology Division
Wright-Patterson Air Force Base, Ohio 45433
Attn: C. L. Harmsworth

Johns Hopkins University
Applied Physics Laboratory
8621 Sergia Avenue
Silver Spring, Maryland
Attn: Librarian