

New Synthesis of TATB. Process Development Studies

Robert D. Schmidt
Alexander R. Mitchell
Philip F. Pagoria

This paper was prepared for submittal to the
JOWOG 9 (Joint Working Group 9)
Aldermaston, England
June 22-26, 1998

May 1998

This is a preprint of a paper intended for publication in a journal or proceedings. Since changes may be made before publication, this preprint is made available with the understanding that it will not be cited or reproduced without the permission of the author.



DISCLAIMER

This document was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor the University of California nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or the University of California, and shall not be used for advertising or product endorsement purposes.

NEW SYNTHESIS OF TATB. PROCESS DEVELOPMENT STUDIES

Robert D. Schmidt, Alexander R. Mitchell and Philip F. Pagoria

Lawrence Livermore National Laboratory, Energetic Materials Center, Livermore, California 94551, USA

ABSTRACT


We have discovered that 1,1,1-trialkylhydrazinium salts are highly reactive reagents which aminate nitroaromatic compounds through vicarious nucleophilic substitution (VNS) of hydrogen. When applied to picramide, these reagents produce TATB in high yield. Traditionally, TATB has been manufactured in the USA by nitration of the relatively expensive and domestically unavailable 1,3,5-trichlorobenzene (TCB) to give 2,4,6-trichloro-1,3,5-trinitrobenzene (TCTNB) which is then aminated to yield TATB. Elevated temperatures (150° C) are required for both reactions. Our new VNS synthesis potentially affords an inexpensive and a more environmentally benign preparation of TATB. We describe in this report our progress in scaling up the synthesis of TATB from the laboratory to the pilot plant. We will discuss structure and control of impurities, changes in yield/quality with reaction conditions, choice of solvents, workup and product isolation, safety, and environmental considerations. Particle size characterizations as well as small-scale safety and performance testing will also be discussed.

INTRODUCTION

The compound 1,3,5-triamino-2,4,6-trinitrobenzene (TATB) is a reasonably powerful high explosive (HE) whose thermal and shock stability is considerably greater than that of any other known material of comparable energy.¹ The high stability of TATB favors its use in military² and civilian applications³ when insensitive high explosives are required. In addition to

its applications as a HE, TATB is used to produce the important intermediate benzenehexamine.⁴⁻⁸ Benzenehexamine has been used in the preparation of ferromagnetic organic salts⁸ and in the synthesis of new heteropolycyclic molecules such as 1,4,5,8,9,12-hexaazatriphenylene (HAT) that serve as strong electron acceptor ligands for low-valence transition metals.^{5,7} The use of TATB to prepare components of lyotropic liquid-crystal phases for use in display devices is the subject of a German patent.⁹

There is a definite need for a less expensive and more environmentally benign production of TATB. Current production techniques for making TATB are expensive and rely on environmentally hazardous reagents and relatively harsh conditions. We recently reported a novel approach to the synthesis of TATB which utilizes relatively inexpensive starting materials and mild reaction conditions.¹⁰⁻¹² This new process relies on amination of nitroaromatic starting materials using a reaction known as Vicarious Nucleophilic Substitution (VNS) of hydrogen.¹³ Scheme 1 outlines the approach.




Scheme 1. VNS Synthesis of TATB from Picramide.

We have been working on the scale-up of this new synthesis with the goal of developing a new production of TATB. This paper examines the influence of aminating reagent, base, solvent, temperature, quenching, etc. on yield, purity and morphology of TATB product.

PROCESS STUDIES WITH 1,1,1-TRIMETHYLHYDRAZINIUM IODIDE AS THE VNS AMINATING REAGENT

Initial Studies

We have determined that 1,1,1-trimethylhydrazinium iodide (TMHI) is the most efficient aminating reagent available for the VNS synthesis of TATB.^{10-12,14} Picramide and solid TMHI are dissolved in DMSO, and base (sodium methoxide or ethoxide) is added to initiate the reaction. The reaction is conducted at room temperature, and is complete in under 3 hours, giving TATB in 80-90% yield (Scheme 2).



Scheme 2. VNS Synthesis of TATB using TMHI

The major expected impurity is 1,3-diamino-2,4,6-trinitrobenzene (DATB), which results from incomplete amination. Under these reaction conditions, no DATB ($\leq 0.5\%$) was detected by FTIR spectroscopy or direct insertion solids probe mass spectrometry (DIP-MS).

Studies on Varying Reaction Conditions

The initial studies of this reaction employed picramide concentrations $\leq 0.13\text{ M}$ with large excesses of TMHI and base to drive the reaction to completion. We examined the effects of

decreased solvent and reagents on the reaction. Table 1 summarizes some of the results of this study.

Entry	Mole Ratio of Reagents (Picramide:TMHI: Base)	Base Used	Molarity of Picramide, mol/L	% Yield (Total Product)	Purity of TATB, %
1	1 : 5 : 10	NaOMe	0.13	89	> 99
2	1 : 4 : 8	NaOMe	0.11	82	> 99
3	1 : 4 : 8	NaOMe	0.22	86	≈ 97
4	1 : 4 : 8	NaOEt	0.22	80	≈ 97
5	1 : 2.5 : 5.6	NaOMe	0.27	86	88
6	1 : 3.1 : 8.4	NaOMe	0.11	81	> 99

Table 1. Effect on yield of TATB by varying quantities of reagents.

In general, the reaction will run efficiently up to 0.2 M picramide and using 3 eq. TMHI. The success of the reaction seems most dependent on base, requiring 8 eq. to proceed efficiently. The yield and purity of TATB drop significantly if an insufficient excess of base is used. It was also found that the reaction is very sensitive to the quality of the base, particularly in the case of sodium methoxide: older lots of the base which had been exposed to air, even while retaining the identical physical appearance of fresh material, gave reduced yields (or, in the worst case, no yield at all) of TATB.

Thus far, the largest scale attempted has been the 10 gram level. The reaction appears to scale linearly, delivering 82% yield of TATB at >99% purity. Larger scale work is currently in progress.

Methods of Quenching the Reaction

All initial studies of this reaction used either aqueous mineral acid solutions or water to quench the reaction and induce precipitation of TATB. This method results in a very small particle size, on the order of 0.2-1 μm . It was reasoned that quenching with a weak organic acid

in the absence of water might result in larger particle size. We found that quenching with citric acid monohydrate in DMSO produced particles in the 1-10 μm range. A larger particle size (20 μm) has recently been obtained using other organic acids.¹⁵ It was also noticed that the final color of the product TATB varied when different quenching solutions were used (Table 2).

Entry ¹	TMHI Addition Method ²	Quench Method	% Yield TATB	Physical Appearance
1	solid	aq. HCl	--	Yellow powder, >99% TATB
2	solid	aq. HNO_3	82	pale tan-yellow powder, >99% TATB
3	in situ	aq. HNO_3	86	pale tan-yellow powder, >99% TATB
4	solid	citric acid/DMSO	80	yellow-maize powder, >99% TATB
5	in situ	citric acid/DMSO	86	yellow-maize powder, >99% TATB

Notes: 1. Reaction conditions were 2 mmol picramide, 4eq TMHI, 8eq NaOMe in 20 mL DMSO.
2. See next section for description of TMHI addition methods.

Table 2. Effects of varying TMHI addition method and quenching method.

In Situ Generation of TMHI

Although TMHI is easy to prepare and handle^{12,14} its use in the solid form requires an additional synthesis and isolation step, which would increase the overall product costs at production scale. Therefore, several experiments were conducted which examined the *in situ* generation of the reagent. To accomplish this, the precursor reagents--1,1-dimethylhydrazine and methyl iodide--were sequentially added to DMSO and allowed to react. Picramide was then added to this solution, followed by base, and the reaction was allowed to proceed as before. This method appears to give at least as good results as the original method, and in several cases gave slightly higher yields of TATB (Table 2).

Quality of Starting Materials

As mentioned earlier, the reaction appears to be very sensitive to the condition of the sodium methoxide. Several attempts at making TATB using an older lot of NaOMe failed, even though the base had been stored in a dessicator and the physical appearance of the base was no different from newer material (white, free-flowing fine powder). Analysis of this lot of NaOMe revealed that much of it had been converted to sodium carbonate by absorption of ambient CO₂ which inactivated it in the VNS reaction. Good yields (>85%) were again obtained when fresh NaOMe was employed.

In a few experiments, there was some variation in the purity of the starting picramide, and this appears to have affected the final appearance of the TATB, even though the TATB appears to be chemically >99% pure by spectroscopy. The principal impurity in the picramide was picryl chloride (vide infra). Impurity levels of greater than a few percent cause the product TATB to darken and, of course, reduce the total yield of TATB (although corrected yields are similar to those using pure picramide). High levels of impurities in starting picramide also change the crystal morphology of the product TATB.

Product Analysis

Since TATB is nearly insoluble in most solvents, simpler forms of chemical analysis such as NMR or Gas Chromatography are not practicable. Therefore, other techniques which allow analysis of the solid were investigated. The first of these attempted was Fourier Transform Infrared Spectroscopy (FTIR). The amine N-H stretching modes in TATB produce two characteristic absorptions at approximately 3225 and 3325 cm⁻¹, while those for DATB occur at 3360 and 3390 cm⁻¹. By using Nujol mull preparations for TATB samples, we have found that DATB can be reliably detected at concentrations of 1% or greater.

Another technique for TATB product analysis which we are using is direct insertion solids probe mass spectrometry (DIP-MS). In this technique, a solid sample of TATB is placed

in a sample holder at the end of a probe. The probe tip is inserted into a mass spectrometer, and is heated to cause the solid sample to evaporate into the MS ion volume, thereby allowing analysis of solids. Compounds with differing volatilities will evaporate at different times (a process known “probe distillation”) and can thus be resolved to some extent by the MS detector. We have found that DATB can be reliably detected in a TATB sample at 1% concentration, and in some cases in concentrations as low as 0.1%.


Selected samples were submitted for elemental analysis. In early samples, the elemental analysis revealed that the product TATB was contaminated with 1-2% iodine. Unreacted TMHI as a source of iodine contamination was ruled out as TMHI could not be detected in the TATB samples using mass spectroscopy. We are examining the effects of quenching methods on impurities such as iodine, chlorine, etc.

In order to compare the TATB from this VNS process to that from more traditional processes, we have also conducted DSC, CRT, DH₅₀, spark and friction sensitivity tests on this material. In general, results are similar to those observed for TATB, except that thus far, the DSC values run consistently low by about 20-30 degrees. This may be an artifact of the much finer particle size produced by this process, although to confirm this more tests will be needed.

PROCESS STUDIES WITH HYDROXYLAMINE AS THE VNS AMINATING REAGENT

Due to the relative toxicity and cost of reagents used to make TMHI, we reinvestigated the use of hydroxylamine as a VNS aminating reagent. Hydroxylamine is in fact, the earliest known example of a VNS aminating reagent,¹⁶ although the term “VNS” was coined many decades later.¹³ Our earliest work in aminating picramide with hydroxylamine was disappointing since the reaction only provided DATB containing trace amounts of TATB at best.¹¹ The poor reactivity of hydroxylamine was independently confirmed by Seko and Kawamura who were unable to amiate nitrobenzene using hydroxylamine.¹⁷ The low cost of hydroxylamine as an aminating reagent initiated further investigation and recent work in our laboratories showed that

hydroxylamine will aminate picramide to TATB at elevated temperature (65-90°C) to furnish TATB (Scheme 3).¹⁸




Scheme 3. VNS Synthesis of TATB using Hydroxylamine Hydrochloride.

Although the work with hydroxylamine is preliminary, satisfactory yields of TATB at approximately 97% purity have been achieved. Thus far the best results were obtained using NaOEt as the base in DMSO at 65°C for 6-12 hours. We are in the process of testing other hydroxylamine salts and anticipate the purity of the product will increase to over 99%. The relatively low cost of hydroxylamine salts makes this option very attractive.

STUDIES OF PICRAMIDE SYNTHESIS

As mentioned earlier, picramide is no longer commercially available. Therefore, as part of this project, we were required to reinvestigate methods for its production. One simple method is nitration of 4-nitroaniline, an inexpensive commodity chemical (Scheme 4).¹⁹



Scheme 4. Synthesis of Picramide.

Early studies in our laboratories using similar conditions gave good results, although some impurities were noted, the most significant being picryl chloride. (The workup of picramide is facilitated by the addition of brine, which apparently gives rise to the picryl chloride impurity.) In one case, picryl chloride was present in up to 20% impurity. Such impurities would require expensive recrystallization processing, since they affect the quality of TATB produced, as discussed earlier. However, our project collaborators at Pantex (Mason & Hanger Corporation, Amarillo, Texas) have improved the process and have prepared picramide in high yields (90%) and purity (>99.5%).

ACKNOWLEDGEMENTS

We wish to acknowledge contributions to this project by Messrs. Ray Thorpe, W. Tim Quinlin, Patrick Phelan and Monty Cates (Mason & Hangar Co., Pantex Plant, Amarillo, Texas, USA), Dr. Michael Coburn (Los Alamos, New Mexico, USA) and Mr. Gregory Lee (LLNL). This work was performed under the auspices of the U.S. Department of Energy by Lawrence Livermore National Laboratory under Contract No. W-7405-ENG-48.

REFERENCES

1. Rice, S. F. and Simpson, R. L., "The Unusual Stability of TATB: A Review of the Scientific Literature," Lawrence Livermore National Laboratory, Livermore, CA, Report UCRL-LR-103683 (July, 1990).
2. Dobratz, B.M., "The Insensitive High Explosive Triaminotrinitrobenzene (TATB): Development and Characterization - 1888 to 1994," Los Alamos Scientific Laboratory, Los Alamos, NM, Report LA-13014-H, (August, 1995).

3. Voreck, W.E., Brooks, J.E., Eberhardt, J.R. and Rezaie, H.A., **U.S. Patent 5,597,974**, "Shaped Charge for a Perforating Gun Having a Main Body of Explosive Including TATB and a Sensitive Primer," January 28, 1997.
4. Kohne, B. and Praefcke, K., "Isolierung farblosen Benzolhexamins," *Liebigs Ann. Chem.*, **1987**, 265.
5. Rogers, D.Z., "Improved Synthesis of 1,4,5,8,9,12-Hexaazatriphenylene" *J. Org. Chem.*, **1986**, 51, 3904.
6. Kohne, B., Praefcke, K., Derz, T. Gondro, T. and Frolow, F., "Benzotri(imidazole) - a New Ring System Derived from Benzenehexamine," *Angew. Chem. Int. Ed. Engl.*, **1986**, 25, 650.
7. Nasielski-Hinkens, R., Benedek-Vamos, M., Maetens, D. and Nasielski, J., "A New Heterocyclic Ligand for Transition Metals: 1,4,5,8,9,12-Hexaazatriphenylene and its Chromium Carbonyl Complexes," *J. Organomet. Chem.*, **1981**, 46, 179
8. Breslow, R., Maslak, P. and Thomaides, J.S., "Synthesis of the Hexaaminobenzene Derivative Hexaazaoctadecahydrocoronene (HOC) and Related Cations," *J. Am. Chem. Soc.*, **1984**, 106, 6453.
9. Praefcke, K. and Kohne, B., "Amido Compounds as Components of Lyotropic Liquid-crystal Phases," Ger. Offen. DE 3,612,238; *Chem. Abstr.*, **1988**, 108, 159109n.
10. Mitchell, Alexander R.; Pagoria, Philip F.; Schmidt, Robert D. "A New Synthesis of TATB Using Inexpensive Starting Materials and Mild Reaction Conditions," in *Energetic Materials-Technology, Manufacturing and Processing*, Keicher, T., Ed., Proc. 27th Int. Annual Conf. of ICT. Karlsruhe, Germany, **1996**, 29.1-29.11.
11. Mitchell, A. R.; Pagoria, P. F.; Schmidt, R. D., **U.S. Patent 5,633,406**, "Vicarious Nucleophilic Substitution Using 4-Amino-1,2,4-triazole, Hydroxylamine or O-Alkylhydroxylamine to Prepare 1,3-Diamino-2,4,6-trinitrobenzene or 1,3,5-Triamino-2,4,6-trinitrobenzene", May 27, 1997.
12. Mitchell, A. R.; Pagoria, P. F.; Schmidt, R. D., **U.S. Patent 5,569,783**, "Vicarious Nucleophilic Substitution to Prepare 1,3-Diamino-2,4,6-trinitrobenzene or 1,3,5-Triamino-2,4,6-trinitrobenzene", October 29, 1996.
13. Makosza, M. and Winiarski, J. "Vicarious Nucleophilic Substitution of Hydrogen", *Acc. Chem. Res.*, **1987**, 20, 282.

14. Pagoria, P. F.; Mitchell, A. R.; Schmidt, R. D., "1,1,1-Trimethylhydrazinium Iodide: a Novel, Highly Reactive Reagent for Aromatic Amination *via* Vicarious Nucleophilic Substitution of Hydrogen", *J. Org. Chem.* **1996**, *61*, 2934.
15. Dr. Michael D. Coburn, personal communication.
16. J. Meisenheimer, J. and Patzig, E., "Directe Einführung von Aminogruppen in den Kern aromatischer Körper", *Ber.*, **1906**, *39*, 2533
17. Seko, S. and Kawamura, N., "Copper-Catalyzed Direct Amination of Nitrobenzenes with O-Alkylhydroxylamines," *J. Org. Chem.*, **1996**, *61*, 442.
18. Mitchell, A. R., Pagoria, P. F. and Schmidt, R. D, U.S. and Foreign Patent Applications have been filed.
19. Holleman, A. F., "1,3,4,5-Tetranitrobenzene," *Rec. trav. chim.*, **1930**, *49*, 112

Technical Information Department • Lawrence Livermore National Laboratory
University of California • Livermore, California 94551

